

**IDENTIFICATION OF VOLATILE CONTAMINANTS
OF SPACE CABIN MATERIALS**

J. V. PUSTINGER, JR.

F. N. HODGSON

W. D. ROSS

**Distribution of this
document is unlimited**

Contrails

FOREWORD

This study was conducted by the Dayton Laboratory of the Monsanto Research Corporation, 1515 Nicholas Road, Dayton, Ohio 45407, under Contract No. AF 33(615)-1779 with the Aerospace Medical Research Laboratories, Wright-Patterson Air Force Base, Ohio. This research was conducted as part of the joint Air Force/National Aeronautics and Space Administration Program on Space Cabin Toxicology. Materials used in this study were supplied by the Manned Spacecraft Center, NASA through McDonnell Aircraft Corporation. The principal investigators for the Monsanto Research Corporation, under the project leadership of Mr. John V. Pustinger, Jr., were Mr. F. Neil Hodgson and Mr. William D. Ross. The contract was initiated by the Toxic Hazards Branch, Physiology Division, Biomedical Laboratory, in support of Project 6302, "Toxic Hazards of Propellants and Materials," Task 630204, "Environmental Pollution." The technical monitor of the contract was Captain John A. Jurgiel of the Toxic Hazards Branch. This study was started in June 1964 and was completed in September 1965.

The authors acknowledge the invaluable assistance of Mr. Bruce E. Boggs, Mr. Donald Q. Douglas, Mr. Laurence R. DuFour, Mr. Richard L. Evers, Mr. Ralph R. Ferguson, Mr. John E. Strobel, and Mr. Guthrie Wheeler.

This technical report has been reviewed and is approved.

WAYNE H. McCANDLESS
Technical Director
Biomedical Laboratory
Aerospace Medical Research Laboratories

ABSTRACT

Fifty-five candidate materials for space cabin construction were stored for 30, 60 and 90 day periods at 23-25°C, and 20-40% R.H. in environments of air at a pressure of one atmosphere and oxygen at 5 psia. The composition of the gas-off products were determined by mass spectrometry and gas chromatography.

Considerable amounts of gas-off products were detected from candidate materials prepared immediately prior to testing, e.g., coatings, paints, and adhesives. Very little, if any, gas-off products were evolved from materials submitted as fabricated sections, e.g., polycarbonates, polyvinylfluorides, and nylon based material.

In general, the major gas-off products were solvents, plasticizers, and monomers. Some coatings desorbed considerable amounts of carbon monoxide. Others gave off relatively large quantities of trimethyl silanol and low molecular weight methyl siloxane polymers.

Although slight differences in relative amounts of alcohols and aldehydes were observed in some gas-off atmospheres, no large changes in atmospheric composition were observed that could be attributed to increased oxidation when materials were exposed at 23-25°C to oxygen at 5 psia.

Quantitative analyses of the gas-off products were influenced by: uniformity of sample lots, sample homogeneity, freshness of sample, free surface area, adsorptive characteristics of the encapsulating chamber, method of sampling the gaseous atmosphere, and method of analysis.

Additional analyses were performed on desorbates from four carbon canisters from space cabin simulators and the hydrolysis products of MCS 198.

Contrails

TABLE OF CONTENTS

<u>Section</u>		<u>Page No.</u>
I	INTRODUCTION	1
II	GAS-OFF EXPERIMENTS	3
	A. Experimental Method	3
	1. Types of Candidate Materials and Sample Preparation	3
	2. Preparation of Chamber Atmospheres	6
	3. Analytical Methods	7
	B. Results and Discussion	13
	1. Sample Preparation	13
	2. Analytical Methods	15
	3. Analytical Data	17
	4. Materials Producing No Gas-Off Products	21
	5. Materials Having Unique Gas-Off Characteristics	22
III	CARBON CANISTERS FROM SPACE CABIN SIMULATORS	28
	A. Experimental Method	28
	B. Results	28
IV	HYDROLYSIS OF MCS 198 IN PRESENCE OF LiOH	29
	A. Experimental Method	29
	B. Results and Discussion	30
V	CONCLUSIONS AND RECOMMENDATIONS	31

Contrails

Table of Contents - Cont'd

<u>Section</u>	<u>Page No.</u>
APPENDIX I	35
Analytical Results for Gas-Off Experiments	
APPENDIX II	77
Representative Mass Spectral Data for Gas-Off Experiments	
APPENDIX III	125
Representative Gas Chromatograms for Gas-Off Experiments	
APPENDIX IV	167
Carbon Desorption Analyses and Gas Chromatograms	
APPENDIX V	181
Analytical Data for Hydrolysis of MCS 198	
REFERENCES	193

Contrails

LIST OF TABLES

<u>Table</u>		<u>Page No.</u>
I	Candidate Materials	4
II	Absolute Sensitivities of GLC Instrumentation to Typical Compounds Found in Gas-Off Experiments	11
III	Types of Compounds Detected	18
IV	Candidate Materials Yielding No Gas-Off Products	21
V	Strong Ionic Species Observed in Mass Spectrum of Fluorolube FS-5 Gas-Off Products	23
VI	Sublimate from Silicone Grease G-300	26
VII	Gas-Off Products - Adhesive, A-4000	37
VIII	Gas-Off Products - Adhesive, No. 271	38
IX	Gas-Off Products - Resin, Versamid 125	39
X	Gas-Off Products - Neoprene, Phenolic EC-847	40
XI	Gas-Off Products - Silastic No. 950	41
XII	Gas-Off Products - Silastic S2007	42
XIII	Gas-Off Products - Silastic 950-4-400	43
XIV	Gas-Off Products - Silastic 9711-2-480	44
XV	Gas-Off Products Wire (MIL-W-16878-C) Type E 23-W-9	45
XVI	Gas-Off Products - Velvet Coating No. 104-C 10 Black	46
XVII	Gas-Off Products - Class H Silicone Impregnating Varnish No. 997	47
XVIII	Gas-Off Products - 620 Light Gull Gray Coating, XA-193	48
XIX	Gas-Off Products - 3614 Gray Coating, XA-194	49

Contrails

List of Tables - Cont'd

<u>Table</u>		<u>Page No.</u>
XX	Gas-Off Products - Silver Marking Ink No. 1448 (W/Cresylic Acid)	50
XXI	Gas-Off Products - Latex Foam Rubber	51
XXII	Gas-Off Products - Lockfoam C-605 (R&T)	52
XXIII	Gas-Off Products - Lockfoam E-302 (R&T)	53
XXIV	Gas-Off Products - Fluorolube Oil - Grade FS-5	54
XXV	Gas-Off Products - Fluorolube Grease - Grade GR-544 Type LG	55
XXVI	Gas-Off Products - Silicone Fluid No. 200	56
XXVII	Gas-Off Products - Silicone Fluid F-50	57
XXVIII	Gas-Off Products - Silicone Grease G-300	58
XXIX	Gas-Off Products - Silicone Release Agent DC-7	59
XXX	Gas-Off Products - DC-4 (MIL-I-8660)	60
XXXI	Gas-Off Products - Wax Lubricant No. 111	61
XXXII	Gas-Off Products - Silastic RTV-882	62
XXXIII	Gas-Off Products - Silastic RTV-731	63
XXXIV	Gas-Off Products - Sealant RTV-90	64
XXXV	Gas-Off Products - Silastic RTV-501	65
XXXVI	Gas-Off Products - Silastic C/R Q-3-0121	66
XXXVII	Gas-Off Products - Silicone EC 1663	67
XXXVIII	Gas-Off Products - Sealer, Epon 828	68
XXXIX	Gas-Off Products - Silicone Primer, A4004	69

Contrails

List of Tables - Cont'd

<u>Table</u>		<u>Page No.</u>
XL	Gas-Off Products - Silicone Primer, SS4004	70
XLI	Gas-Off Products - Silicone Primer, EC-1694	71
XLII	Gas-Off Products - Electrical Resin, Scotchcast No. 8	72
XLIII	Gas-Off Products - DC-325	73
XLIV	Gas-Off Products - Plexiglas No. 2 Clearmil	74
XLV	Gas-Off Products - Thermofit Tubing Splicer C/R 197-075	75
XLVI	Gas-Off Products - Acetal Resin, Delrin No. 100	76
XLVII	Representative Mass Spectral Data for Adhesive, A-4000	79
XLVIII	Representative Mass Spectral Data for Adhesive, No. 271	81
XLIX	Representative Mass Spectral Data for Resin, Versamid 125	82
L	Representative Mass Spectral Data for Neoprene, Phenolic EC-847	83
LI	Representative Mass Spectral Data for Silastic No. 950	84
LII	Representative Mass Spectral Data for Silastic S2007	85
LIII	Representative Mass Spectral Data for Silastic 950-4-500	86
LIV	Representative Mass Spectral Data for Silastic 9711-2-480	87
LV	Representative Mass Spectral Data for Wire (MIL-W-16878-C), Type E 22-W-9 5M114E22W9	88

Contrails

List of Tables - Cont'd

<u>Table</u>		<u>Page No.</u>
LVI	Representative Mass Spectral Data for Velvet Coating No. 104-C 10 Black	89
LVII	Representative Mass Spectral Data for Class H Silicone Impregnating Varnish, No. 997	90
LVIII	Representative Mass Spectral Data for 620 Light Gull Gray XA-193	91
LIX	Representative Mass Spectral Data for 3615 Gray XA-194	92
LX	Representative Mass Spectral Data for Silver Marking Ink No. 1448 (with Cresylic Acid)	93
LXI	Representative Mass Spectral Data for Latex Foam Rubber	94
LXII	Mass Spectral Data for Latex Foam Rubber Products Removed While Heating Under Vacuum	95
LXIII	Representative Mass Spectral Data for Lockfoam C-605 (R&T)	96
LXIV	Representative Mass Spectral Data for Lockfoam E-302 (R&T)	97
LXV	Representative Mass Spectral Data for Fluorolube Oil Grade FS-5	98
LXVI	Representative Mass Spectral Data for Fluorolube Grease Grade GR-544, Type LG	100
LXVII	Representative Mass Spectral Data for Silicone Fluid No. 200	102
LXVIII	Representative Mass Spectral Data for Silicone Fluid F-50	103
LXIX	Representative Mass Spectral Data for Silicone Grease G-300	104
LXX	Representative Mass Spectral Data for Silicone Release Agent DC-7	106

Contrails

List of Tables - Cont'd

<u>Table</u>		<u>Page No.</u>
LXXI	Representative Mass Spectral Data for DC-4 (MIL-I-8660)	107
LXXII	Representative Mass Spectral Data for Wax Lubricant No. 111	108
LXXIII	Representative Mass Spectral Data for Silastic RTV 882	109
LXXIV	Representative Mass Spectral Data for Silastic RTV 731	110
LXXV	Representative Mass Spectral Data for Sealant RTV 90	111
LXXVI	Representative Mass Spectral Data for Silastic RTV 501	112
LXXVII	Representative Mass Spectral Data for Silastic C/R Q-3-0121	113
LXXVIII	Representative Mass Spectral Data for Silicone EC 1663	114
LXXIX	Representative Mass Spectral Data for Sealer - Epon 828	115
XXC	Representative Mass Spectral Data for Silicone Primer A-4004	116
XXCI	Representative Mass Spectral Data for Silicone Primer SS-4004	117
XXCII	Representative Mass Spectral Data for Silicone Primer EC-1694	118
XXCIII	Representative Mass Spectral Data for Electrical Resin, Scotchcast No. 8	119
XXCIV	Representative Mass Spectral Data for DC-325	120
XXCV	Representative Mass Spectral Data for Plexiglas, No. 2 Clearmil	121

Contrails

List of Tables - Cont'd

<u>Table</u>		<u>Page No.</u>
XXCVI	Representative Mass Spectral Data for Thermofit Tubing Splicer C/R 197-075	122
XXCVII	Representative Mass Spectral Data for Acetal Resin, Delrin No. 100	123
XXCVIII	Mass Spectral Data for GLC Fraction of Component Common go Gas-Off Products from Magnesium/Lithium Alloys, LA-91, LA-141, and LA-2-933	124
XXCIX	Gas Chromatographic Instrument Conditions	127
XC	Gas Chromatographic Instrument Conditions for Analysis of Carbon Desorbates	169
XCI	Analysis of Desorbate from Carbon Canister 10-12 Day	170
XCII	Analysis of Desorbate from Carbon Canister 16-18 Day	171
XCIII	Analysis of Desorbate from Carbon Canister 26-28 Day	172
XCIV	Analysis of Desorbate from Carbon Canister 28 Day (Thomas)	173
XCV	Gas Chromatographic Instrument Conditions for Analysis of Hydrolysis Products of MCS 198	183
XCVI	MCS 198 + LiOH in Atmosphere of 35% Relative Humidity	184

Contrails

LIST OF FIGURES

<u>Figure</u>		<u>Page No.</u>
1	Gas-Off Chamber and Collection Helix	5
2	Carbon Monoxide and Methane Analyzer	9
3	F & M Model 810 Gas Chromatograph	10
4	Chamber to Helix Collection System	14
5	Gas Chromatograms of Gas-Off Products from Silicone Primer SS-4004	16
6	Infrared Spectrum of Sublimate from Silicone Grease, G300 (KBr pellet)	25
7	Gas Chromatogram of 10 Component Standard	129
8	Gas Chromatogram of Gas-Off Products from Adhesive, A-4000 (90 Days, Air)	130
9	Gas Chromatogram of Gas-Off Products from Adhesive #271 (30 Days, Oxygen)	131
10	Gas Chromatogram of Gas-Off Products from Resin, Versamid 125 (90 Days, Air)	132
11	Gas Chromatogram of Gas-Off Products from Neoprene, Phenolic EC-847 (30 + 30 Days, Air)	133
12	Gas Chromatogram of Gas-Off Products from Silastic #950 (90 Days, Oxygen)	134
13	Gas Chromatogram of Gas-Off Products from Silastic S2007 (90 Days, Oxygen)	135
14	Gas Chromatogram of Gas-Off Products from Velvet Coating No. 104-C 10 Black (30 + 30 + 30 Days, Air)	136
15	Gas Chromatogram of Gas-Off Products from Class H Silicone Impregnating Varnish, No. 997 (30 + 30 + 30 Days, Oxygen)	137
16	Gas Chromatogram of Gas-Off Products from 620 Light Gull Gray Coatings XA-193 (90 Days, Oxygen)	138

Contrails

List of Figures - Cont'd

<u>Figure</u>		<u>Page No.</u>
17	Gas Chromatogram of Gas-Off Products from 3615 Gray Coating XA-194 (90 Days, Oxygen)	139
18	Gas Chromatogram of Gas-Off Products from Silver Marking Ink No. 1448 (with Cresylic Acid) (30 + 30 Days, Oxygen)	140
19	Gas Chromatogram of Gas-Off Products from Lockfoam E-302 (R and T) (60 Days, Oxygen)	141
20	Gas Chromatogram of Gas-Off Products from Fluorolube Oil Grade FS-5 (90 Days, Oxygen)	142
21	Gas Chromatogram of Gas-Off Products from Fluorolube Grease Grade GR-544 Type L.G. (90 Days, Oxygen)	143
22	Gas Chromatogram of Gas-Off Products from Silicone Fluid F-50 (90 Days, Air)	144
23	Gas Chromatogram of Gas-Off Products from Silicone Grease G-300 (90 Days, Oxygen)	145
24	Gas Chromatogram of Gas-Off Products from Silicone Release Agent DC-7 (90 Days, Air)	146
25	Gas Chromatogram of Gas-Off Products from DC-4 (MIL-I-6880) (90 Days, Oxygen)	147
26	Gas Chromatogram of Gas-Off Products from Wax Lubricant #111 (90 Days, Air)	148
27	Gas Chromatogram of Gas-Off Products from Silastic RTV-882 (30 + 30 + 30 Days, Oxygen)	149
28	Gas Chromatogram of Gas-Off Products from Silastic RTV-731 (60 Days, Oxygen)	150
29	Gas Chromatogram of Gas-Off Products from Sealant RTV-90 (30 + 30 + 30 Days, Oxygen)	151
30	Gas Chromatogram of Gas-Off Products from Silastic RTV-501 (60 Days, Oxygen)	152
31	Gas Chromatogram of Gas-Off Products from Silastic C/R Q-3-0121 - Sealant Q-3-0121 (30 Days, Air)	153

Contrails

List of Figures - Cont'd

<u>Figure</u>		<u>Page No.</u>
32	Gas Chromatogram of Gas-Off Products from Silicone EC-1663 (30 + 30 Days, Air)	154
33	Gas Chromatogram of Gas-Off Products from Sealer - Epon 828 (30 + 30 + 30 Days, Oxygen)	155
34	Gas Chromatogram of Gas-Off Products from Silicone Primer A-4004 (30 + 30 Days, Air)	156
35	Gas Chromatogram of Gas-Off Products from Silicone Primer SS-4004 (30 + 30 + 30 Days, Oxygen)	157
36	Gas Chromatogram of Gas-Off Products from Silicone Primer SS-4004 (60 Days, Oxygen)	158
37	Gas Chromatogram of Gas-Off Products from Silicone Primer EC-1694 (90 Days, Air)	159
38	Gas Chromatogram of Gas-Off Products from Electrical Resin Scotchcast #8 (60 Days, Oxygen)	160
39	Gas Chromatogram of Gas-Off Products from DC-325 (30 + 30 + 30 Days, Oxygen)	161
40	Gas Chromatogram of Gas-Off Products from Plexiglas No. 2 Clearmil (30 Days, Oxygen)	162
41	Gas Chromatogram of Gas-Off Products from Magnesium Lithium Alloy La-91 (9% Lithium) (30 Days, Oxygen)	163
42	Gas Chromatogram of Gas-Off Products from Magnesium Lithium Alloy LA-141 (14% Lithium) (30 Days, Oxygen)	164
43	Gas Chromatogram of Gas-Off Products from Magnesium Lithium Alloy LA2-933 (9% Lithium) (30 Days, Oxygen)	165
44	Gas Chromatogram of Desorption Products of Carbon 16-18 Day (-76°C Fraction)	174

Contrails

List of Figures - Cont'd

<u>Figure</u>		<u>Page No.</u>
45	Gas Chromatogram of Desorption Products of Carbon 16-18 Day (0°C Fraction)	175
46	Gas Chromatogram of Desorption Products of Carbon 16-18 Day (23°C Fraction) Using Carbowax 4000 Column	176
47	Gas Chromatogram of Desorption Products of Carbon 16-18 Day (23°C Fraction) Using Octoil S Column	177
48	Gas Chromatogram of Desorption Products of Carbon 16-18 Day (100°C Fraction) Using Carbowax 4000 Column	178
49	Gas Chromatogram of Desorption Products of Carbon 16-18 Day (100°C Fraction) Using Octoil S Column	179
50	Gas Chromatogram of Gaseous Product from MCS 198 and LiOH (1 hour)	185
51	Gas Chromatogram of Gaseous Product from MCS 198 and LiOH (1 hour + 5 hours)	186
52	Gas Chromatogram of Gaseous Product from MCS 198 and LiOH (1 hour + 5 hours + 18 hours)	187
53	Gas Chromatogram of Gaseous Product from MCS 198 and LiOH (6 hours)	188
54	Gas Chromatogram of Gaseous Product from MCS 198 and LiOH (24 hours)	189
55	Gas Chromatogram of Gaseous Product from MCS 198 (24 hour Blank - no LiOH)	190
56	Gas Chromatogram of Gaseous Product from MCS 198, LiOH and Water (24 hours)	191
57	Gas Chromatogram of Gaseous Product from MCS 198 Sprayed onto LiOH·H ₂ O	192

Contrails

SECTION I

INTRODUCTION

A potential problem in manned space programs is the possible contamination of the cabin atmosphere. Considerable data on trace atmospheric contaminants from the atomic submarine programs (Refs. 1-12) and from various space cabin simulators (Refs. 12-18) have shown that sources of contamination may include biological products and the materials of construction. Limited information on the specific gas-off products from individual cabin materials is available (Refs. 19-20).

To establish the possible gas-off and oxidation products from cabin materials, a program using bench-scale environmental simulators was initiated. Fifty candidate materials were tested and over 1000 gaseous environments were analyzed to identify the gas-off products and to estimate the concentration and the gas-off rates of these potential contaminants. All materials were commercial products provided by the Government. Some were partially-fabricated sections from the Gemini program, whereas others required preliminary preparation.

The experiments were designed to simulate normal conditions, 23-25°C and 20-40% relative humidity, in two atmospheres, air at normal atmospheric pressure and oxygen at 5 psia. To obtain a measure of gas-off rate, all candidate materials were stored in 9-liter, borosilicate glass chambers for periods of 30, 60 and 90 days.

Analysis of the atmospheres from the gas-off chambers was performed by three different analytical operations:

1. Gas chromatographic analysis for carbon monoxide and methane after catalytic reduction of the carbon monoxide.
2. Direct gas chromatographic and mass spectrometric analyses of atmospheres from the gas-off chambers.
3. Condensation of gas-off products at -195°C, fractionation of the composite by gas chromatography, and characterization of the fractions by mass spectrometry and infrared spectrophotometry.

In addition to the gas-off experiments, two other analyses were performed:

Contracts

1. Identification of desorbates from carbon canisters used in space cabin simulators.
2. Characterization of the hydrolysis products and volatiles formed in the reaction of MCS 198 with LiOH and H₂O.

SECTION II

GAS-OFF EXPERIMENTS

A. EXPERIMENTAL METHOD

1. Types of Candidate Materials and Sample Preparation

Table I lists the candidate materials for cabin construction used in these experiments. All materials were commercial products provided by the Government.

The candidate materials were stored at 23-25°C and 20-40% relative humidity in two atmospheres, air at normal atmospheric pressure, and oxygen at 5 psia. Five test periods were used with each atmosphere.

Individual samples of each candidate material were stored for gas-off periods of 30, 60 and 90 days. Since the freshness of the sample could easily influence the type and the amount of gas-off product, the 30 day test chambers were analyzed, purged of their environments and recharged with air or oxygen. After an additional 30 day period, the atmosphere of the chamber was again analyzed, purged, and recharged. Following an additional 30 days of storage, the chamber was analyzed. The five test periods are designated as: (a) 30-Days, (b) 60-Days, (c) 90-Days, (d) 30 + 30-Days, and (e) 30 + 30 + 30-Days. For each test, duplicate chambers were prepared and analyzed.

All candidate materials were stored in 9-liter, borosilicate glass chambers. Special chamber inlet systems were constructed from borosilicate glass and fitted with greaseless Teflon stopcocks and with Teflon sleeves for the ground joint (Figure 1). Two hundred and ten chambers were used on a staggered schedule over a span of 14 months to permit over 1000 analyses to be performed on a 30, 60 and 90 day schedule.

Before use, chambers were: (a) cleaned with either chromic acid cleaning solution or Fisher Detergent RBS-25 Concentrate, (b) rinsed with distilled water (3 times), and (c) dried with the full heat and air flow of a Master Appliance Heat Gun, NG-501LP (minimum temperature rating of 500°F) for 20 minutes. Analyses of the atmospheres in these chambers by mass spectrometry indicated no contamination.

After completion of a test, the candidate material was removed and the chamber was cleaned according to the procedure shown above. In some cases, pretreatment with an organic

Contrails

Table I

CANDIDATE MATERIALS

I. ADHESIVES

Adhesive, A-4000
Adhesive, No. 271
Resin, Versamid 125
Neoprene, Phenolic EC-847
Adhesive Tape C/R No. 465 (Y 9010)

II. ELASTOMERS

Elastic Webbing, 731-5RDC
Silastic No. 950
Silastic S2007
Silastic 950-4-400
Silastic 9711-2-480

III. ELECTRICAL INSULATION AND WIRING

Wire (MIL-W-16878-C), Type E 22-W-9
5M114E22W9

IV. FINISHES, COATINGS AND MARKING MATERIALS

Velvet Coating No. 104-C 10 Black
Class Silicone Impregnating Varnish, No. 997
620 L₁ + Gull Gray XA-193
3615 Gray XA-194
Red Dye, Red PL
Silver Marking Ink No. 1448 (with cresylic acid)

V. FOAMS

Latex Foam Rubber
Lockfoam C-605 (R and T)
Lockfoam E-302 (R and T)
Lockfoam G-502 (R and T)
Silastic Sponge 445 Base
(3.5/300 + 10/400)

VI. GREASES AND LUBRICANTS

Fluorolube Oil Grade FS-5
Fluorolube Grease Grade GR-544, Type LG
Silicone Fluid No. 200
Silicone Fluid F-50
Silicone Grease G-300
Silicone Release Agent DC-7
DC-4 (MIL-I-8660)
Wax Lubricant No. 111

VII. MOLDING MATERIALS

(See Section IX)

VIII. PLASTIC LAMINATES

(None)

IX. POTTING AND SEALING COMPOUNDS

Silastic RTV 882
Silastic RTV 731
Sealant RTV 90
Silastic RTV 501
Silastic C/R Q-3-0121
Silicone EC 1663
Sealer - Epon 828
Silicone Primer A-4004
Silicone Primer SS-4004
Silicone Primer EC-1694
Electrical Resin, Scotchcast No. 8
DC-325

X. THERMOPLASTICS

Polycarbonate, Lexan (1 1/4" cylinder)
Polycarbonate, Lexan (1 1/4" x 2 1/4" x 36")
Polyvinylfluoride
Plexiglas Clear No. 2 (MIL-P-5425)
Plexiglas No. 2 Clearmil
Blue Thermofit RNF 100
Thermofit Tubing Splicer
C/R 197-075
Thermofit Molded Parts Type S
(6005-2915-S) (5M83354)
Nylatron G5 (MILP-46060)
Acetal Resin, Delrin No. 100

XI. MISCELLANEOUS

LA-91, Magnesium/Lithium Alloy
LA-141, Magnesium/Lithium Alloy
LA-2-933, Magnesium/Lithium Alloy



Figure 1. Gas-Off Chamber and Collection Helix.

Contrails

solvent, e.g., methylene chloride, chloroform or acetone, was required. Whenever the use of the organic solvent was necessary, the full cleaning process was repeated several times to eliminate contamination, as determined by mass spectrometry.

A weighed portion (10-100 grams) of each sample was placed into the 9-liter chamber in a manner to provide the largest possible surface area. Whenever possible, the candidate materials were put into the chambers in the same state as received. Materials such as paints and inks were applied to an aluminum foil substrate and allowed to dry under conditions of temperature and time designated by the manufacturer. Similarly, two-part resins were mixed and cured according to procedures submitted by the manufacturers. All calculations were made on basis of the dry sample weight. Control chambers (containing only aluminum foil) were processed concurrently with those chambers containing the test materials. No contamination was detected from the control chambers.

2. Preparation of Chamber Atmospheres

a. Air at 23-25°C, 1 Atmosphere Pressure and 20-40% Relative Humidity

Chambers were purged with six to ten changes of air-zero gas (less than 2 ppm hydrocarbon) supplied by Matheson Co. Relative humidity was adjusted to 20-40% by bubbling the air-zero gas through triply distilled water cooled externally to 0°C in an ice bath and by allowing the air to reach equilibrium in the chamber at approximately 20-23°C. Measurement of relative humidity was made on the effluent gas from the chamber with an Alnor type 7300 Dew-Pointer. The chambers were stored in the absence of light in large metal cabinets for the 30, 60 and 90 day periods. Agitation of samples was performed every seven days.

b. Oxygen at 23-25°C, 5 psia, and 20-40% Relative Humidity

The relative humidity of oxygen-zero gas (less than 10 ppm hydrocarbon) supplied by Matheson Co. was adjusted to between 20 and 40% by the following procedure. The chamber was purged with six to ten changes of oxygen saturated with water by bubbling the gas through triply distilled water at 23°C. The pressure in the chamber was reduced to 260 mm Hg (5 psia), removing roughly 2/3 of the oxygen and 2/3 of the water. Thus, the relative humidity was approximately 33%. Measurement of relative humidity was made with an Alnor Type 7300 Dew-Pointer.

Contrails

Because of slight differences in characteristics of the ground joints, some of the chambers would not maintain the reduced pressure of 5 psia. Minor leaks were eliminated by the use of either of two sealants, Apiezon wax or a polyester cement, Atlantic Hard Cement, both routinely used in mass spectrometry and possessing low vapor pressures. These sealants were applied only to the exterior crevices of the joints. Very little, if any, of the sealants was exposed to the chamber atmosphere. In either case, control chambers were processed concurrently. No contamination was detected from the sealants.

3. Analytical Methods

In the first stages of the program, all analyses, except the carbon monoxide determination, were performed on the condensates obtained by passing the total atmosphere from the 9-liter chamber through a trap cooled to -195°C with liquid nitrogen. The pressure in the trap was maintained at less than 0.5 atmosphere to minimize the condensation of oxygen (Ref. 17).

Later development of more efficient mass spectrometric and gas chromatographic techniques⁽¹⁾ resulted in an increase in sensitivity and attendant lower detection levels. Analytical methods were developed which use aliquots of chamber atmosphere and allowed the detection of <0.001 mg of individual contaminant/10 grams of candidate material in a 9-liter volume of chamber atmosphere. Only, in the extreme cases, where little, if any, gas-off products were evolved, was the total 9-liter volume processed.

a. Gas Chromatographic Analysis for Methane and Carbon Monoxide

Carbon monoxide and methane were determined by using a variation of a sensitive and accurate gas chromatographic method developed by Schwenk, et al. (Ref. 21). A 3.3 ml gas sample (measured volume of a commercial 5 ml sample loop) from the test chamber is passed through a Linde 5A molecular sieve to isolate carbon monoxide from the other atmosphere gases, particularly methane. The carbon monoxide is reduced to methane by passage over a nickel catalyst at 360°C in an atmosphere of hydrogen

(1) Approximately 4-fold increase in sensitivity was obtained by operating the F&M Gas Chromatograph, Model 810, with a single flame ionization detector rather than with the normal dual flame detection system.

carrier gas. Methane originally present and that produced from the reduction of carbon monoxide, are eluted separately and detected by a flame ionization detector. The peaks are compared with a standard concentration of carbon monoxide in nitrogen. The sensitivity is approximately 2×10^{-8} grams of carbon monoxide. The analytical system is shown in Figure 2. A cross-check of the higher carbon monoxide levels was made with a Monoxor carbon monoxide detector tube.

b. Gas Chromatographic Analysis of Gas-Off Products

Gas chromatography was used primarily for its high efficiency fractionating capability. Component identification from retention data and quantitative analyses by peak height were used only to support mass spectrometry data.


The general analyses of the gas-off products by gas chromatography were performed by introducing 25 ml of the atmosphere from the gas-off chambers directly into the gas chromatograph by the sampling system illustrated in Figure 3. The calibrated sample loop was evacuated and attached directly to the 9-liter chamber by a ground glass joint.

Larger volumes can be sampled, if needed, but 25 ml is the volume of chamber atmosphere which, in general, permits operation of the chromatograph with minimum peak broadening and no significant loss of resolution. Also, the removal of such a small relative volume from the 9-liter chamber permits repeated samplings without upsetting the equilibrium. As determined by sampling at various heights in the chamber, there is no evidence for stratification of gas-off components.

The chamber atmospheres were analyzed on an F and M Model 810 Research Gas Chromatograph equipped with two recording systems and three detectors, dual flame ionization, thermal conductivity and electron capture. Most of the analyses were performed using the flame ionization detection system.

In most cases, a general purpose column, Carbowax 20M on Gas Pack F (temperature programmed 40° - 230° C at 10° C/min.), was used because of its excellent partitioning properties for both polar and nonpolar compounds, and its stability at relatively high temperatures. Other columns were employed as needed. Gas chromatography instrument conditions are presented in Table XXCIX, Appendix III.


When needed, quantitative gas chromatography data were obtained by comparing the peak heights with those of a standard mixture. Table II lists typical compounds and their respective detection limits with the flame ionization detector.



**A. HYDROGEN FLOWMETER.
B. FLOW REGULATOR.
C. TOGGLE VALVE BY-PASS SYSTEM.
D. BARBER-COLMAN GAS SAMPLING VALVE (DETACHABLE).**

**E. CHROMATOGRAPHIC COLUMN AND OVEN.
F. CATALYTIC COLUMN AND OVEN.
G. FLAME IONIZATION DETECTOR.
H. AMPLIFICATION AND RECORDING SYSTEM.**

Figure 2. Carbon Monoxide and Methane Analyzer.



- A. FLOWMETER.
- B. PERKIN-ELMER GAS SAMPLING VALVE WITH TOGGLE VALVES [⊗] ON SAMPLE INLET AND VACUUM LINE.
- C. GAS-OFF CHAMBER ATTACHES HERE.
- D. CHROMATOGRAPHIC COLUMN AND OVEN.
- E. SAMPLE SPLITTER [1:10 RATIO].
- F. THERMAL CONDUCTIVITY DETECTOR.
- G. FRACTION COLLECTOR AND HEATER.
- H. FRACTION COLLECTOR ATTACHES HERE.
- I. FLAME IONIZATION DETECTOR.
- J. AMPLIFICATION AND RECORDING SYSTEM.

Figure 3. F & M Model 810 Gas Chromatograph and Sampling System.

Table II

ABSOLUTE SENSITIVITIES OF GLC INSTRUMENTATION
TO TYPICAL COMPOUNDS FOUND IN GAS-OFF EXPERIMENTS

<u>Compounds</u>	<u>Weight, grams</u>
ethanol	1.4×10^{-7}
isopropanol	4.1×10^{-7}
n-propanol	8.5×10^{-7}
iso-butanol	6.3×10^{-8}
benzene	4.3×10^{-8}
toluene	4.2×10^{-8}
xylene	5.0×10^{-8}
m-dichlorobenzene	8.3×10^{-8}
trichloroethylene	2.5×10^{-7}
methyl methacrylate	4.8×10^{-8}

Contrails

Identifications of gas chromatographic fractions were made by collecting components from the effluent gases and by subsequently characterizing them with mass spectrometry or infrared spectrophotometry. Fractions were isolated by splitting the effluent gases, permitting a small percentage (10%) to pass through the flame ionization detector and directing the rest through the trapping system. Several collection systems were used including the F and M Total Collection System, cold traps of various shapes, and packed and unpacked capillaries. A heated outlet was used to eliminate condensation and contamination in the effluent lines of the chromatograph.

c. Mass Spectrometric Analysis of Gas-Off Products

A Consolidated Electrodynamics Corporation Model 21-103C Mass Spectrometer was used in these analyses. This instrument gives complete resolution of mass 350 with usable peak separation to mass 700 or more. Only a few micromoles of material are needed to obtain a suitable spectrum. A heated inlet, maintained at a temperature of 135°C, was used which permitted the introduction of relatively nonvolatile liquids and solids.

Since considerable amounts of gas-off products were obtained from many of the candidate materials, generally only a portion (125 ml) of the atmosphere of the 9-liter bottle was taken for analysis. In cases where the amounts of gas-off products were low, the products were frozen from the entire nine liters of atmosphere. In either case the contaminants were frozen with liquid nitrogen and the oxygen and nitrogen were removed. Water and CO₂ remained along with the gas-off products. The pressure of the material remaining in the trap of known volume was measured, then the mass spectrum was obtained. If large amounts of gas-off products were obtained, they were weighed.

In some cases, the major gas-off components could be identified directly from the mass spectrum. Often, collection of gas chromatographic fractions was necessary to identify minor components. After a component was definitely established as being present, a quantitative estimate of the level was made by using the pressure of the gas-off products at a known volume to indicate the total amount of off-gassing, and the characteristic mass line intensities to provide the amount of each individual component.

d. Collection of Total Amount of Gas-Off Products from Chambers

In cases where little, if any, gas-off products were detected in the general analysis by using gas chromatography or mass spectrometry, the total gaseous atmosphere in the chamber was

processed through the sample trapping system shown in Figure 4. The condensate obtained at -195°C was analyzed by gas chromatography and mass spectrometry.

To ensure complete removal of all gases, a volume of pre-purified nitrogen several times the volume of the chamber was drawn through the system, and metered by means of a flowmeter. Isolation of condensables was accomplished by purging the chamber atmosphere through a helix, similar to that shown in Figure 1, which was cooled with a liquid nitrogen bath. To eliminate condensation of oxygen, purging was performed slowly with the pump of the trapping system maintaining pressure of approximately 0.5 atmosphere or less. Under these conditions, oxygen will not liquefy in the trap (Ref. 17). The pressure in the system can be adjusted by means of the needle valves at either end of the trapping train. The needle valves and interconnecting joints were Teflon or Teflon clad.


B. RESULTS AND DISCUSSION

1. Sample Preparation

Difficulties were encountered in attempting to obtain sample uniformity. Since most of the candidate materials were submitted for testing in a number of small, individual containers, a problem of mixing existed. Although care was taken to ensure uniformity in mixing and sampling, some inhomogeneities occurred resulting in minor differences in relative amounts of gas-off products.

The problem of inhomogeneity became very apparent when two different batches of Silastic RTV-882 were tested. More than twice the amount of 1-propanol was detected from batch A after 30 days, than from batch B after 60 days.

An additional sampling problem arose when large, one-section samples, e.g., Plexiglas No. 2 Clearmil (approx. 4 sq.ft.), were reduced in size to pass through the opening (1-3/4" diameter) of the gas-off chamber. Despite uniform sample sizes, differences in amounts of fresh surface at the fracture were believed sufficient to cause variations in the quantities of gas-off products.



- | | |
|--|--|
| A. PREPURIFIED NITROGEN. | G. VENT. |
| B. TEFLON SLEEVED GROUND GLASS JOINT. | H. FLOWMETER. |
| C. STOPCOCK. | I. HELICAL TRAP IN LIQUID NITROGEN. |
| D. GAS-OFF CHAMBER. | J. PUMP ISOLATION TRAP. |
| E. NEEDLE FLOW CONTROL VALVE. | K. VACUUM PUMP. |
| F. VACUUM GAUGE. | |

Figure 4. Chamber to Helix Collection System.

2. Analytical Methods

Two methods for sampling the chamber atmospheres were used. As shown in Section II.A.3, these methods were, (a) to isolate all condensables at -195°C from the total 9-liter chamber, and (b) to make aliquots, e.g., 25 ml for gas chromatography and 125 ml for mass spectrometry, from the chamber atmosphere.

Repeatable data were not obtained by condensing at -195°C all the gas-off products from the total 9-liter volume. Up to 5-fold differences in analytical results were observed when comparing data for duplicate chambers. Consequently, this method was only used in special cases, e.g., when gas-off products could not be detected in the aliquots.


Entrainment of volatiles, aerosol formation, and nonquantitative condensation of various types of compounds during the attempted condensation of total gas-off products resulted in loss of some products and considerable variation in relative proportions of the components. Additional losses could be attributed to irreversible adsorption of polar compounds on the glass surfaces, and to polymerization of the silanol gas-off products.

The adsorption effect was considerable when glass beads, sand or glass wool were used as packing to increase the efficiency of the trapping system. The increased surface area and availability of $-\text{OH}$ sites permitted greater adsorption. This was particularly true whenever the packings were pretreated with chromic acid solution to remove organic residues, e.g., silicons. This pretreatment produces an increased number of active sites, resulting in greater adsorption of polar compounds from the chamber atmosphere.

Better repeatability of analyses ($\pm 100\%$ at the 0.001 mg level and $\pm 25\%$ at the 0.01 mg level between duplicate chambers) was obtained when analyzing aliquots from the chamber atmospheres. Although variations between duplicate chambers were observed, no measurable differences were detected from aliquots taken from the same chamber. The high sensitivities of mass spectrometry and gas chromatography with a flame ionization detector permitted use of relatively small, representative samples of chamber atmosphere with no impairment of the detection levels.

The differences in relative distribution of components obtained by both sampling methods are shown graphically in the gas chromatograms of Silicone Primer SS-4004. Figure 5-A is representative of a 25-ml portion of the gaseous atmosphere, whereas Figure 5-B was obtained from a sample of condensate

(A)



(B)




Figure 5. Gas Chromatograms of Gas-Off Products from Silicone Primer SS-4004.

(A) 25 ml aliquot of gaseous atmosphere
(B) Condensables at -196°C from nine liter volume

isolated at -195°C in a helical trap similar to that shown in Figure 1.

3. Analytical Data

Table III lists the types of compounds detected in the chamber atmospheres. These data represent compounds exclusive of the normal constituents of air, i.e., H_2O , CO_2 , O_2 , N_2 , CO , etc. The presence of carbon monoxide was reported only when in excess of 2 ppm of chamber atmosphere, which was the normal content of CO in the "zero" air used in these experiments.

As expected, the major yields of gas-off products occur with the candidate paints and coatings, which desorb entrapped solvents and plasticizers. Small, but still significant, amounts of contaminants result from oxidation, hydrolysis and sublimation processes. Analytical data are presented in Tables VII-XLVI (Appendix I), Tables XLVII-XXCVIII (Appendix II) and Figures 7-43 (Appendix III).

All values appearing in the tables of Appendix I are calculated on the basis of the dried or cured sample. This becomes important in the case of paints and coatings where the weight of the material is substantially reduced by drying.

Representative mass spectral data for the gas-off products from various candidate materials are shown in Tables XLVIII-XXCIX (Appendix II). These data are for the composite of gas-off components from the 9-liter gas-off chambers. An attempt was made to show the contribution of each known component to the total observed mass spectrum. API (American Petroleum Institute) or CEC Keysort Mass Spectra File reference mass spectra of the pure components were used whenever available. The observed spectrum is given in the first column in chart division. Using the relative intensities of the reference spectrum, the contribution in chart divisions for each mass number was calculated for each component. When standard spectra were not available, spectra from our laboratory files were used and are labeled MRC spectra. While care was taken to select API spectra obtained on an instrument similar to the one used for this study, small differences occur between the spectrum of a compound obtained with our instrument and published reference spectra.

In some cases identification of components can be accomplished directly from the mass spectrum for the composite. However, in many cases, isolation and collection of individual components were performed by gas chromatography to obtain additional spectral data on the pure or more concentrated species.

Table III

TYPES OF COMPOUNDS DETECTED

I. Inorganics

Ammonia
Carbon monoxide
Carbonyl sulfide
Carbon disulfide

II. Alkanes

Methane
Variety of C₅-C₇ hydrocarbons, as naphtha

III. Alkenes

Trichloroethylene

IV. Alcohols

Ethanol
2-Ethoxyethanol
n-Propanol
2-Propanol
n-Butanol

V. Alkyl Halides

Trichlorofluoromethane
Variety of low molecular weight, C₆ and lower,
chlorofluorocarbons

VI. Carboxylic Acids and Their Derivatives

Acetic acid
2-Ethoxyethylacetate
Methyl methacrylate

VII. Aldehydes

Formaldehyde
Acetaldehyde
Propionaldehyde

Table III - Cont'd

VIII. Ketones

Acetone
Methyl ethyl ketone
Methyl isobutyl ketone

IX. Aliphatic Nitrogen Compounds

Ethylamine

X. Benzene and Its Homologs

Benzene
Toluene
Xylenes
C₃ alkyl benzenes

XI. Aryl Halides

Dichlorobenzene
1,2,4,5-Tetrachlorobenzene

XII. Silicon Compounds




Various cyclic and linear methylsiloxane polymers
Trimethylsilanol

Contrails

An extreme example of this occurred with Latex Foam Rubber. The mass spectrum of the gas-off products showed only several weak lines, from which no positive identification could be made. However, by subjecting the material to a substantially reduced pressure with slight warming, material was obtained which gave the same lines previously obtained, but now many times stronger. Separation and collection by gas chromatography with subsequent mass spectral characterization provided identification of the components. This scheme was followed whenever identification could not be readily obtained on a direct analysis of the gas-off product mixture.

Hydrocarbons are gas-off components from a number of candidate materials. Where naphtha or petroleum ether are used as solvents, saturated hydrocarbons are obtained in large amounts. These are characterized as to carbon-number range only, with no attempt to specifically identify the multitude of possible isomers present. In these cases, quantitative estimates of the amounts present are obtained from gas chromatography data.

Most of the materials having a silicone base evolved volatile siloxane polymers, both linear and cyclic, having dimethyl siloxy groups as monomer units. These polymers exhibited characteristic mass spectra for the fragments.



Contrails

The volatile silicone materials are listed in the tables simply as silicone oil. McLafferty (Ref. 22) and Biemann (Ref. 23) list the strong mass spectral lines observed from the volatile components of a silicone grease and suggest species giving rise to them. From their information, most of the siloxane polymeric material observed as gas-off products in these studies arises from a cyclic structure similar to "A". However, in the case of Silicone Fluid, F-50, a linear species similar to "C" was equally important. For this reason an estimate has been made of the amount of silicone oil "A" and silicone oil "C".

Under the conditions of the experiments, 23-25°C and 20-40% R.H., there were no major differences between the types of gas-off products evolved in the tests in air at a pressure of one atmosphere and in oxygen at 5 psia. With some materials, e.g., Class H Silicone Impregnating Varnish, smaller amounts of alcohols were observed in the chambers containing oxygen at 5 psia. In general, the differences between the tests were characterized by some increase in amount of gas-off products in the chambers at reduced pressure.

4. Materials Producing No Gas-Off Products

The candidate materials for which gas-off products were not detected are shown in Table IV. Based on sensitivities for gas chromatography and mass spectrometry, the detection limit is estimated as much less than 0.001 mg/10 grams of candidate material.

Table IV

CANDIDATE MATERIALS YIELDING NO GAS-OFF PRODUCTS

Adhesive Tape C/R No. 465 (Y 9010)
Elastic Webbing, 731-5RDC
Red Dye, Red PL
Silastic Sponge 445 Base (3.5/300 + 10/400)
Polycarbonate, Lexan (1-1/4" cylinder)
Polycarbonate, Lexan (1-1/4" x 2-1/4" x 36")
Polyvinylfluoride
Plexiglas Clear No. 2 (MIL-P-5425)
Blue Thermofit RNF 100
Thermofit Molded Parts Type S
(6005-2915-S) (5M83354)
Nylatron G5 (MIL-P-46060)
Lockfoam G-502 (R & T)

5. Materials Having Unique Gas-Off Characteristics

a. Velvet Coating No. 104-C 10 Black and Class H Silicone Impregnating Varnish No. 997

Most surprising were the high levels of carbon monoxide issuing from several candidate materials. As shown in Tables XVI and XVII, significant amounts of carbon monoxide (0.2 to 5.4 mg/10 grams candidate material) were detected in the chamber atmospheres for Velvet Coating No. 104-C 10 Black, and Class H Silicone Impregnating Varnish No. 997.

Carbon monoxide in the atmosphere above the Velvet Coating arises partly from desorption from carbon which is a major constituent of the coating. Similarly, the presence of methane (0.04-0.16 mg/10 grams candidate material) can be attributed to the retention of small quantities during the formation of the carbon black and subsequent desorption during storage.

Although not evident in the gas-off products of the Velvet Coating No. 104-C Black, condensation of methyl silanols occurred on the inner walls of the chamber to form a methyl siloxy polymer. This oil coating was identified by infrared analysis of the residue.

b. 620 Light Gull Gray XA-193 and 3615 Gray XA-194

There is some mass spectral evidence of the presence of chlorobenzene at very low levels (10^{-3} mg/10 gms) as a gas-off product from the XA-193 and XA-194 Coatings. However, this component has not been conclusively identified.

c. Lockfoams C-605 and G-502

Excessive amounts of carbon dioxide (1-20 mg/10 grams candidate material) were detected in Lockfoams C-605 and G-502. The carbon dioxide is due to gas entrapped during the formation of the polyurethane foams.

d. Fluorolube Oil Grade FS-5 and Fluorolube Grease Grade GR-544, Type LG

The exact structures of the six major components present as gas-off products from Fluorolube Oil Grade FS-5 (Table XXIV, Figure 20) are not presently known, due to lack of reference data. However, the composition of the major mass fragments giving rise to the mass spectrum can be established with reasonable certainty. These fragments are shown in Table V.

Table V

STRONG IONIC SPECIES OBSERVED IN MASS SPECTRUM
OF FLUOROLUBE FS-5 GAS-OFF PRODUCTS

<u>Mass</u>	<u>Species</u>	<u>Mass</u>	<u>Species</u>
66	CClF	147	C ₃ ClF ₄
68	CClF	149	C ₃ ClF ₄
69	CF ₃	151	C ₂ Cl ₂ F ₃
74	C ₃ F ₂	153	C ₂ Cl ₂ F ₃
85	CF ₂ Cl	163	C ₃ Cl ₂ F ₃
87	CF ₂ Cl	165	C ₃ Cl ₂ F ₃
93	C ₃ F ₃	185	C ₃ ClF ₆
101	CCl ₂ F	187	C ₃ ClF ₆
103	CCl ₂ F	201	C ₃ Cl ₂ F ₅
105	CCl ₂ F	203	C ₃ Cl ₂ F ₅
109	C ₃ ClF ₂	229	C ₄ Cl ₃ F ₄
116	C ₂ ClF ₃	231	C ₄ Cl ₃ F ₄
118	C ₂ ClF ₃	247	C ₅ ClF ₈
131	C ₃ F ₅		
135	C ₂ ClF ₄		
137	C ₂ ClF ₄		

*Mass difference due to chlorine 35 and 37 isotopes.

Contrails

The mass spectrum of any one component, as separated by gas chromatography, does not differ significantly from the mass spectrum of the total mixture. This fact tends to indicate that the components are members of a homologous series probably differing only in chain length. These components have been characterized as chlorine substituted fluorocarbons up to approximately C₆. Infrared absorption, spectrophotometry, nuclear magnetic resonance (¹⁹F and ¹H) and mass spectral data combine to strongly support this characterization. Similar gas-off products were detected from Fluorolube Grease Grade GR-544, Type LG.

e. Silicone Grease G-300

Several days after the chambers were charged with Silicone Grease G-300 fine needle-like crystals were observed growing on the inner wall of each chamber. This took place with the air atmosphere as well as with the oxygen atmosphere at 5 psi. The crystals were removed and analyzed by mass spectrometry, proving to be tetrachlorobenzene. Subsequent infrared analysis Figure 6, confirmed the material as 1,2,4,5-tetrachlorobenzene.

No tetrachlorobenzene was detected by mass spectrometry analysis of the gas-off products. Apparently, through the sublimation process, the tetrachlorobenzene is deposited in the solid state on the inner surface of the chamber with little, if any, remaining in the gas phase. Although the deposits are considerable, collection and quantitative measurement of this compound directly from the chamber was impossible due to the random scattering of the crystals. Data were obtained from a small scale experiment performed in air at 23°C and 35% relative humidity (Table VI).

f. Plexiglas No. 2 Clearmil

Considerable variance in the amounts of methyl methacrylate evolved from Plexiglas No. 2 Clearmil, Table XLIV, was observed. Although the sample size was kept uniform, differences in amounts of free, freshly exposed surface at the fracture produced varying amounts of methyl methacrylate.

g. Delrin No. 100

The aldehydes reported as gas-off products in Table XLVI for Delrin No. 100 were detected by mass spectrometry, but not by gas chromatography with the flame ionization detector and the Carbowax column.




Figure 6. Infrared Spectrum of Sublimate from Silicone Grease, G300 (KBr pellet).

Table VI

SUBLIMATE FROM SILICONE GREASE G-300

<u>Storage Time (Days)</u>	<u>Wt. of 1,2,4,5 Tetrachlorobenzene (mg per 10 g of Silicone Grease)</u>
30	2.1
60	3.3
90	5.8

Contrails

h. Silastic Sponge 445 Base, Silastic 950-4-400 and Silastic 9711-480

Due to inadequate amounts of sample, only partial testing of Silastic Sponge 445 Base, Silastic 950-4-400 and Silastic 9711-2-480 was performed. Silastic Sponge 445 Base gave no detectable gas-off products. As a cross-check, this candidate material was put directly into the mass spectrometer inlet, under a vacuum of 10^{-5} torr. The only components desorbed were small amounts of water and air.

Small amounts of gas-off products from Silastic 950-4-400 and Silastic 9711-2-480 were detected only by mass spectrometric analysis of the condensables from the total 9-liter chamber volume. The results are reported in Tables XIII and XIV.

i. Resin, Versamid 125

Significant amounts of ammonia and ethyl amine were produced by hydrolysis during the testing of Versamid 125, Table IX. No ammonia or ethyl amine were detected when vapors from fresh polyamide were analyzed.

j. Magnesium/Lithium Alloys LA-91, LA-141, and LA2-933

Magnesium/lithium alloys LA-91, LA-141, and LA2-933 were studied only for a thirty day period. Though no gas-off products were detected by mass spectrometry, several minor components were found by gas chromatography.

The gas-off products were concentrated and isolated by gas chromatography. A mass spectrum of the final collected fraction had lines corresponding to an alcohol. The retention time by gas chromatography did not agree with any of the alcohols up to C_5 . Though no positive identification can be made because of the small amount of this material present, it may be a C_5 or higher alcohol. The level is estimated at 0.002 mg or less per 10 grams of candidate material. The component is a gas-off product common to all three alloys.

A second component appears as a gas-off component of LA-91. Its level was estimated at 0.001 mg/10 grams or less. At this low level no identification was possible.

SECTION III

CARBON CANISTERS FROM SPACE CABIN SIMULATORS

A. EXPERIMENTAL METHOD

Description of gases from carbon canisters was performed by the technique developed by Saunders (Ref. 16). Materials desorbed at 300°C were collected at -195°C and subsequently fractionated by employing baths at -76°C, 0°C, 23°C and 100°C. Materials vaporized at these temperatures were again collected at -195°C and were analyzed by gas chromatography and mass spectrometry.

F & M Scientific Co. Model 300 and Model 500 Gas Chromatographs with thermal conductivity detectors and a Consolidated Electrodynamics Corporation 21-103C Mass Spectrometer were used in this study. Gas chromatography instrument conditions are shown in Table XC (Appendix IV).

B. RESULTS

Mass spectrometric and gas chromatographic analyses were performed on a series of carbon canisters from space cabin simulators,

1. Carbon Canister 10-12 Day
2. Carbon Canister 16-18 Day
3. Carbon Canister 26-28 Day
4. CBR Carbon 28 Day (Thomas)

Quantitative analytical data are reported in Tables XCI-XCIV for the four carbon canisters and typical gas chromatograms are shown in Figures 44-49 (Appendix IV).

SECTION IV

HYDROLYSIS OF MCS 198 IN PRESENCE OF LiOH

A. EXPERIMENTAL METHOD

1. MCS 198 and Anhydrous LiOH

Weighed amounts (64 grams) LiOH were placed in 1000 ml heavy-walled Erlenmeyer flasks fitted with side-arms. MCS 198 (10 ml) was pipetted uniformly over the surface of the LiOH. The flasks were capped with stoppers having glass inlet tubes extending to approximately 1/2-inch above the surface of the LiOH and the inlet and exit lines were then sealed. Air temperature and relative humidity were 23°C and 35%, respectively. Flasks were stored for 1 hour, 6 hours, and 24 hours. A flask not containing LiOH, but charged with MCS 198 in air, was used as a control. Samples were collected by purging the flasks with prepurified nitrogen and condensing the head gases in a glass helical trap cooled with liquid nitrogen.

2. MCS 198 and Hydrated LiOH

In a system similar to that used in Section II.C.1, 10 ml of MCS 198 was pipetted onto 64 grams of anhydrous LiOH, previously treated with 3 ml of distilled water. Other conditions remained the same.

3. MCS 198 Sprayed Onto Hydrated LiOH

Two ml of MCS 198 was sprayed onto LiOH, previously treated with a stoichiometric amount of water to give $\text{LiOH}\cdot\text{H}_2\text{O}$. The temperature of the reaction chamber, a 1-liter, 4-hole, round bottom flask, was maintained at 150°F. Collections of head gases were made after 5 minutes and 15 minutes.

4. Identification of Hydrolysis Products of MCS 198

To facilitate the identification of the MCS 198 hydrolysis products, two gas chromatographic column systems were used. Octoil S (OS) liquid phase is effective for resolving complex alcoholic mixtures and water, whereas silicon gum rubber (SGR) can be employed in the observation of less volatile materials. Identifications were performed from GLC retention data and mass spectrometric analysis of collected chromatographic fractions.

Contrails

F and M Scientific Co. Model 300 and Model 500 Gas Chromatographs with thermal conductivity detectors and a Consolidated Electrodynamics Corporation 21-103C Mass Spectrometer were used in this study. The gas chromatography instrument conditions are presented in Table XCV (Appendix V).

B. RESULTS AND DISCUSSION

Results of the MCS 198 + LiOH experiments are reported in Table XCIII and Figures 50-57, Appendix V. The principal components of the head gases exclusive of air, are isopropanol, 2-butanol, water and lesser amounts of the mixed isopropyl and 2-butyl silicates. In addition, trace amounts of ethyl alcohol, o-xylene and secondary alcohols, believed to be mostly C₅, C₆ and C₇ materials, were identified.

The principal components were observed as distinct peaks in the gas chromatograms. o-Xylene and the secondary alcohols with a carbon number greater than C₄ were detected as a relatively weak, broad band extending from 12 to 24 minutes (SGR). Characterization of this peak system was performed by mass spectrometric analysis of a collected GLC fraction and subsequent investigation of retention times of known alcohols and o-xylene.

In addition to o-xylene, it is likely that a much smaller quantity of the other xylene isomers are present also.

As noted from a comparison of the data in Table XCIII for the 24-hour blank and the 24-hour anhydrous LiOH experiment, hydrolysis of MCS 198 is markedly enhanced by the presence of LiOH. Also, most of the hydrolysis, under the static conditions of storage at 23°C and 35% R.H. without agitation, occurs after 6 hours. Diffusion of water from the head gases to the MCS 198-LiOH interface appears to be rate controlling step.

No evidence for any significant hydrolysis was observed in the experiment in which MCS 198 was sprayed onto LiOH·H₂O. As shown in Table XCIII, the head gases are primarily water and the mixed isopropyl and 2-butyl silicates. No differences were noted between the two samplings. Contact time was too short to promote any significant hydrolysis. Similar observations were made in the static tests, which showed the greater degree of hydrolysis after 6 hours.

SECTION V

CONCLUSIONS AND RECOMMENDATIONS

This study has shown that many factors influence analyses of gas-off products from the candidate materials. The major factors are: (a) physical state and composition of each specimen, (b) adsorptive characteristics of the gas-off chamber, (c) storage time, (d) nature of the chamber atmosphere, (e) method of sampling the chamber atmosphere, and (f) method of analysis. Slight differences in each of these can appear as large relative differences when comparing analytical data for extremely small amounts of gas-off products.

A large part of the variation in yields from the 12 specimens of each candidate material used in these tests can be attributed to differences in physical properties and to changes in chemical composition of the specimens. Some factors affecting the physical properties and the chemical composition are: non-uniformity of sample specimens, possible changes in proprietary mixes between sample lots, localized entrapment of solvent and plasticizers, freshness of sample, variations in sample size and shape, and amount of exposed surface.

The adsorptive characteristics of the inner wall of the glass chamber have a marked influence on the nature and the amounts of gas-off products. Low molecular weight methyl siloxanes were detected as coatings on the glass walls in the tests with silicone-based materials. Not only are the gas-phase analyses for trimethylsilanol and low molecular weight silicones affected, but the coating on the glass surface provides an excellent medium for the potential adsorption of organic compounds from the chamber atmosphere. In addition, the adsorption sites on the glass surface can remove significant amounts of polar gas-off products, e.g., alcohols, acids, ketones and aldehydes, from the gas phase.

The variability in the analytical data produced by sample inhomogeneity and by the adsorptive nature of the glass chamber are sufficient to mask the detection of significant changes in amounts of gas-off products after continuous 30, 60 and 90 day periods. Data for most periods indicate that little increase in gas-off products occurs after the first 30 days.

Generally, the tests, in which the chamber atmospheres were analyzed, purged, and recharged every 30 days for a cumulative time of 90 days, show a reduction in gas-off products after each purging. These data also show some tests in which

Contrails

the amounts of gas-off products from the second 30 day period are equivalent to the first and are almost equal to the total amount of gas-off products from the continuous 90 day tests. The mechanism by which this desorption occurs is not known, but data indicate a relatively constant amount of gas-off products is in the gas phase during continuous 30, 60 and 90 day storage periods, whereas, repeated evolution of gas-off products occurs if the atmosphere above the candidate material is changed. The amounts of gas-off products accumulated during three purging and recharging tests may be two to three times the quantities measured for a continuous 90 day storage.

The variations in the gas-off products produced in air at a pressure of 1 atmosphere and in oxygen at 5 psia under the conditions of 23-25°C and 20-40% R.H. are believed to result mostly from differences in total pressure, i.e., some increase in gas-off products was obtained at the reduced pressure. Although slight changes in relative amounts of alcohols and aldehydes were detected in some cases, there is not sufficient evidence of a general increase in oxidation in the oxygen atmosphere at 5 psia. There is some evidence for hydrolysis products in both environments.

The methods for sampling the chamber atmosphere can strongly influence the relative amounts of gas-off components isolated for analysis. Problems associated with aerosol formation, entrainment of vapor, adsorption, and possibly hydrolysis or oxidation during isolation and concentration of all the gas-products in each 9-liter chamber by condensation at -195°C, prevented application of this technique in the general quantitative analytical method. A technique, in which an aliquot of the gaseous atmosphere is used for analysis, was found to be more repeatable.

A program, which surveys a wide variety of materials, requires several rapid analytical techniques. Generally, one will not suffice. In this study, there were several cases in which gas-off components were detected by mass spectrometry, but not by gas chromatography. Some of these components were carbon disulfide, carbonyl sulfide, acetic acid, and various aldehydes. Additional analyses for carbon monoxide, methane, and naphtha were more easily obtained by gas chromatography, than by mass spectrometry. For a complete characterization of all components, several techniques, e.g., gas chromatography, mass spectrometry, infrared spectrophotometry, and a variety of classical chemical tests, should be used.

The analytical procedures employed in this program were developed to cover a wide range of candidate materials. For each material, more optimum conditions, particularly in the gas

Contrails

chromatography operation, could be established. To attain the maximum sensitivity for a particular component, specific column packings, instrument conditions, and detection systems are needed for each type of candidate material.

We have concluded that:

- (1) Qualitative identification of gas-off components is possible to the level of 0.1 ppm in the gaseous atmosphere.
- (2) Estimates of the amounts of gas-off components can be made from mass spectrometry and gas chromatography analyses, but, at these extremely low levels, considerable variation in the measurements can arise from sample inhomogeneity, occlusion of solvents and plasticizers, slight difference in composition of sample lots, and adsorption phenomena.

Future evaluations of candidate materials should consider the following recommendations:

- (1) Whenever possible, materials should be evaluated in their final form and under the conditions of use.
- (2) Pretreatment of candidate materials should simulate conditions encountered in use.
- (3) To provide quantitative data for meaningful comparison between testing laboratories, some standardizations of sample preparation, i.e., size, shape, exposed surface, etc., should be made. However, the testing laboratories must recognize that the level of gas-off products is generally so small that variations in proprietary mixes, sample homogeneity, occlusion of solvents, and adsorption in the gas-off chamber may influence the yields of gas-off products to a greater degree than small differences in size and shape.

Contracts

APPENDIX I

ANALYTICAL RESULTS
FOR
GAS-OFF EXPERIMENTS

Contrails

The following tables list compounds found as gas-off products under the various test conditions. The tests may be summarized as follows:

1. A 30-day gas-off period in (a) air and (b) in 5 psia oxygen.
2. Removal of complete atmosphere from the 30 day test and analysis after a second 30 day period in (a) air and (b) oxygen in 5 psi. Test is designated by "30 + 30 day."
3. Removal of complete atmosphere from above "30 + 30 day" test and analysis after one more 30 day period in (a) air, and (b) oxygen at 5 psia. Test is designated "30 + 30 +30 day."
4. A 60 day undisturbed period in (a) air and (b) oxygen at 5 psia.
5. A 90 day undisturbed period in (a) air and (b) oxygen at 5 psia.

The values for the gas-off product levels are given in milligrams per 10 grams of the cured candidate material. In most cases more than 10 grams of material were used, but each yield of gas-off products was normalized to that of a 10 gram sample. The values reported are averages of two separate experiments.

The order of the tables in this appendix is the same as the order of the candidate materials listed in Table I.

Table VII
GAS-OFF PRODUCTS - ADHESIVE, A-4000

Storage Time (Days)	Atmosphere	Wt. of Component (mg per 10 g Candidate Material)							
		n-Propanol 2-Propanol	Xylene	Trimethyl Silanol	Silicone Oil*	Acetone	Toluene	C ₁₁ -C ₁₅ Hydrocarbon	
30	Air	1.9	0.3	0.3	0.7	<0.005	0.05	0.6	
60	"	1.5	0.3	0.2	0.6	<0.005	0.03	0.6	
90	"	1.4	0.3	0.2	0.7	<0.005	0.05	0.7	
30 + 30	"	0.7	0.4	0.2	0.6	<0.005	<0.02	0.1	
30 + 30 + 30	"	1.5	0.3	0.7	0.5	<0.005	<0.02	0.2	
30	Oxygen	0.7	0.5	0.8	0.3	<0.005	0.05	0.5	
60	"	0.8	0.1	0.1	0.5	<0.005	0.05	0.5	
90	"	1.0	0.06	0.1	0.5	<0.005	0.11	0.6	
30 + 30	"	0.7	0.1	0.1	0.5	<0.005	0.04	0.05	
30 + 30 + 30	"	0.6	0.2	0.1	0.5	<0.005	0.05	0.03	

*See Analytical Data, Results and Discussion, Section II.

Table VIII
GAS-OFF PRODUCTS - ADHESIVE, NO. 271

Storage Time (Days)	Atmosphere	Wt. of Component (mg per 10 g Candidate Material)						
		Hydro- Carbons*	Silicone Oil**	Trimethyl Silanol	Xylene	2-Propanol	Ethanol	
30	Air	0.2	0.1	0.4	0.002	0.04	0.03	
60	"	0.06	0.08	0.7	0.004	0.1	0.1	
90	"	0.06	0.1	0.9	0.001	0.3	0.3	
30 + 30	"	0.06	0.06	0.3	0.002	0.06	0.05	
30 + 30 + 30	"	0.05	0.04	0.5	0.003	0.08	0.09	
30	Oxygen	0.3	0.1	0.6	0.01	0.09	0.1	
60	"	0.1	0.08	0.9	0.04	0.06	0.05	
90	"	0.1	0.2	1.0	0.006	0.1	0.1	
30 + 30	"	0.06	0.1	0.8	0.002	0.07	0.07	
30 + 30 + 30	"	0.04	0.1	0.7	0.003	0.08	0.07	

*Estimated C₄-C₅ from mass spectral data.

**See Analytical Data, Results and Discussion,
Section II.

Table IX
GAS-OFF PRODUCTS - RESIN, VERSAMID 125

Storage Time (Days)	Atmosphere	Wt. of Component (mg per 10 g Candidate Material)		
		Ammonia	Ethyl Amine	Xylene CO
30	Air	0.7	0.005	0.0004 *
60		1.2	0.006	0.0007 *
90		2.6	0.01	0.001 0.077
30 + 30		2.0	0.004	N.D. 0.072
30 + 30 + 30		2.6	0.02	N.D. 0.021
30		1.5	0.006	0.004 *
60		3.0	0.02	0.003 0.028
90		4.1	0.01	0.008 0.062
30 + 30		1.7	0.02	N.D. 0.025
30 + 30 + 30		4.1	0.03	N.D. 0.020

*Not determined.

Additionally, n-propanol was detected by gas chromatographic analysis of the condensables from the total nine liter volume. Level is estimated at less than 0.001 mg/10 g.

See Part 5.1, Results and Discussion, Section II.

Table X
GAS-OFF PRODUCTS - NEOPRENE, PHENOLIC EC-847

Storage Time (Days)	Atmosphere	C6 - C7* Hydrocarbons	Weight of Component (mg per 10 g Candidate Material)					
			Acetone	Methyl Ethyl Ketone	Benzene	n-Propanol	Toluene	Xylene
30	Air	13.5	14.2	1.8	0.6	7.6	4.8	0.3
60	"	13.8	15.1	3.4	1.2	7.1	5.9	0.6
90	"	10.7	12.3	4.2	0.8	7.7	7.2	1.1
30 + 30	"	5.4	9.9	2.2	0.7	5.2	3.7	0.3
30 + 30 + 30	"	2.5	11.3	1.5	0.4	4.1	3.6	0.3
30	Oxygen	12.0	12.8	3.7	0.7	7.5	8.8	1.3
60	"	13.9	11.3	3.2	1.0	7.0	5.5	0.6
90	"	14.1	14.6	4.4	0.9	8.7	8.1	1.4
30 + 30	"	5.2	15.5	1.7	0.6	6.3	5.8	1.2
30 + 30 + 30	"	2.7	12.9	1.8	0.4	5.8	6.7	1.1

* 2-methyl pentane, 3-methyl pentane, 2,3 dimethyl pentane, 2,4 dimethyl pentane, hexane were identified specifically though others may be present.

Table XI

GAS-OFF PRODUCTS - SILASTIC NO. 950

<u>Storage Time (Days)</u>	<u>Atmosphere</u>	<u>Wt. of Component (mg per 10 g Candidate Material) Sat.* Hydrocarbon</u>
30	Air	0.005
60	"	0.005
90	"	0.002
30 + 30	"	0.007
30 + 30 + 30	"	0.002
30	Oxygen	0.002
60	"	0.003
90	"	0.003
30 + 30	"	0.002
30 + 30 + 30	"	0.002

*Approximately C₅ according to mass spectra data.

Table XII

GAS-OFF PRODUCTS - SILASTIC S2007

Storage Time (Days)	Atmosphere	Wt. of Component (mg per 10 g Candidate Material)			
		Ethanol	Acetaldehyde	Silicone Oil*	Dichlorobenzene CO
30	Air	2.1	0.21	0.55	<0.005 **
60	"	1.9	0.44	0.50	<0.005 0.013
90	"	1.1	0.66	0.47	<0.005 **
30 + 30	"	1.8	0.85	0.73	<0.005 0.008
30 + 30 + 30	"	0.2	0.22	0.11	N.D. 0.006
30	Oxygen	1.1	0.30	0.50	<0.005 **
60	"	1.9	0.53	0.32	<0.005 0.007
90	"	0.8	0.80	0.27	N.D. 0.027
30 + 30	"	1.7	1.5	0.20	N.D. 0.005
30 + 30 + 30	"	1.0	2.8	0.20	N.D. 0.005

*See Analytical Data, Results and Discussion, Section II.

**Not determined.

Note: Additionally, n-Butanol appears in the 90 day experiments at a level of less than 0.1 mg/10 grams.

Table XIII

GAS-OFF PRODUCTS - SILASTIC 950-4-400

<u>Storage Time (Days)</u>	<u>Atmosphere</u>	<u>Wt. of Component (mg per 10 g Candidate Material)</u>	
		<u>Ethanol</u>	<u>Silicone Oil**</u>
30	Air	.05	.023
60	"	*	*
90	"	*	*
30 + 30	"	.008	.012
30 + 30 + 30	"	.003	-
30	Oxygen	*	*
60	"	*	*
90	"	*	*
30 + 30	"	*	*
30 + 30 + 30	"	*	*

*No other experiments were performed on this candidate material since only a small supply was available.

**See Analytical Data, Results and Discussion, Section II.

Table XIV

GAS-OFF PRODUCTS - SILASTIC 9711-2-480

<u>Storage Time (Days)</u>	<u>Atmosphere</u>	<u>Wt. of Component (mg per 10 g Candidate Material) Silicone Oil**</u>
30	Air	<0.01
60	"	*
90	"	*
30 + 30	"	<0.01
30 + 30 + 30	"	<0.01
30	Oxygen	*
60	"	*
90	"	*
30 + 30	"	*
30 + 30 + 30	"	*

*No other experiments were performed on this candidate material since only a small supply was available.

**See Analytical Data, Results and Discussion, Section II.

Table XV

GAS-OFF PRODUCTS WIRE (MIL-W-16878-C) TYPE E 23-W-9

<u>Storage Time (Days)</u>	<u>Atmosphere</u>	<u>Weight of Component (mg per 10 g Candidate Material) Sat. Hydrocarbon*</u>
30	Air	<0.005
60	"	<0.005
90	"	<0.005
30 + 30	"	<0.005
30 + 30 + 30	"	<0.005
30	Oxygen	<0.005
60	"	<0.005
90	"	<0.005
30 + 30	"	<0.005
30 + 30 + 30	"	<0.005

* C₆ or lower by Mass Spectrometry.

Table XVI

GAS-OFF PRODUCTS - VELVET COATING NO. 104-C 10 BLACK

Storage Time (Days)	Wt. of Component (Mg per 10 g Candidate Material)							
	Atmosphere	Ethanol	Acetone	Methylethyl Ketone	Toluene	CO	Methane Naphtha*	
30	Air	0.3	0.1	0.4	0.02	2.8	0.04	1.0
60	"	0.3	0.3	0.5	0.02	3.6	0.06	1.0
90	"	0.1	0.1	0.4	0.02	4.5	0.10	1.0
30 + 30	"	0.05	0.1	0.3	0.02	0.7	N.D.	0.4
30 + 30 + 30	"	0.04	0.08	0.2	0.01	0.6	N.D.	0.4
30	Oxygen	0.4	0.5	0.3	0.2	4.9	0.16	1.0
60	"	0.2	0.1	0.6	0.02	4.0	0.08	1.0
90	"	0.08	0.3	0.5	0.01	5.4	0.12	1.0
30 + 30	"	0.09	0.09	0.3	0.02	1.2	N.D.	0.5
30 + 30 + 30	"	0.07	0.09	0.3	0.01	0.9	N.D.	0.4

* Estimated from group of GLC peaks characteristic of C₅-C₇ hydrocarbons.

See Part 5.a, Results and Discussion, Section II.

Table XVII

GAS-OFF PRODUCTS - CLASS H SILICONE IMPREGNATING VARNISH NO. 997

Storage Time (Days)	Atmosphere	Wt. of Component (mg per 10 g Candidate Material)					
		Ethanol	Propionaldehyde	Benzene	Toluene	Xylene	CO
30	Air	0.2	0.7	0.1	0.05	0.2	2.3
60	"	0.3	0.5	0.02	0.004	0.01	2.4
90	"	0.2	0.4	0.04	0.05	0.01	2.7
30 + 30	"	0.4	0.2	0.01	0.03	0.1	0.3
30 + 30 + 30	"	0.4	0.1	N.D.	N.D.	N.D.	0.2
30	Oxygen	0.04	0.5	0.02	0.2	0.3	2.0
60	"	0.05	0.2	0.02	0.5	0.2	2.6
90	"	0.05	0.4	0.02	0.9	0.7	2.9
30 + 30	"	0.03	0.1	0.02	0.6	1.0	0.7
30 + 30 + 30	"	0.04	0.2	0.04	0.7	2.0	0.5

Contrails

Table XVIII
GAS-OFF PRODUCTS - 620 LIGHT GULL GRAY COATING, XA-193

Storage Time (Days)	Atmosphere	Weight of Component (mg per 10 g Candidate Material)						
		Ethanol	2-Propanol	C6-C10 Sat. Hydrocarbon(s)	Methyl Ethyl Ketone	Benzene	Toluene	Xylene
30	Air	0.7	2.5	0.3	2.5	0.6	2.6	2.0
60	"	0.6	3.0	0.5	1.8	1.2	0.3	2.3
90	"	0.5	3.0	0.5	1.1	0.5	5.0	3.9
30 + 30	"	0.5	3.5	0.5	0.9	0.6	5.9	4.1
30 + 30 + 30	"	0.02	0.06	0.07	0.2	0.2	2.4	2.4
30	Oxygen	0.2	2.4	1.5	0.4	0.1	4.7	2.5
60	"	0.1	1.2	0.2	0.8	0.3	5.9	4.0
90	"	0.1	1.5	1.0	2.0	1.2	13	23
30 + 30	"	0.3	3.0	0.5	1.3	0.7	10	8.2
30 + 30 + 30	"	0.08	1.1	0.2	1.8	0.5	13	16

See Part 5.b, Results and Discussion, Section II.

Table XIX

GAS-OFF PRODUCTS - 3614 GRAY COATING, XA-194

Storage Time (Days)	Atmosphere	Wt. of Component (mg per 10 g Candidate Material)						
		Ethanol	2-Propanol	Methyl Ethyl Ketone	Toluene	Xylene	Sat. Hydrocarbons	
30	Air	1.5	1.1	0.4	7.1	2.9	0.3	
60	"	1.4	0.7	0.7	13.5	13.4	1.1	
90	"	1.0	0.3	0.3	7.6	13.8	0.4	
30 + 30	"	1.1	0.8	0.5	12.1	5.8	0.5	
30 + 30 + 30	"	0.6	0.5	0.3	8.1	4.2	0.2	
30	Oxygen	3.7	3.0	0.9	12.2	5.7	0.6	
60	"	0.8	0.9	0.3	6.3	5.7	0.4	
90	"	0.6	0.7	N.D.	3.3	4.8	0.4	
30 + 30	"	0.7	0.4	0.1	2.9	2.0	0.1	
30 + 30 + 30	"	0.5	0.3	0.2	2.1	1.5	0.1	

See Part 5.b, Results and Discussion, Section II.

Table XX

GAS-OFF PRODUCTS - SILVER MARKING INK NO. 1448 (W/Cresylic Acid)

Storage Time (Days)	Atmosphere	Wt. of Component (mg per 10 g Candidate Material)		
		2-Ethoxy- Ethanol	2-Ethoxy Ethyl Acetate	Acetone CO
30	Air	0.3	7.0	0.1 0.08
60	"	0.9	6.8	0.2 0.2
90	"	0.6	12.5	0.7 0.2
30 + 30	"	0.4	15.0	0.4 0.06
30 + 30 + 30	"	0.5	11.8	0.3 0.09
30	Oxygen	0.7	10.8	0.2 0.1
60	"	0.5	9.5	0.2 0.1
90	"	0.3	9.2	0.2 0.1
30 + 30	"	0.1	9.0	0.1 0.08
30 + 30 + 30	"	0.2	7.1	0.1 0.09

Table XXI
GAS-OFF PRODUCTS - LATEX FOAM RUBBER

<u>Storage Time (Days)</u>	<u>Atmosphere</u>	<u>Wt. of Component (mg per 10 g Candidate Material)</u>	
		<u>Carbonyl Sulfide</u>	<u>Carbon Disulfide</u>
30	Air	0.03	0.002
60	"	0.05	0.002
90	"	0.09	0.004
30 + 30	"	0.03	0.001
30 + 30 + 30	"	0.04	0.001
30	Oxygen	0.07	0.002
60	"	0.10	0.002
90	"	0.12	0.004
30 + 30	"	0.12	0.002
30 + 30 + 30	"	0.13	0.002

See Analytical Data, Results and Discussion, Section II.

Table XXII

GAS-OFF PRODUCTS - LOCKFOAM C-605 (R&T)

<u>Storage Time (Days)</u>	<u>Atmosphere</u>	<u>Wt. of Component (mg per 10 g Candidate Material) CO</u>
30	Air	<0.001
60	"	<0.001
90	"	<0.001
30 + 30	"	<0.001
30 + 30 + 30	"	<0.001
30	Oxygen	<0.001
60	"	<0.001
90	"	.0.08
30 + 30	"	<0.001
30 + 30 + 30	"	<0.001

See Part 5.c, Results and Discussion, Section II.

Table XXIII

GAS-OFF PRODUCTS - LOCKFOAM E-302 (R&T)

<u>Storage Time (Days)</u>	<u>Atmosphere</u>	<u>Wt. of Component (mg per 10 g Candidate Material) (Freon-11) Trichlorofluoro Methane</u>
30	Air	43
60	"	75
90	"	42
30 + 30	"	13
30 + 30 + 30	"	7.5
30	Oxygen	27
60	"	20
90	"	45
30 + 30	"	20
30 + 30 + 30	"	8.3

Table XXIV
GAS-OFF PRODUCTS - FLUOROLUBE OIL - GRADE FS-5

Storage Time (Days)	Atmosphere	Wt. of Component (mg per 10 g Candidate Material)					
		A	B	C	D	E	F
30	Air	0.11	0.04	0.05	0.05	-	-
60	"	0.16	0.07	0.09	0.03	0.09	0.01
90	"	0.11	0.04	0.06	0.02	0.05	0.005
30 + 30	"	0.09	0.03	0.05	0.02	0.04	0.005
30 + 30 + 30	"	0.10	0.04	0.06	0.03	0.05	0.004
30	Oxygen	0.14	0.11	0.10	0.09	-	-
60	"	0.16	0.07	0.09	0.03	0.08	0.01
90	"	0.11	0.04	0.06	0.02	0.05	0.005
30 + 30	"	0.11	0.04	0.06	0.03	0.05	0.01
30 + 30 + 30	"	0.10	0.04	0.06	0.03	0.05	0.004

Components A through F are various chlorofluorocarbons, C₆ or lower.

See Table XLIV, and Results and Discussion, Section II.

Table XXV

GAS-OFF PRODUCTS - FLUOROLUBE GREASE - GRADE GR-544 TYPE LG

Storage Time (Days)	Atmosphere	n-Butanol	Wt. of Component (mg per 10 g Candidate Material)		
			Total CClF Components	Benzene	Toluene
30	Air	0.2	0.02	0.006	<0.001
60	"	0.2	0.02	0.001	<0.001
90	"	0.2	0.02	0.001	<0.001
30 + 30	"	0.1	0.01	<0.001	<0.001
30 + 30 + 30	"	0.2	0.005	<0.001	<0.001
30	Oxygen	0.3	0.02	0.002	<0.001
60	"	0.2	0.02	0.002	N.D.
90	"	0.3	0.03	0.003	0.003
30 + 30	"	0.3	0.02	0.001	<0.001
30 + 30 + 30	"	0.2	0.01	<0.001	<0.001

See Results and Discussion, Section II.

Table XXVI
GAS-OFF PRODUCTS - SILICONE FLUID NO. 200

Storage Time (Days)	Atmosphere	Weight of Component (mg per 10 g Candidate Material)				
		Ethanol	Toluene	Xylene	Silicone Oil*	Trimethyl Silanol
30	Air	0.003	0.003	N.D.	0.008	0.003
60	"	<0.001	0.003	N.D.	0.015	0.002
90	"	N.D.	0.002	N.D.	0.007	0.002
30 + 30	"	0.006	0.03	0.04	0.04	0.006
30 + 30 + 30	"	0.005	0.01	0.01	0.03	0.003
30	Oxygen	0.002	0.002	<0.001	0.003	0.005
60	"	<0.001	<0.001	<0.001	0.006	<0.001
90	"	<0.001	0.006	N.D.	0.005	<0.001
30 + 30	"	N.D.	0.015	0.008	0.01	0.003
30 + 30 + 30	"	0.003	0.004	0.005	0.005	<0.001

*See Analytical Data, Results and Discussion, Section II.

Table XXVII
GAS-OFF PRODUCTS - SILICONE FLUID F-50

Storage Time (Days)	Atmosphere	Weight of Component (mg per 10 g Candidate Material)						
		Ethanol	Trimethyl Silanol	Toluene	Xylene	Silicone Oil (a)*	Silicone Oil (C)*	
30	Air	0.006	0.05	<0.001	N.D.	0.01	0.01	0.01
60	"	0.007	0.04	N.D.	N.D.	0.004	0.008	0.008
90	"	0.002	0.02	0.002	N.D.	0.003	0.03	0.03
30 + 30	"	0.004	0.06	0.005	N.D.	0.03	0.06	0.06
30 + 30 + 30	"	<0.001	0.003	N.D.	N.D.	0.008	0.008	0.008
30	Oxygen	0.003	0.11	0.003	0.002	0.03	0.5	0.5
60	"	0.005	0.02	<0.001	N.D.	0.005	0.2	0.2
90	"	0.003	0.01	N.D.	N.D.	0.02	0.3	0.3
30 + 30	"	0.002	0.02	<0.001	N.D.	0.005	0.2	0.2
30 + 30 + 30	"	0.002	0.01	<0.001	<0.001	<0.001	<0.001	0.03

*See Analytical Data, Results and Discussion, Section II.

Table XXVIII
GAS-OFF PRODUCTS - SILICONE GREASE G-300

Storage Time (Days)	Atmosphere	Weight of Component (mg per 10 g Candidate Material)				
		Alcohols*	Trimethyl Silanol	Trichloroethylene	Silicone Oil**	
30	Air	0.04	0.28	0.43	0.29	
60	"	0.02	0.04	0.02	0.01	
90	"	0.03	0.35	0.04	0.006	
30 + 30	"	0.003	0.05	0.02	0.04	
30 + 30 + 30	"	0.007	0.01	0.02	0.05	
30	Oxygen	0.01	0.45	0.27	0.15	
60	"	0.006	0.35	0.06	0.007	
90	"	0.007	0.37	0.1	N.D.	
30 + 30	"	0.02	0.23	0.17	0.02	
30 + 30 + 30	"	<0.001	<0.001	N.D.	<0.001	

*Combined ethanol and n-propanol.

**See Part 5.e and Analytical Data, Results and Discussion, Section II.

Table XXIX

GAS-OFF PRODUCTS - SILICONE RELEASE AGENT DC-7

<u>Storage Time</u> <u>(Days)</u>	<u>Weight of Component</u> <u>(mg per 10 g Candidate Material)</u>			
	<u>Atmosphere</u>	<u>Acetaldehyde</u>	<u>Ethanol</u>	<u>Silicone Oil*</u>
30	Air	N.D.	0.05	0.04
60	"	0.1	0.09	0.08
90	"	0.004	0.07	0.04
30 + 30	"	0.05	0.08	0.08
30 + 30 + 30	"	0.01	0.02	0.02
30	Oxygen	N.D.	0.2	0.03
60	"	0.008	0.1	0.06
90	"	0.009	0.07	0.05
30 + 30	"	0.02	0.07	0.07
30 + 30 + 30	"	0.01	0.03	0.02

*See Analytical Data, Results and Discussion, Section II.

Table XXX

GAS-OFF PRODUCTS - DC-4 (MIL-I-8660)

Storage Time (Days)	Wt. of Component (mg per 10 g Candidate Material)					
	Atmosphere	Ethanol	Silicone Oil*	Trimethyl Silanol	Saturated** Hydrocarbon	
30	Air	0.05	0.08	0.003		N.D.
60	"	0.06	0.07	0.005		0.009
90	"	0.06	0.1	0.004		0.02
30 + 30	"	0.03	0.06	0.002		0.01
30 + 30 + 30	"	0.03	0.05	0.002		0.002
30	Oxygen	0.08	0.05	0.004		N.D.
60	"	0.1	0.06	0.004		0.004
90	"	0.1	0.08	0.004		0.02
30 + 30	"	0.06	0.09	0.004		0.009
30 + 30 + 30	"	0.05	0.08	0.004		0.02

*See Analytical Data, Results and Discussion, Section II.

** C₄-C₅ Hydrocarbon according to mass spectral data.

Table XXXI

GAS-OFF PRODUCTS - WAX LUBRICANT NO. 111

<u>Storage Time (Days)</u>	<u>Atmosphere</u>	<u>Weight of Component (mg per 10 g Candidate Material)</u>	
		<u>Petroleum</u>	<u>Ether</u>
30	Air	0.9	
60	"	2.2	
90	"	4.2	
30 + 30	"	0.4	
30 + 30 + 30	"	0.2	
30	Oxygen	6.9	
60	"	7.8	
90	"	5.0	
30 + 30	"	3.6	
30 + 30 + 30	"	2.0	

Table XXXII
GAS-OFF PRODUCTS - SILASTIC RTV-882

Storage Time (Days)	Wt. of Component (mg per 10 g Candidate Material)	
	Atmosphere	Silicone Oil
30	Air	0.03
60	"	0.02
90	"	0.03
30 + 30	"	0.02
30 + 30 + 30	"	0.009
	"	N.D.
30	Oxygen	0.04
60	"	N.D.
90	"	0.02
30 + 30	"	<0.008
30 + 30 + 30	"	N.D.

* Samples prepared from a separate batch of RTV882.
 See Sample Preparation, Results and Discussion, Section II.

Table XXXIII

GAS-OFF PRODUCTS-SILASTIC RTV-731

<u>Storage Time (Days)</u>	<u>Atmosphere</u>	<u>Wt. of Component (mg per 10 g Candidate Material)</u>	
		<u>Acetic Acid</u>	<u>Trimethyl Silanol</u>
30	Air	1.4	0.003
60	"	0.1	0.010
90	"	0.008	N.D.
30 + 30	"	1.3	0.003
30 + 30 + 30	"	0.7	0.002
30	Oxygen	0.8	0.005
60	"	0.2	0.02
90	"	0.7	0.03
30 + 30	"	0.4	0.008
30 + 30 + 30	"	0.1	0.002

Table XXXIV

GAS-OFF PRODUCTS - SEALANT RTV-90

Storage Time (Days)	Atmosphere	Wt. of Component (mg per 10 g Candidate Material)		
		Ethanol	Saturated Hydrocarbons*	Silicone Oil**
30	Air	23.4	0.7	0.4
60	"	18.2	0.2	0.5
90	"	12.5	0.4	0.3
30 + 30	"	15.1	0.04	0.08
30 + 30 + 30	"	1.2	0.09	0.3
30	Oxygen	9.0	0.02	0.02
60	"	9.3	0.02	0.02
90	"	2.9	0.5	N.D.
30 + 30	"	3.0	0.005	0.02
30 + 30 + 30	"	1.5	0.004	0.01

*Estimated C₅₋₆ by Mass Spectrometry.

**See Analytical Data, Results and Discussion,
Section II.

Table XXXV

GAS-OFF PRODUCTS-SILASTIC RTV-501

<u>Storage Time (Days)</u>	<u>Atmosphere</u>	<u>Weight of Component (mg per 10 g Candidate Material)</u>		
		<u>n-Propanol</u>	<u>n-Butanol</u>	<u>Acetone</u>
30	Air	20.4	0.08	0.10
60	"	14.2	0.07	0.50
90	"	18.4	0.07	0.12
30 + 30	"	12.7	0.06	0.04
30 + 30 + 30	"	3.8	0.02	N.D.
30	Oxygen	11.8	0.05	0.05
60	"	13.0	0.05	0.20
90	"	8.5	0.04	N.D.
30 + 30	"	5.5	0.05	0.04
30 + 30 + 30	"	0.8	0.005	N.D.

Table XXXVI
GAS-OFF PRODUCTS - SILASTIC C/R Q-3-0121

<u>Storage Time (Days)</u>	<u>Atmosphere</u>	<u>Wt. of Component (mg per 10 g Candidate Material)</u>	
		<u>Acetic Acid</u>	<u>Trimethyl Silanol</u>
30	Air	2.5	0.06
60	"	0.2	0.01
90	"	3.1	0.008
30 + 30	"	2.7	0.01
30 + 30 + 30	"	1.5	0.01
30	Oxygen	1.8	0.008
60	"	0.5	0.01
90	"	2.2	0.05
30 + 30	"	1.1	0.003
30 + 30 + 30	"	0.2	0.002

Table XXXVII

GAS-OFF PRODUCTS - SILICONE EC 1663

Storage Time (Days)	Atmosphere	Wt. of Component (mg per 10 g Candidate Material)				
		Ethanol	Xylene	Trimethyl Silanol	Silanol	C8-9-
30	Air	1.8	0.05	0.003		1.9
60	"	1.8	0.04	-		0.6
90	"	2.9	N.D.	-		N.D.
30 + 30	"	0.3	0.02	-		0.2
30 + 30 + 30	"	0.2	0.09	-		0.2
30	Oxygen	2.0	0.04	0.01		0.6
60	"	2.4	0.06	0.005		0.8
90	"	2.0	0.05	-		0.5
30 + 30	"	0.2	0.03	-		0.8
30 + 30 + 30	"	0.25	0.06	-		0.2

Contrails

Table XXXVIII

GAS-OFF PRODUCTS - SEALER, EPON 828

Storage Time (Days)	Weight of Component (mg per 10 g Candidate Material)		
	<u>Atmosphere</u>	<u>Methyl Isobutyl Ketone</u>	<u>Ethanol</u>
30	Air	1.1	-
60	"	0.5	0.001
90	"	0.5	<0.001
30 + 30	"	1.1	0.003
30 + 30 + 30	"	0.6	<0.001
30	Oxygen	0.6	<0.001
60	"	0.5	0.05
90	"	0.7	0.09
30 + 30	"	0.8	0.04
30 + 30 + 30	"	0.8	0.002

Table XXXIX

GAS-OFF PRODUCTS - SILICONE PRIMER, A4004

Storage Time (Days)	Wt. of Component (mg per 10 g Candidate Material)						
	Atmosphere	Ethanol	n-Butanol	Saturated* Hydrocarbon	Benzene	Toluene	Xylene
30		10.9	7.6	1.7	-	-	-
60		3.0	9.1	1.1	-	0.04	-
90		3.6	9.9	1.4	0.2	0.06	0.05
30 + 30		2.0	5.5	1.1	-	0.06	-
30 + 30 + 30		0.2	0.6	0.3	-	0.01	0.009
30	Oxygen	1.5	4.4	0.5	0.04	0.04	-
60		1.3	4.1	0.6	-	0.07	-
90		1.4	4.4	0.8	0.04	0.01	-
30 + 30		1.6	4.6	0.3	0.03	0.09	0.04
30 + 30 + 30		1.7	1.3	0.8	0.1	0.04	-

*Estimated C₅₋₆ by Mass Spectrometry

Contrails

Table XL
GAS-OFF PRODUCTS - SILICONE PRIMER, SS4004

Storage Time (Days)	Atmosphere	Wt. of Component (Mg per 10 g Candidate Material)					Acetone
		Ethanol	n-Butanol & 2-Propanol	Toluene	Xylene	C3 Alkyl Benzene*	
30	Air	10.3	53	2.0	0.2	0.2	~2.0
60	"	5.0	45	4.5	<0.2	<0.2	~2.0
90	"	7.5	27	17.5	0.2	<0.2	~2.0
30 + 30	"	6.6	25	0.6	0.2	<0.2	~2.0
30 + 30 + 30	"	6.0	20	0.8	<0.2	<0.2	~2.0
30	Oxygen	13.0	86	5.6	0.7	0.2	~2.0
60	"	7.6	56	1.5	<0.2	<0.2	~2.0
90	"	16.5	102.4	2.6	1.0	<0.2	~2.0
30 + 30	"	4.6	25	1.6	0.2	<0.2	~2.0
30 + 30 + 30	"	4.0	23	1.1	0.2	<0.2	~2.0

*e.g., trimethyl, methyl-ethyl, n-propyl or isopropyl benzene.

70

Table XLI

GAS-OFF PRODUCTS - SILICONE PRIMER, EC-1694

<u>Storage Time (Days)</u>	<u>Atmosphere</u>	<u>Weight of Component (mg per 10 g Candidate Material)</u>			
		<u>Ethanol</u>	<u>n-Butanol</u>	<u>2-Propanol</u>	<u>Toluene</u>
30	Air	4.6	14.2	26.4	2.7
60	"	4.6	6.5	29.6	3.4
90	"	8.2	10.0	18.9	7.9
30 + 30	"	1.8	15.5	15.3	0.7
30 + 30 + 30	"	0.4	13.8	8.3	0.1
30	Oxygen	4.1	11.1	21.7	3.3
60	"	4.6	10.4	27.9	4.2
90	"	7.2	12.6	25.4	6.5
30 + 30	"	2.3	10.7	14.8	2.9
30 + 30 + 30	"	0.8	9.6	10.5	1.1

Contrails

Table XLII

GAS-OFF PRODUCTS - ELECTRICAL RESIN, SCOTCHCAST NO. 8

Storage Time (Days)	Atmosphere	Wt. of Component (mg per 10 g Candidate Material)				
		Acetone	Toluene	CO	n-Propanol Benzene	
30	Air	0.1	0.05	0.002	0.03	N.D.
60	"	0.1	0.03	0.003	0.08	0.003
90	"	0.03	0.02	< 0.001	0.05	0.002
30 + 30	"	0.02	0.01	0.001	0.02	< 0.001
30 + 30 + 30	"	0.01	0.007	< 0.001	0.02	N.D.
30	Oxygen	0.1	0.06	0.005	0.02	N.D.
60	"	0.08	0.05	0.005	0.08	0.004
90	"	0.04	0.02	0.003	0.05	0.004
30 + 30	"	0.02	0.01	0.001	0.02	N.D.
30 + 30 + 30	"	0.005	0.003	0.003	0.02	N.D.

Table XLIII
GAS-OFF PRODUCTS - DC-325

<u>Storage Time (Days)</u>	<u>Atmosphere</u>	<u>Wt. of Component (mg per 10 g Candidate Material)</u>		
		<u>Acetone</u>	<u>Trimethyl Silanol</u>	<u>Toluene</u>
30	Air	0.005	0.005	0.002
60	"	0.1	0.006	0.006
90	"	0.02	0.006	0.002
30 + 30	"	0.008	0.003	0.004
30 + 30 + 30	"	N.D.	0.007	N.D.
30	Oxygen	0.02	0.02	0.002
60	"	0.02	0.009	0.003
90	"	0.02	0.01	0.001
30 + 30	"	0.02	0.02	0.001
30 + 30 + 30	"	0.007	0.02	0.001

Table XLIV

GAS-OFF PRODUCT - PLEXIGLAS NO. 2 CLEARMIL

<u>Storage Time (Days)</u>	<u>Atmosphere</u>	<u>Wt. of Methylmethacrylate (Mg. per 10 g. Candidate Material)</u>
30	Air	<0.03
60	"	<0.05
90	"	<0.01
30 + 30	"	N.D.
30 + 30 + 30	"	N.D.
30	Oxygen	<0.01
60	"	<0.02
90	"	<0.04
30 + 30	"	N.D.
30 + 30 + 30	"	N.D.

See Part 5.f, Results and Discussion, Section II.

Table XLV
GAS-OFF PRODUCTS - THERMOFIT TUBING SPLICER C/R 197-075

<u>Storage Time (Days)</u>	<u>Atmosphere</u>	<u>Wt. of Component (mg per 10 g Candidate Material)</u> C4-C6 Hydrocarbon(s)*
30	Air	<0.001
60	"	<0.001
90	"	<0.001
30 + 30	"	<0.001
30 + 30 + 30	"	<0.001
30	Oxygen	<0.001
60	"	<0.001
90	"	<0.001
30 + 30	"	<0.001
30 + 30 + 30	"	<0.001

*Determined by Mass Spectrometry.

Table XLVI

GAS-OFF PRODUCTS - ACETAL RESIN, DELRIN NO. 100

<u>Storage Time (Days)</u>	<u>Atmosphere</u>	<u>Weight of Component (mg per 10 g Candidate Material)</u>		
		<u>Formaldehyde</u>	<u>Acetaldehyde</u>	<u>Acetic Acid</u>
30	Air	0.1	0.004	-
60	"	0.15	0.005	-
90	"	0.3	0.02	-
30 + 30	"	0.2	0.02	-
30 + 30 + 30	"	0.2	0.005	0.02
30	Oxygen	0.1	0.02	-
60	"	0.1	0.008	-
90	"	0.4	0.02	-
30 + 30	"	0.25	0.01	-
30 + 30 + 30	"	0.2	0.008	0.03

See Part 5.g, Results and Discussion, Section II.

APPENDIX II

REPRESENTATIVE MASS SPECTRAL DATA
FOR
GAS-OFF EXPERIMENTS

Contrails

Mass spectral data were obtained using a Consolidated Electrodynamics 21-103C mass spectrometer. A heated inlet, maintained at a temperature of 135°C, was employed. Conditions were standardized at 70 volts ionizing potential and 10 micro-amperes ionizing current.

The observed spectrum is given in the first column in chart divisions. The contribution of each known component has been calculated in chart divisions using a reference spectrum. The source of the reference spectrum is listed at the foot of each table as:

CEC Serial No. - Keysort File of Mass Spectra Consolidated
Electrodynamic Corp.

API Serial No. - American Petroleum Institute Research
Project 44

MRC Spectra - Monsanto Research Corp. Spectra File

Contrails

Table XLVII

**REPRESENTATIVE MASS SPECTRAL DATA
FOR ADHESIVE, A-4000**

Mn	Spectrum of Mixture	Calculated Components						G, H, I, J, K	Mass No.	Spectrum of Mixture	Calculated Components						G, H, I, J, K
		A	B	C	D	E	F				A	B	C	D	E	F	
14	64.7				1.1		50.1	13.5	62	23.8		17.6	3.0	0.2			
15	213.3		20.1	0.9	5.3		160.7		63	57.5		48.5	6.5				
16	144.0				0.3		6.6	137.1	64	12.3		10.7	1.6				
17	925.0				0.2		6.5	918.3	65	70.3		59.5	9.6				
18	3180.0						8.3	3171.7	66	27.0		8.2	1.2				
19	81.8						77.5		67	4.5							
20	8.1								68								
21									69	1.5							
22	2.1							2.1	70	1.0							
23									71	1.8							
24	1.4								72	3.0				0.3			
25	8.0				0.3	7.1			73	30.5	31.4			1.0			
26	55.3		11.0	1.5	0.5	1.3	37.4		74	19.3	7.8	11.7	0.8	0.7			
27	283.8		72.5	3.7	1.1	1.8	194.4		75	93.0	4.6	11.3	0.5	76.6			
28	121.2		5.8		2.8	0.4	18.3	93.9	76	15.0		8.2	0.3	4.9			
29	152.1				2.0	1.0	138.3		77	106.2		99.9	0.9	2.8			
30	12.1				0.4		11.8		78	65.8		59.1					
31	78.7				0.7	0.1	64.7		79	52.5		56.0					
32	21.6							21.6	80	3.5		3.5					
33	1.0								81								
34									82								
35									83								
36	3.9				0.1				84	1.0							
37	30.6		6.4	1.7	0.5	18.5			85	2.4			0.4				
38	57.7		21.0	3.6	0.5	27.8			86	4.0			0.6				
39	220.2		122.6	13.8	0.2	0.9	79.8		87	6.4			0.4				
40	29.9		13.4	1.6	0.1	0.2	12.0	2.6	88	1.6			0.1				
41	111.6		17.9	1.5	0.5	0.5	85.3		89	20.2		15.7	3.0				
42	58.0				1.1	1.6	53.4		90	11.1		5.9	2.5				
43	237.3			1.3	3.4	22.9	217.2		91	831.0		756.6	74.4				
44	152.4			0.7	0.7	0.5	39.7	110.8	92	66.3		56.4	51.3				
45	1131.0			3.6	18.7		1108.7		93	2.3							
46	29.1			2.6	1.4		25.4		94								
47	13.5				9.6				95								
48	0.8				0.5				96	3.8							
49	7.5		3.6	0.7	0.3				97								
50	58.2		46.9	4.5					98	2.4							
51	130.5		115.8	7.1					99								
52	60.2		54.0	1.8					100								
53	32.1		29.8	0.9	0.5				101	3.0							
54	3.0				0.1				102	10.2		10.3					
55	5.8				0.4				103	42.0		43.0					
56	4.5				0.2				104	18.5		22.3					
57	6.1				0.4	0.2			105	180.0		182.3					
58	6.2				0.2	6.2			106	401.0		401.0					
59	52.3	3.3			2.2	0.2	37.9		107	35.5		38.0					
60	7.1				1.2		4.5		108	1.3							
61	13.1		5.1	1.5	2.0				109								

A - Silicone Oil (See Text, Results & Discussion)
 B - Xylene (CEC Card No. 220)
 C - Toluene (CEC Card No. 214)
 D - Trimethyl Silanol (MRC Specta)
 E - Acetone (CEC Card No. 318)
 F - 2-Propanol (CEC Card No. 326)

G - Water)
 H - Nitrogen)
 I - Oxygen) Atmospheric
 J - Carbon Dioxide) Contamination
 K - Argon)

Contrails

Table XLVII- Cont'd

Mass No.	Spectrum of Mixture	Calculated Components							Mass No.	Spectrum of Mixture	Calculated Components							
		A	B	C	D	E	F	GHI J, K										
125	1.0	1.6																
133	8.3	5.9																
147	129.9	9.5																
148	21.0																	
149	14.1																	
191	3.8	3.6																
193	2.5	3.9																
207	23.8	10.8																
249	1.3	2.0																
251	0.9	2.1																
265	1.9	2.3																
267	0.8	9.5																
281	32.7	32.7																
282	9.1	9.2																
283	5.8	5.9																

Table XLVIII

REPRESENTATIVE MASS SPECTRAL DATA
FOR ADHESIVE, NO. 271

Mass No.	Spectrum of Mixture	Calculated Components					Mass No.	Spectrum of Mixture	Calculated Components				
		A	B	C	D	E			A	B	C	D	E
14	27.4		3.7				62						
15	48.7		11.8	22.2			63						
16	186.5						64						
17	996						65						
18	3470						66						
19	10.9		5.7				67						
20	9.2						68						
21							69						
22	7.5						70						
23							71						
24							72						
25							73	10.0				10.0	
26	9.8	1.0	2.7	2.1			74	3.8				4.0	
27	37.9	1.9	14.2	4.6			75	323		323			
28	201		1.3	11.9			76	24.5		20.8			
29	38.8	2.0	10.1	8.6			77	15.5		11.8	0.7		
30	3.5		0.9	1.7			78						
31	18	7.5	4.7	3.1			79						
32	62.5						80						
33							81						
34							82						
35	2.8						83						
36	1.8						84						
37	3.8		1.3				85						
38	4.8		2.0				86						
39	16.3		5.9				87						
40	9.9		1.0				88						
41	25		6.2	2.1			89						
42	17.7		3.9	4.6			90						
43	99.9		15.9	14.3			91	4.8			4.8		
44	425		2.9	3.1			92	1.0			0.4		
45	163.2	2.7	81	78.9									
46	9.7	1.2	1.9	6.3			105	1.2			1.4		
47	4.4			40.6			106	2.2			2.5		
48	3.8												
49	1.9						133	4.0				4.0	
50	1.0												
51	3.4						147	6.2					
52	1.2												
53	3.2						281	8.5				8.5	
54	1.0						282	2.3				2.3	
55	4.2						283	1.3				1.3	
56	5.0												
57	6.8												
58	11.8												
59	12.9		2.3	9.4		1.0							
60	7.8		0.7	5.0									
61	9.4			8.6									

A - Ethanol (CEC Card No. 312)
 B - 2-Propanol (CEC Card No. 326)
 C - Trimethyl Silanol (MRC Spectra)
 D - Xylene (CEC Card No. 220)
 E - Silicone Oil (See Text, Results & Discussion)

Note: Lines at 43,57,58, mass no's. indicate C₄-C₅ Hydrocarbon also. Atmospheric Components CO₂, Argon, Water and some N₂ and O₂ present.

Table XLIX

REPRESENTATIVE MASS SPECTRAL DATA
FOR RESIN, VERSAMID 125

Mass No.	Spectrum of Mixture	Calculated Components					Mass No.	Spectrum of Mixture	Calculated Components					
		A	B	C	D, E, F, G, H				A	B	C	D, E, F, G, H		
14	281.0	3.6	173.8				62							
15	814.0	8.2	592.5				63							
16	7490.0	1.6	6320.1			69.9	64							
17	8390.0	2.5	7900.1			489.9	65							
18	1701.0	10.6	27.0			1663.4	66							
19	3.7					2.7	67							
20	3.8						68							
21							69							
22							70							
23							71							
24							72							
25	1.6	0.8					73							
26	9.6	4.4					74							
27	24.1	11.0					75							
28	111.6	23.9				87.7	76							
29	19.6	6.1					77							
30	82.6	82.6					78							
31	7.1	1.4					79							
32	6.9					6.9	80							
33							81							
34							82							
35							83							
36							84							
37							85							
38	3.0	1.3					86							
39	8.7	1.8		1.6			87							
40	10.8	3.8				7.0	88							
41	15.4	3.9					89							
42	11.9	7.4					90							
43	16.6	2.5					91	9.6			9.6			
44	17.0	16.2				0.8	92	3.2			0.7			
45	11.0	15.5					93							
46							94							
47							95							
48							96							
49							97							
50	1.2			1.5			98							
51	2.4						99							
52	1.4						100							
53	2.1						101							
54	1.2						102							
55	2.5						103							
56	2.9						104							
57	5.2						105	1.8			2.3			
58	1.3						106	3.4			5.1			
59	1.0						107							
60							108							
61							109							

- A - Ethyl Amine (API Serial No. 764)
 - B - Ammonia (API Serial No. 90)
 - C - Xylene (CEC Card No. 220)
 - D - Water
 - E - Nitrogen
 - F - Oxygen
 - G - Carbon Dioxide
 - H - Argon
- } Atmospheric Contamination

Table L

**REPRESENTATIVE MASS SPECTRAL DATA
FOR NEOPRENE, PHENOLIC EC-847**

Peak No.	Spectrum of Mixture	Calculated Components								M, I, J, K, L	Peak No.	Spectrum of Mixture	Calculated Components					
		A	B	C	D*	E	F	G	H				A	B	C	D	E	F
1	735.0									735.0	60							
2	3500.0										63	18.0		4.8				
3	133.2									133.2	64							
4	83.0									83.0	65	24.0		7.0				
5	255.0									255.0	66							
6	8.8										67	42.8						
7	17.3										68	38.0						
8											69	318.0					C5 H9	
9											70	250.5					C5 H10	
10											71	480.0		2.1			C5 H11	
11	25.9										72	46.0		46.0				
12	153.9	117.3	1.9								73	3.0		2.1				
13	745.0	443.6	14.2						6.4		74							
14	2190.0	618.1	43.7	2.7					19.8		75							
15	754.0	134.3	8.0						6.7	605.0	76							
16	1674.0	331.0	67.4						18.3		77	10.5					3.0	
17	41.5	13.1	1.5						2.6		78	18.5					18.5	
18	50.0	44.0							106.7		79							
19	83.0								2.4	80.6	80							
20											81							
21											82							
22											83	75.8						
23	63.5	44.8									84	219.0					C6 H12	
24	258.0	161.3	1.9						1.2		85	130.0					C6 H13	
25	333.0	179.0	2.4						1.8		86	106.8					C6 H14	
26	1350.0	294.0	6.2	10.2					5.6		87	12.0						
27	258.0	62.5	0.7						1.1		88							
28	2454.0	162.8	4.3						7.0		89							
29	2010.0	539.3	14.5						8.6		90							
30		7716.0	285.7						4.0		91	56.5		54.6			1.9	
31	648.0	173.6	7.0						467.4		92	36.6		37.6				
32	58.4		1.9	2.7					4.7		93							
33											94							
34											95							
35											96							
36											97							
37	58.0		1.7	3.3					3.5		98	26.0					C7 H14	
38	82.8			5.2					3.9		99							
39	39.4								3.8		100	26.5					C7 H16	
40	154.2										101							
41	68.0										102							
42	608.0		1.3								103							
43	1800.0										104							
44	1680.0	63.3							1.6		105	0.4					0.5	
45	2091.0	2091.0									106	1.0					1.0	
46	87.0	72.5							10.4		107							
47	7.0								7.0		108							
48											109							
49											110							

A - Acetone (CEC Card No. 318)
 B - 2-Butanone (CEC Card No. 339)
 C - Toluene (CEC Card No. 214)
 D - Sat. Hydrocarbons
 E - Xylene (CEC Card No. 220)
 F - Benzene (CEC Card No. 212)

G - 1-Propanol (CEC Card No. 325)
 H - Water
 I - Nitrogen
 J - Oxygen
 K - Carbon Dioxide
 L - Argon

* Hydrocarbon portion identified as 5 separate C₆ and C₇ hydrocarbons by collection of GLE fractions.
 Atmospheric Contamination

Contrails

Table LI

REPRESENTATIVE MASS SPECTRAL DATA
FOR SILASTIC NO. 950

Peak No.	Spectrum of Mixture	Calculated Components				Mass No.	Spectrum of Mixture	Calculated Components			
		B, C, D, E, F									
14	190.0		190.0			52					
15	6.6					53					
16	170.4		170.4			64					
17	756.0		756.0			65					
18	2620.0		2620.0			66					
19	4.2		4.2			67					
20	9.6					68					
21						69					
22	1.5		1.5			70					
23						71					
24						72					
25						73					
26	1.5					74					
27	2.9					75					
28	1086.0		1086.0			76					
29	10.6	C ₂ H ₅	10.6			77					
30						78					
31	1.4					79					
32	240.3		240.3			80					
33						81					
34	1.0		1.0			82					
35	0.7					83					
36	2.5					84					
37	0.4					85					
38	1.2					86					
39	1.3					87					
40	19.4		19.4			88					
41	1.4					89					
42	1.5					90					
43	16.1	C ₃ H ₇				91					
44	59.3		59.3			92					
45	2.4		2.4			93					
46						94					
47						95					
48						96					
49						97					
50						98					
51						99					
52						100					
53						101					
54						102					
55	0.9					103					
56	0.4					104					
57	1.5	C ₄ H ₉				105					
58	3.8	C ₄ H ₁₀				106					
59						107					
60						108					
61						109					

- A - Sat. Hydrocarbon
- B - Water)
- C - Nitrogen)
- D - Oxygen) Atmospheric
- E - Carbon Dioxide) Contamination
- F - Argon)

Table LII

**REPRESENTATIVE MASS SPECTRAL DATA
FOR SILASTIC S2007**

No. of Mixture	Spectrum of Mixture	Calculated Components					Mass No.	Spectrum of Mixture	Calculated Components				
		A	B	C	D	E, F, G, H, I			A	B	C	D	E, F, G, H, I
14	562.0			293.4	275.0		62						
15	1170.0			476.3	666.0		63						
16	2445.0			29.4	99.1	2316.5	64						
17	814.0			49.2		764.8	65						
18	2670.0			37.9		2632.1	66						
19	139.2			127.8			67						
20	8.3						68						
21							69						
22	365.0					365.0	70						
23							71						
24	46.7			22.6	29.6		72	10.0					
25	179.4			104.0	86.2		73	189.6	287.0				
26	559.0			421.1	156.4		74	15.5	71.7	1.9			
27	1007.0			1001.1	78.0		75	24.2	41.9	3.3			
28	2688.0			280.5	63.3	2344.2							
29	2679.0			1087.3	1583.0								
30	273.0			249.5	18.0		111	9.0		6.2			
31	4030.0			4030.0			125	9.0	15.0				
32	63.8			49.6		14.2	133	31.5	53.8				
33	8.5						134	5.0					
34							146	19.0		19.0			
35							147	5.0	86.7				
36							148	13.0		12.3			
37							177	6.8					
38							191	17.5	32.9				
39	6.3						193	16.6	35.9				
40	48.9				15.7	33.2	207	19.8	98.7				
41	108.0			43.1	64.0		249	12.1	17.9				
42	289.0			140.2	148.8		251	8.0	19.4				
43	813.0			346.6	419.0		265	16.0	20.9				
44	>10,000			67.7	713.1	>10,000	267	19.5	86.7				
45	1698.0			1452.0	20.9		281	299.0	299.0				
46	637.0			627.0			282	85.0	83.7				
47	61.3						283	51.0	53.8				
48													
49													
50	6.2												
51													
52													
53													
54													
55	5.3												
56													
57													
58													
59	10.0	30.0											
60													
61	10.3												

A - Silicone Oil (See Text, Results & Discussion)	E - Water)
B - Dichlorobenzene (MRC Spectra)	F - Nitrogen)
C - Ethanol (CEC Card No. 312)	G - Oxygen) Atmospheric
D - Acetaldehyde (CEC Card No. 288)	H - Carbon Dioxide) Contamination
	I - Argon)

Table LIII
 REPRESENTATIVE MASS SPECTRAL DATA
 FOR SILASTIC 950-4-400

No.	Spectrum of Mixture	Calculated Components				Mass No.	Spectrum of Mixture	Calculated Components			
		A	B	C, D, E, F, G				A	B	C, D, E, F, G	
15	13.5	5.5		8.0		52					
16	24.3	8.9				63					
17	313.0	0.6		312.4		64					
18	730.0	0.9		729.1		65					
19	2484.0	0.2		2483.8		66					
20	8.9	2.4		6.5		67					
21	5.5					68					
22						69					
23	35.2			35.2		70					
24						71					
25	0.9	0.4				72					
26	2.8	1.9				73					
27	11.2	7.9				74					
28	29.3	18.7				75					
29	247.5	5.2		242.3		76					
30	32.7	20.3				77					
31	7.3	4.7				78					
32	75.4	75.4				79					
33	9.2	0.9		8.1		80					
34						81					
35						82					
36	0.5					83					
37	1.5					84					
38	2.2					85					
39	6.0					86					
40	4.1			4.1		87					
41	6.3	0.8				88					
42	7.1	2.6				89					
43	42.5	6.5				90					
44	1983.0	1.3		1981.7		91					
45	83.6	27.2		56.4		92					
46	19.3	11.7				93					
47	0.7					94					
48						95					
49						96					
50	1.0					97					
51	1.2					98					
52	0.8					99					
53	0.9					100					
54						207	0.7	0.5			
55	1.9					281	1.6	1.6			
56	1.2					282	0.2	0.4			
57	1.9										
58	6.0										
59	2.9		0.2								
60											
61											

- A - Ethanol (CEC Card No. 312)
- B - Silicone Oil (See Text, Results & Discussion)
- C - Water)
- D - Nitrogen)
- E - Oxygen) Atmospheric Contamination
- F - Carbon Dioxide)
- G - Argon)

Table LIV

REPRESENTATIVE MASS SPECTRAL DATA
FOR SILASTIC 9711-2-480

Mass No.	Spectrum of Mixture	Calculated Components				Mass No.	Spectrum of Mixture	Calculated Components			
		A	B	C, D, E				A	B		
14	7.2					62					
15	11.0					63					
16	516.0			516		64					
17	483.0			483		65					
18	1650.0			1650		66					
19	3.0					67					
20	4.1					68					
21						69					
22	73.9					70					
23						71					
24						72					
25						73	2.3	10.0			
26	3.4					74	0.2	2.5			
27	7.8		0.2			75	1.2	1.5			
28	482.0			482		76					
29	18.2					77	0.4	0.3			
30	4.1					78	1.5	0.2			
31	7.3					79	0.3	0.2			
32	10.0			10.0		80					
33						81					
34						82	1.2				
35	2.1					83					
36						84					
37	1.3					85					
38	1.2					86					
39	3.9		0.4			87	1.3				
40	6.5					88					
41	4.5					89	0.4				
42	2.8					90					
43	21.2			4270		91	2.4	2.4			
44	4270.0			43		92		0.2			
45	56.6										
46	17.6					96	5.1	0.7			
47	3.6					105	0.6	0.6			
48	1.4					106	0.6	1.3			
49	1.0					133	3.2	1.9			
50	1.1					177	0.8				
51	1.0		0.4			191	2.8	1.1			
52	0.6		0.2			193	1.4	1.2			
53						207	29.1	3.4			
54						208	6.2	0.7			
55	2.2					209	3.5	0.4			
56	1.3					265	0.3	0.7			
57	2.8					267	0.3	3.0			
58	3.5					281	10.4	10.4			
59	1.1	1.0				282	2.6	2.9			
60						283	1.7	1.9			
61											

A - Silicone Oil (See Text, Results & Discussion)
 B - Xylene (CEC Card No. 220)
 C - Water
 D - Nitrogen
 E - Oxygen
 F - Carbon dioxide

Contrails

Table LV

**REPRESENTATIVE MASS SPECTRAL DATA
FOR WIRE (MIL-W-16878-C), TYPE E 22-W-9 5M114E22W9**

Mass No.	Spectrum of Mixture	Calculated Components				Mass No.	Spectrum of Mixture	Calculated Components			
		Hydro-Carbon									
62											
63											
64											
65		249									
66		1260	(H ₂ O)								
67		3160									
68		10.8									
69		9.8									
70		8.1	(CO ₂ (++))			1.0	C ₅ H ₁₀				
71						1.2	C ₅ H ₁₁				
72						0.8	C ₅ H ₁₂				
73						0.5					
74											
75		4.1									
76		83.4	(N ₂)								
77		4.5									
78											
79		4.8									
80		12.2	(O ₂)								
81											
82											
83											
84											
85											
86											
87		2.0									
88		3.0	(Argon)								
89		5.0	C ₃ H ₅								
90		1.9									
91		5.7	C ₃ H ₇								
92		457	CO ₂								
93		6.5									
94		2.0									
95											
96											
97											
98											
99											
100											
101											
102											
103		2.0	C ₄ H ₇								
104		2.5	C ₄ H ₈								
105		1.0	C ₄ H ₉								
106											
107											
108											
109											

Table LVI

**REPRESENTATIVE MASS SPECTRAL DATA
FOR VELVET COATING NO. 104-C 10 BLACK**

M	Relative Abundance	Calculated Components					E, F, G, H, I, O,	Mass No.	Spectrum of Mixture	Calculated Components				
		A	B	C	D					A	B	C	D	
62	97.5			2.3		95.2	62	1.0						
63	340.0			3.8			63	2.0						
64	807.0			0.2		806.8	64	1.0						
65	119.4			0.4		119.0	65	2.5		1.9				
66	390.0			0.3		389.7	66							
67	6.5			1.0			67	1.5						
68	2.8					2.8	68	1.0						
69							69	3.9						
70	125.7					125.7	70	5.8						
71							71	14.8	5.2					
72	3.0			0.8			72	120.0	120.0					
73	14.2			3.3	2.3		73	6.0	5.6					
74	82.0	38.5		2.2	8.8		74	3.8						
75	229.8	117.8		7.9	12.2		75							
76	975.0	21.5			2.7	950.8	76							
77	549.0	177.5		8.6	6.6		77							
78	55.0	4.0		2.0	0.3		78							
79	36.4	4.4		32.0	0.9		79							
80	226.2			0.4		225.8	80							
81	3.8						81							
82							82							
83							83							
84	2.8				0.9		84							
85	14.9				3.2		85							
86	19.2	6.2			3.5		86							
87	61.3	17.2	2.8		5.8		87							
88	18.5	2.0			1.2	15.3	88							
89	76.7	12.6		0.3	3.2		89							
90	91.5	37.9		1.1	10.7		90							
91	958.0	727.3		2.8	152.8		91	15.0		15.0				
92	7400.0	19.9		0.5	3.4	7376.2	92	9.3		10.3				
93	138.0	12.7			11.5		93							
94	32.7				5.0		94							
95							95							
96							96							
97	3.8						97							
98	8.3			0.9			98							
99	7.0	2.4	1.4				99							
100	2.5	0.9					100							
101	8.0	4.1					101							
102	3.0	1.5					102							
103	15.2	4.1					103							
104	13.0	1.4					104							
105	72.6	44.4			1.3		105							
106	43.0	1.6			41.4		106							
107	5.0				1.4		107							
108	10.8						108							
109	1.0						109							

A - 2 Butanone (API Serial No. 429)
 B - Toluene (CEC Card No. 214)
 C - Ethanol (CEC Card No 312)
 D - Acetone (CEC Card No 318)

E - Water)
 F - Nitrogen) Atmospheric
 G - Oxygen) Contamination
 H - Carbon Dioxide)
 I - Argon)

Contrails

Table LVII

**REPRESENTATIVE MASS SPECTRAL DATA
FOR CLASS H SILICONE IMPREGNATING VARNISH, NO. 997**

Mass No.	Spectrum of Mixture	Calculated Components					Mass No.	Spectrum of Mixture	Calculated Components				
		A	B	C	D	E, F, G, H, I			A	B	C	D	E, F, G, H, I
14	32.8			6.9		25.9	62	1.0	0.8				
15	63.5		0.7	11.3			63	4.8	2.1				
16	467.0			0.7		466.3	64	1.0	0.5				
17	870.0			1.2		868.8	65	4.0	2.6				
18	2961.0			0.9		2960.1	66						
19	7.4			3.0			67						
20	6.8						68						
21							69						
22	56.5						70	1.4					
23							71						
24	3.5			0.5	0.8		72	2.7					
25	14.0			2.5	3.6		73	14.5		0.8			
26	54.3	0.5	2.1	10.0	18.4		74	4.0	0.5	2.5			
27	109.2	3.1	1.7	23.7	50.0		75	2.9	0.5	0.8			
28	522.0			6.6	59.3	456.1	76	3.5	0.4	1.9			
29	209.4			25.7	85.9		77	11.7	4.3	7.7			
30	22.3			5.9	4.9		78	50.0	2.5	47.5			
31	97.8			95.4	2.4		79	5.5	2.4	3.0			
32	10.6			1.2		9.4	80						
33							81						
34							82	1.0					
35	2.5						83	12.3					
36	1.7				0.6		84						
37	8.0		2.3		2.2		85	8.0					
38	8.5	0.9	2.9		2.3		86						
39	24.0	5.3	6.7		3.5		87	1.6					
40	9.0	0.6			0.9	7.5	88						
41	17.1	0.8		1.0	1.7		89	1.2	0.7				
42	17.5			3.3	3.3		90						
43	48.5			8.2	9.7		91	32.6	32.6				
44	3440.0			1.6	2.6	3435.6	92		2.4				
45	75.3			34.4			93						
46	25.5			14.8			94						
47	4.5						95						
48	2.5						96						
49	2.9		1.5				97						
50	12.2	2.0	9.0				98						
51	15.6	5.0	10.1				99						
52	11.8	2.3	9.7				100						
53	2.9	1.3			0.8		101						
54							102						
55	6.0				1.4		103	2.0	1.9				
56	4.3		1.7		0.7		104	0.7	1.0				
57	12.3				9.3		105	5.2	7.9				
58	32.1				32.1		106	14.3	17.3				
59	3.5				1.3		107						
60	1.0						108						
61	1.0						109						

A - Xylene (CEC Card No. 220)
 B - Benzene (CEC Card No. 212)
 C - Ethanol (CEC Card No. 312)
 D - Propionaldehyde (CEC Card No. 319)

E - Water
 F - Nitrogen
 G - Oxygen
 H - Carbon Dioxide
 I - Argon

} Atmospheric Contamination

Table LVIII

REPRESENTATIVE MASS SPECTRAL DATA
FOR 620 LIGHT GULL GRAY XA-193

Mixture No.	Spectrum of Mixture	Calculated Components								H, I, J, K, L	Mixture No.	Spectrum of Mixture	Calculated Components					H, I, J, K
		A	B	C	D	E	F	G	C				D	E	F	G		
14	34.0		6.6							27.4	62	95.4			0.4	50.1	32.5	
15	129.0	1.2	21.2				0.8	15.5	37.1		63	216.3			1.9	108.4	89.5	
16	19.5								19.5		64	48.0				25.9	19.7	
17	78.0								78.0		65	279.0				158.9	109.7	
18	275.0								275.0		66	36.1				20.1	15.2	
19	9.0		10.2								67							
20											68							
21											69	12.0						
22											70	10.0						
23											71	11.5	C ₅ H ₁₁	0.7				
24											72	16.2	C ₅ H ₁₂	16.2				
25											73	10.5		0.8				
26	73.8	1.0	4.9		5.0	2.3	24.9	20.4			74	44.0			2.7	13.1	21.6	
27	275.0	2.4	25.6		15.4	1.8	61.7	133.7			75	30.5			1.0	8.5	20.9	
28	43.6		2.4		2.8			10.6	27.8		76	25.5			1.1	5.4	15.2	
29	73.5	2.6	18.2	C ₂ H ₅	23.7						77	210.0			8.4	14.5	184.3	
30											78	161.0			52.0		109.0	
31	18.3	9.8	8.5								79	99.0			3.3		103.3	
32	5.0								5.0		80	8.0					6.4	
33											81							
34											82							
35											83	11.5						
36											84	9.0						
37	59.0		2.4		0.7	0.4	28.2	11.9			85	19.0	C ₆ H ₁₃			7.3		
38	126.0		3.7		0.8	3.2	59.5	38.8			86	18.0				10.6		
39	510.0		10.5		2.2	7.3	229.1	226.2			87	13.5				6.7		
40	57.9		1.6		0.3		25.6	24.7	5.7		88							
41	105.0		11.2		1.5		24.9	33.1			89	82.2				49.2	29.0	
42	27.0		7.0		5.1						90	85.0				41.9	10.9	
43	189.0	0.8	28.6	C ₃ H ₇	100.6			21.3			91	2628.0				1232.0	1396.0	
44	89.0		5.2		2.5		12.0		69.3		92	910.0				848.8	104.1	
45	165.0	3.5	146.2		0.7		60.0				93	70.3				67.0		
46	48.5	1.5	3.3				42.5				94							
47											95							
48											96							
49	26.4					1.7	11.2	6.7			97	18.4						
50	194.7						9.9	74.3	86.6		98							
51	365.0						11.0	118.0	213.6		99							
52	142.5						10.6	29.3	99.7		100							
53	72.7						0.4	14.3	55.0		101							
54											102	17.0					18.9	
55	37.1				0.5						103	73.0					79.3	
56	17.5										104	35.0					41.1	
57	38.5			C ₄ H ₇							105	340.0					336.4	
58	8.0										106	740.0					740.0	
59	5.0		5.0								107	62.0					70.1	
60											108							
61	43.5						0.4	25.1	9.4		109							

A - Ethanol (CEC Card No. 312)
 B - 2-Propanol (CEC Card No. 326)
 C - C_n-C_m Saturated Hydrocarbon
 D - 2-Butanone (CEC Card No. 339)
 E - Benzene (CEC Card No. 212)
 F - Toluene (CEC Card No. 214)

G - Xylene (CEC Card No. 220)
 H - Water
 I - Nitrogen
 J - Oxygen
 K - Carbon Dioxide
 L - Argon
 } Atmospheric Contamination

Contrails

Table LIX

REPRESENTATIVE MASS SPECTRAL DATA
FOR 3615 GRAY XA-194

Peak No.	Spectrum of Mixture	Calculated Components						F, G, H, I, J	Mass No.	Spectrum of Mixture	Calculated Components					
		A	B	C	D	E	F, G, H, I, J				A	B	C	D	E	F, G, H, I, J
14	33.8				0.9	6.9	26.0	52	45.2	12.7	27.9					
15	82.0	14.5	8.7		0.8	11.3		53	102.0	34.8	60.4					
16	336.0				0.1	0.7	335.2	54	24.0	7.7	14.4					
17	255.9				0.3	1.2	254.4	55	46.0	43.7	88.6					
18	870.0				0.8	0.9	868.3	56	19.5	5.9	11.2					
19	10.0				0.5	3.0		57	11.2							
20	3.0						3.0	58	6.5							
21								59	32.0							
22	4.8						4.8	60	33.0							
23								61	39.0				0.2			
24								62	5.0				5.0			
25	6.8			0.2	0.4	2.5		63	5.0				0.2			
26	49.0	7.9	13.9	1.5	2.8	10.0		64	20.5	8.4	7.3					
27	67.5	52.1	34.4	4.8	8.5	23.8		65	14.0	8.2	4.7					
28	440.0	4.1		0.9	2.9	6.6	425.5	66	11.0	5.9	3.0					
29	120			7.3	7.9	25.7		67	87.0	71.7	8.1					
30	11.0			0.2	1.1	5.9		68	70.0	42.4						
31	141.0				45.7	95.3		69	44.0	40.2						
32	38.0				1.0	1.2	35.8	70	4.0	2.5						
33								71	6.5							
34								72	9.0							
35								73	22.0							
36	2.5							74	19.5							
37	29.5	4.6	15.7	0.2	0.5			75	34.5		4.1					
38	60.5	15.1	33.2	0.3	0.8			76	10.5		5.9					
39	270.0	88.0	127.7	0.7	2.4			77	7.0		3.7					
40	38.5	9.6	14.5	0.1	0.5		13.8	78								
41	139.5	12.9	13.9	0.5	3.0	1.0		79	37.8	11.3	27.4					
42	48.5			1.6	3.7	3.3		80	47.0	4.2	23.3					
43	190.0		11.9	31.1	1.7	8.2		81	1230.0	543.4	686.6					
44	2754.0		6.7	0.8	0.3	1.6	2744.6	82	470.0	40.5	473.1					
45	168.0		33.4	0.2	2.0	34.3	98.1	83	32.5		37.4					
46	46.4		23.7			14.8		84								
47								85	4.5							
48								86	4.0							
49	11.8	2.6						87	31.0							
50	90.9	33.7		0.2				88	8.0							
51	163.5	83.1						89	5.5							
52	59.0	38.8						90								
53	8.5	21.4						91								
54	7.2							92	7.0	7.4						
55	78.0			0.1				93	30.0	30.9						
56	57.5							94	15.0	16.0						
57	94.0				0.7			95	123.0	130.9						
58	6.5				0.2			96	288.0	288.0						
59	3.0				4.5			97								
60	3.0				3.0			98								
61	21.0	3.6	14.0					99								

A - Xylene (CEC Card No. 220)
 B - Toluene (CEC Card No. 214)
 C - Methyl Ethyl Ketone (CEC Card No. 339)
 D - 1-Propanol (CEC Card No. 325)
 E - Ethanol (CEC Card No. 312)

F - Water
 G - Nitrogen
 H - Oxygen
 I - Carbon Dioxide
 J - Argon
 } Atmospheric Contamination
 Sat. hydrocarbons also present

Table LX

**REPRESENTATIVE MASS SPECTRAL DATA
FOR SILVER MARKING INK NO. 1448 (WITH CRESYLIC ACID)**

Mass No.	Spectrum of Mixture	Calculated Components				Mass No.	Spectrum of Mixture	Calculated Components			
		A	B	C	D, E, F, G, H			A	B	C	D, E, F, G, H
14	109.8	3.3			106.5	62					
15	208.5	9.6				63					
16	201.0				201.0	64					
17	906.0				906.0	65					
18	3180.0				3180.0	66					
19	13.3	2.1				67					
20	9.0					68					
21						69					
22	9.8					70	5.9		8.4		
23						71					
24	1.5					72	197.4	9.4	173.1		
25	5.0					73	27.2		26.8		
26	9.0	4.3		0.7		74	14.0		12.4		
27	10.0	19.0		0.9		75					
28	526.0	5.3			520.7	76					
29	300.0	35.6	198.6			77					
30	18.0	2.4	17.3			78					
31	390.0	69.2	320.8			79					
32	32.3	1.8			30.5	80					
33	1.5	0.7				81					
34						82					
35						83					
36						84					
37						85					
38						86					
39	3.5					87	44.0		41.5		
40	12.0				12.0	88	33.9		28.5		
41	20.0	1.7	36.3			89	8.0		7.1		
42	44.8	2.0	49.9	0.8		90					
43	830.0	9.4	820.7	11.4		91					
44	725.0	2.6	9.6		712.8	92					
45	104.4	18.2	81.4			93					
46	6.3					94					
47						95					
48						96					
49						97					
50						98					
51						99					
52						100					
53						101					
54						102					
55						103					
56						104					
57	6.2					105					
58	17.3		14.2	3.1		106					
59	279.6	34.4	253.6			107					
60	11.3	1.3	11.8			108					
61	23.3	1.3	22.2			109					

A - 2-Ethoxyethanol (API Serial No. 1146)
 B - 2-Ethoxyethyl Acetate (MRC Specta)
 C - Acetone (CEC Card No. 318)

D - Water)
 E - Nitrogen)
 F - Oxygen) Atmospheric
 G - Carbon Dioxide) Contamination
 H - Argon)

Table LXI

REPRESENTATIVE MASS SPECTRAL DATA
FOR LATEX FOAM RUBBER

Mass No.	Spectrum of Mixture	Calculated Components					Mass No.	Spectrum of Mixture	Calculated Components					
		A	B	C, D, E, F, G					A	B				
14							62							
15							63							
16	325.			325			64							
17	1194			1194			65							
18	4640			4640			66							
19	7.0						67							
20	9.7						68							
21							69							
22	6.5						70							
23							71							
24							72							
25							73							
26							74							
27							75							
28	165	2.8		263			76	3.5		3.5				
29	4						77							
30	2.5	1.7					78							
31	5.0	0.5					79							
32	32.8	19.9		13			80							
33							81							
34							82*							
35							83							
36							84							
37							85							
38							86							
39							87							
40	3.0			3.0			88							
41							89							
42							90							
43	4.0						91							
44	365			365			92							
45	5.0			3.6			93							
46							94							
47							95							
48							96							
49							97							
50							98							
51							99							
52							100							
53							101							
54							102							
55							103							
56							104							
57							105							
58							106							
59							107							
60	33.9	33.9					108							
61							109							

A - Carbonyl Sulfide (API Serial No. 174)
 B - Carbon Disulfide (API Serial No. 92)
 C - Water)
 D - Oxygen)
 E - Nitrogen) Atmospheric
 F - Carbon Dioxide) Contamination
 G - Argon)

Table LXII

MASS SPECTRAL DATA FOR LATEX FOAM RUBBER PRODUCTS REMOVED WHILE HEATING UNDER VACUUM

Mass No.	Spectrum of Mixture	Calculated Components				Mass No.	Spectrum of Mixture	Calculated Components			
		A	B	C, D, E, F, G				A	B		
14	41.4			35.9		62	90.6	89.3			
15	82.4					63	2.2				
16	369.0	25		365		64	9.0		8.8		
17	873.0			870		65					
18	2850			2873		66					
19	5.3					67					
20	6.0					68					
21						69					
22	41.1	0.8		33.1		70					
23						71					
24						72					
25	7.1					73					
26	35.1					74					
27	70.3					75					
28	597.0	163		434		76	627.0		627		
29	67.0	1.9				77	13.8		16.3		
30	159.0	2.0				78	68.9		53.9		
31	15.1	4.0				79					
32	1482.0	1137	134.8	210		80					
33	12.3	1.0	1.2			81					
34	67.0	50.5	5.6	1.0		82					
35						83					
36	4.1					84					
37	5.0					85					
38	50.6					86					
39	32.4					87					
40	11.4					88					
41	46.2					89					
42	39.5					90					
43	225.9					91					
44	1950.0	58	111.6	1789		92					
45	32.3	1.0	1.9	20.4		93					
46	16.1	2.9	5.0	7.5		94					
47	4.1					95					
48	3.5	1.9				96					
49						97					
50						98					
51						99					
52						100					
53						101					
54						102					
55	13.0					103					
56	21.0					104					
57	27.3					105					
58	40.0					106					
59	1.6					107					
60	1941.0	1941				108					
61	40.4	33.0				109					

A - Carbonyl Sulfide (API Serial No. 174)
 B - Carbon Disulfide (API Serial No. 92)

C - Water)
 D - Nitrogen)
 E - Oxygen) Atmospheric
 F - Carbon Dioxide) Contaminants
 G - Argon)

NOTE: Since these components are not products of a scheduled Gas Off Study, no attempt has been made to account for many of the lines.

Table LXIII

REPRESENTATIVE MASS SPECTRAL DATA
FOR LOCKFOAM C-605 (R&T)

Mass No.	Spectrum of Mixture	Calculated Components				Mass No.	Spectrum of Mixture	Calculated Components			
		A	B, C, D, E								
14	6.0		5.9			62					
15	1.2					63					
16	1120	1068	28.3			64					
17	184		184			65					
18	625		625			66					
19	1.0					67					
20	2.0		1.0			68					
21	-					69					
22	177.6	171				70					
23	2.0					71					
24						72					
25						73					
26						74					
27						75					
28	990	956	40			76					
29	10	9.0				77					
30						78					
31						79					
32	11.3		11.3			80					
33						81					
34						82					
35						83					
36						84					
37						85					
38						86					
39						87					
40	9.0		9.0			88					
41						89					
42						90					
43						91					
44	9230	9230				92					
45	109.2	105				93					
46	30.3	33				94					
47						95					
48						96					
49						97					
50						98					
51						99					
52						100					
53						101					
54						102					
55						103					
56						104					
57						105					
58						106					
59						107					
60						108					
61						109					

A - Carbon Dioxide (CEC Card No. 423)
 B - Water
 C - Nitrogen
 D - Oxygen
 E - Argon

} Atmospheric Contamination

NOTE: CO₂ is greatly in excess of that normally present in the atmosphere.

Table LXIV

REPRESENTATIVE MASS SPECTRAL DATA
FOR LOCKFOAM E-302 (R&T)

Mass No.	Spectrum of Mixture	Calculated Components				Mass No.	Spectrum of Mixture	Calculated Components			
		A	B, C, D, E, F					A			
14						62					
15						63					
16	820		820			64					
17	261		261			65					
18	898		898			66	252	244			
19	15.2	15				67					
20	10.8					68	80.3	78.7			
21						69					
22	44					70	11.0	10.5			
23						71					
24						72	7.2	7.0			
25						73					
26						74					
27	6.8					75					
28	85.5		85.5			76					
29	15.9					77					
30						78					
31	261	154.5				79					
32	19		19			80					
33						81					
34						82	68.5	68.0			
35	286	268				83					
36	40	33.3				84	44	44.2			
37	80	79.3				85					
38						86	7.3	7.2			
39						87					
40	10.5		10.5			88					
41	14.5					89					
42	9.0					90					
43	16.8	10.8				91					
44	7410	10.9	7410			92					
45	87		74			93					
46	31					94					
47	228.6	202				95					
48						96					
49	72	65				97					
50	33	32.1				98					
51	21.0	16.6				99					
52						100					
53						101	1500	1500			
54						102					
55						103	955	960			
56						104					
57						105	154.5	150			
58											
59						117	34.5	27.5			
60						119	33.1	26.4			
61						121	10.8	8.5			

A - Trichlorofluoromethane (Freon -11) (API Serial No. 1641)
 B - Carbon Dioxide)
 C - Water)
 D - Nitrogen)) Atmospheric
 E - Oxygen)) Contaminants
 F - Argon))

Table LXV

REPRESENTATIVE MASS SPECTRAL DATA FOR FLUOROLUBE OIL GRADE FS-5

Mass No.	Spectrum of Mixture	Calculated Components				Mass No.	Spectrum of Mixture	Calculated Components			
		A		B, C, D, E, F				A			
14	28.1			28.1	62	3.8					
15	2.2				63						
16	183.0			183.0	64						
17	835.0			835.0	65						
18	2844.0			2844.0	66	28.9	CC ₁ F				
19	5.7				67	2.7		C ₂ ₃₅	C ₂ ₃₇		
20	8.4				68	9.3	CC ₁ F				
21					69	140.1	CF ₃				
22	8.4			8.4	70	2.1					
23					71	1.8					
24	0.5				72						
25	0.4				73						
26	1.5				74	9.0					
27	6.1				75	0.9					
28	247.6			247.6	76						
29	8.4				77	0.6					
30	0.9				78	3.8					
31	103.5	CF			79	0.8					
32	121.5			121.5	80	1.1					
33					81	3.3					
34	0.5				82	6.0					
35	18.1				83	3.2					
36	4.2				84	3.8					
37	5.7				85	435.0	CF ₂ C ₂				
38	1.6				86	6.0		C ₂ ₃₅	C ₂ ₃₇		
39	2.6				87	138.6	CF ₂ C ₂				
40	6.6			6.6	88	1.5					
41	4.5				89	0.5					
42	1.8				90	2.9					
43	14.8				91						
44	458.0			458.0	92	1.1					
45	6.1				93	27.8	C ₃ F ₃				
46	2.1				94	1.5					
47	20.0				95						
48	0.9				96	0.8					
49	6.6				97	4.9					
50	10.7				98	0.6					
51	2.1				99	1.6					
52					100	13.1					
53					101	348.0					
54					102	3.4	CC ₂ F				
55	5.7				103	219.9					
56	0.6				104	2.3	CC ₂ F	C ₂ ₃₅	C ₂ ₃₇		
57	1.8				105	35.7					
58	1.9				106	0.6	CC ₂ F				
59	0.9				107						
60					108						
61	0.7				109	17.8	C ₃ C ₂ F ₂	C ₂ ₃₅			

A - Ionic Species Corresponding to Mass Spectral Lines
 B - Water)
 C - Nitrogen)
 D - Oxygen) Atmospheric Contamination
 E - Carbon Dioxide)
 F - Argon)

Table LXV - Cont'd

Mass No.	Spectrum of Mixture	Calculated Components				Mass No.	Spectrum of Mixture	Calculated Components			
		A						A			
110	0.7					179	4.3				
111	5.8	$C_2C_2F_3$	Cl_{37}			180	0.6				
112	5.1					181	5.6				
113	1.9					182	1.2				
115	1.0					183	1.6				
116	68.3	$C_2C_2F_3$				184	0.7				
117	4.9		Cl_{35}	Cl_{37}		185	32.0	$C_3C_2F_6$			
118	22.2	$C_2C_2F_3$				186	1.5		Cl_{35}	Cl_{37}	
119	18.3					187	10.6	$C_3C_2F_6$			
121	1.1					193	1.2				
124	2.3					197	4.3				
125	2.1					198	1.1				
127	1.5					199	2.6				
128	1.1					200	1.9				
129	1.2					201	33.0	$C_3C_2F_5$			
130	0.7					202	3.2		Cl_{35}	Cl_{37}	
131	33.0	C_3F_5				203	21.0	$C_3C_2F_5$			
132	11.9					204	1.2				
133	0.9					205	3.8				
134	6.9					209	1.0				
135	84.0	$C_2C_2F_4$				213	3.8				
136	3.0		Cl_{35}	Cl_{37}		215	2.3				
137	27.4	$C_2C_2F_4$				216	0.7				
138	0.7					217	8.1				
140	0.9					219	7.7				
141	0.6					221	2.4				
142	0.7					229	2.8				
143	2.8					231	3.1				
147	15.8	$C_3C_2F_4$				232	0.5				
148	2.5		Cl_{35}	Cl_{37}		233	1.4				
149	17.0	$C_3C_2F_4$				235	1.8				
150	1.8					237	0.6				
151	14.8	$C_2C_2F_3$				243	0.6				
152	1.4		Cl_{35}	Cl_{37}		247	1.0				
153	31.8	$C_2C_2F_3$				251	1.5				
154	0.8					253	1.1				
155	5.9					259	0.4				
159	1.5					263	0.8				
161	0.9					265	0.5				
163	18.7	$C_3C_2F_3$				267	1.1				
164	1.1		Cl_{35}	Cl_{37}		269	1.0				
165	11.8	$C_3C_2F_3$				285	0.6				
166	1.9					293	0.8				
167	4.9										
168	0.8										
169	5.9										
171	1.1										
178	1.4										

A - Ionic Species Corresponding to Mass Spectral Lines

Table LXVI

REPRESENTATIVE MASS SPECTRAL DATA
FOR FLUOROLUBE GREASE GRADE GR-544, TYPE LG

Mass No.	Spectrum of Mixture	Calculated Components					Mass No.	Spectrum of Mixture	Calculated Components				
		A	B	C	D	E			A	B	C	D	
14	21.0					21.0	62						
15	24.6						63						
16	159.0					159.0	64						
17	1110.0					1110.0	65						
18	3850.0					3850.0	66	0.7				CClF	
19	9.0						67	0.4				CCl ₃ Cl ₃	
20							68	0.3				CClF	
21	1.0						69	7.2				CF ₃	
22							70						
23							71						
24							72	1.8					
25	2.0	0.7					73	2.0					
26	18.0	9.0					74	1.2					
27	99.0	71.3					75						
28	157.5	23.3				134.2	76	1.4					
29	67.5	43.1					77	0.8			0.7		
30	5.5	3.2					78	4.2			4.2		
31	196.8	141.4				CF	79						
32	40.4	2.2					80						
33	11.5	11.4					81						
34							82						
35							83	3.4					
36							84						
37	4.5	2.0					85	12.7				CF ₂ Cl	
38	7.5	3.7					86					CF ₂ Cl	Cl ₃ Cl ₃
39	35.3	22.5			0.6		87	3.8					
40	11.8	5.5				6.3	88						
41	102.0	87.2					89						
42	52.0	44.4					90						
43	108.0	85.0					91	0.7		0.7			
44	58.0	5.9				52.1	92						
45	17.3	9.2					93	0.9				C ₃ F ₃	
46	1.5	0.6					94						
47	2.0						95						
48	0.8						96						
49	1.5						97						
50	3.5	1.1			0.8		98						
51	2.5	1.0			0.9		99						
52	1.5	0.3			0.9		100						
53	2.5	1.4					101	7.2				CCl ₂ F	
54	1.5	1.3					102						
55	18.4	16.4					103	3.6				CCl ₂ F	Cl ₃₅ Cl ₃₇
56	114.3	114.0					104						
57	10.5	8.1					105	0.7				CCl ₂ F	
58	2.2						106						
59	5.8						107						
60	6.0						108						
61							109						

A - 1-Butanol (CEC Card No. 346)
 B - Toluene (CEC Card No. 214)
 C - Benzene (CEC Card No. 212)
 D - Ionic Species Corresponding to Mass Spectral Lines

E - Water)
 F - Nitrogen)
 G - Oxygen) Atmospheric
 H - Carbon Dioxide) Contamination
 I - Argon)

Contrails

Table LXVI- Cont'd

Mass No.	Spectrum of Mixture	Calculated Components				Mass No.	Spectrum of Mixture	Calculated Components					
				D									
116	1.6			C_2CF_3									
117	0.5				$CL_{35}CL_{37}$								
118	0.6			C_2CF_3									
119	1.2												
131	2.0			C_3F_5									
132	0.4												
135	2.6			C_2CF_4	$CL_{35}CL_{37}$								
137	0.8			C_2CF_4									
147	1.8			C_3CF_4	$CL_{35}CL_{37}$								
149	0.6			C_3CF_4									
151	0.7			C_2CF_3	$CL_{35}CL_{37}$								
153	0.6			C_2CF_3									
185	0.8			C_3CF_6	$CL_{35}CL_{37}$								
187	0.2			C_3CF_6									

D - Ionic Species Corresponding to Mass Spectral Lines

Table LXVII

REPRESENTATIVE MASS SPECTRAL DATA FOR SILICONE FLUID NO. 200

Mass No.	Spectrum of Mixture	Calculated Components						Mass No.	Spectrum of Mixture	Calculated Components			
		A	B	C	D	E	F, G, H, I, J			A	B	C	D
14	8.5					0.9	7.6	62	7.8			2.6	4.1
15	12.2		1.7	3.0	1.3	1.5		63	15.5			7.1	8.8
16	340.0						340.0	64	3.3			1.6	2.1
17	1695.0					0.2	1694.8	65	21.5			8.7	12.9
18	5800.0						5800.0	66	4.0			1.2	1.6
19	10.3					0.4		67					
20	12.0							68					
21								69	3.0				
22	19.0							70	4.0				
23								71	4.0				
24								72					
25								73	6.0	5.8			
26	6.9			1.6	2.0	1.3		74	5.1	1.4			1.1
27	28.5		3.1	10.7	5.0	3.1		75	28.5	0.8	25.3	1.7	0.7
28	188.4		0.9	0.8		0.9	185.8	76	4.5		1.6	1.2	0.4
29	15.0		0.7			3.4		77	18.0		0.9	14.7	1.2
30	2.0					0.8		78	11.3			8.7	
31	12.5					12.5		79	8.8			8.2	
32	10.5					0.2	10.3	80					
33								81					
34								82					
35								83	4.0				
36								84					
37	4.7			0.9	2.3			85	3.1				0.6
38	9.4			3.1	4.8			86					
39	41.9			18.0	18.6			87					
40	10.9			2.0	2.1		6.8	88					
41	12.9			2.6	2.0	0.1		89	6.9			2.3	4.0
42	6.9					0.4		90	6.8			0.9	3.4
43	23.0		1.1		1.7	1.1		91	211.5			111.3	100.2
44	1104.0				1.0	0.2	1102.8	92	61.0			8.3	69.0
45	35.0		6.2		4.9	4.5		93	4.8				5.5
46	8.5				3.5	1.9							
47	4.2		3.2					103	7.2			6.3	
48								104	3.0	0.2		3.3	
49								105	28.0			26.8	
50	15.3			6.9	6.0			106	59.0			59.0	
51	28.0			17.0	9.6			107	4.0			5.6	
52	10.0			7.9	2.4			133	4.5	1.1			
53	6.8			4.4	1.2			147	7.5	1.7			
54								149	4.0				
55	8.0							191	3.0	0.7			
56	6.5							207	35.0	2.0			
57	8.0							208	7.5	0.4			
58								209	4.5	0.2			
59	3.2	0.6	0.7					281	6.0	6.0			
60													
61	5.0		0.7	0.7	2.0								

A - Silicone Oil (See Text, Results & Discussion)
 B - Trimethyl Silanol (MRC Spectra)
 C - Xylene (CEC Card No. 220)
 D - Toluene (CEC Card No. 214)
 E - Ethanol (CEC Card No. 312)

F - Water
 G - Nitrogen
 H - Oxygen
 I - Carbon Dioxide
 J - Argon

} Atmospheric Contamination

Table LXVIII
 REPRESENTATIVE MASS SPECTRAL DATA
 FOR SILICONE FLUID F-50

Peak No.	Spectrum of Mixture	Calculated Components					F ₁ G ₂ H ₁ J	Peak No.	Spectrum of Mixture	Calculated Components					F ₁ G ₂ H ₁ J
		A	B	C	D	E				A	B	C	D	E	
14	13.0		8.0			0.2	4.8	62	1.6		1.1				
15	45.7		36.7			0.4		63	2.0		0.5	0.3	0.5		
16	332.0		2.4				329.6	64							
17	807.0		1.1				805.9	65	1.8			0.4	0.7		
18	2754.0						2754.0	66	9.8						
19	5.0							67	2.0						
20	6.0							68							
21								69	1.5						
22	37.1						37.1	70	2.5		0.7				
23								71	3.6		0.7				
24								72	4.0		2.2				
25	1.9		0.5					73	34.0	X	7.3				
26	10.4		3.5			0.4		74	7.5	X	5.2				
27	25.3		7.6	0.5	0.3	0.8		75	535.0	X	535.0				
28	310.0		19.7			0.2	290.1	76	38.2		34.5				
29	34.7		14.2			0.9		77	22.5		19.5	0.6			
30	8.2		2.8			0.2		78	3.7		0.5				
31	8.5		5.1			3.4		79							
32	10.3						10.3	80							
33								81							
34								82							
35								83							
36								84							
37	1.7							85	3.2						
38	2.7				0.3			86							
39	11.0		1.1	0.8	1.1			87	1.5						
40	5.0		0.7				4.3	88							
41	21.9		3.5					89	1.0				0.2		
42	17.9		7.5			0.1		90	2.8				0.2		
43	55.8		23.8			0.3		91	10.4			4.7	5.7		
44	2241.0		5.2				2235.8	92	5.2			0.4	3.9		
45	171.0		130.8		0.3	1.2		103	1.6			0.3			
46	20.2		10.1			0.5		105	1.8			1.1			
47	70.9		67.2					106	2.5			2.5			
48	3.5		3.4					129	2.8						
49	3.2		2.2	2.6				131	3.9						
50	2.8			0.3	0.3			132	2.9						
51	3.8			0.7	0.5			133	4.2						
52	4.9			0.3				147	65.3	X					
53	4.9		3.3					148	10.6						
54								149	9.8						
55	6.5		0.8					150	1.0						
56	14.0		1.6					207	4.7	X					
57	20.4		2.9					221	3.7	X					
58	4.7		1.5					281	9.0	X					
59	22.2	X	15.5					282	2.7	X					
60	9.0		8.2					283	1.8	X					
61	16.0		14.2												

A - Silicone Oil Types A & C (See text, Results & Discussion)
 B - Trimethyl Silanol (MRC Spectra)
 C - Xylene (CEC Card No. 220)
 D - Toluene (CEC Card No. 214)
 E - Ethanol (CEC Card No. 312)

F - Water
 G - Nitrogen
 H - Oxygen
 I - Carbon Dioxide
 J - Argon
 } Atmospheric Contamination

Contrails

Table LXIX

REPRESENTATIVE MASS SPECTRAL DATA FOR SILICONE GREASE G-300

Mass No.	Spectrum of Mixture	Calculated Components					F, G, H, I, J	Mass No.	Spectrum of Mixture	Calculated Components		
		A	B	C	D	E				A	B	C
14	93.0		0.5	50.0	2.8	23.7	6.0	138.0		127.8	7.0	
15	375.0			228.8	2.4	38.5		61	13.6	2.8	3.3	
16	1719.0		0.1	15.0	0.4	2.4	1701.1	64	2.0		0.3	
17	5790.0			7.0	1.1	4.0	5777.9	65	27.2	16.7	1.7	
18	19,660		0.4		2.4	3.1	19,654	66	45.2	16.1	1.7	
19	74.0				1.5	10.3		67	42.0	5.2	1.3	
20	42.1							68	5.0	0.8	1.0	
21								69	8.2	0.4	2.3	
22	154.5						154.5	70	10.0	6.1	4.7	
23								71	7.1	3.7	4.7	
24	64.0		63.1	0.7		1.8		72	22.7		13.7	
25	216.6		196.7	3.3	1.3	8.4		73	216.3	376.3	0.4	
26	78.9		4.9	22.0	8.3	34.0		74	52.7	94.1	0.6	
27	189.3		0.4	47.4	25.7	80.9		75	3390.0	54.9	3335.1	
28	1242.0		1.8	123.1	8.7	22.7	1085.7	76	240.0		214.8	
29	264.6			88.4	23.8	87.8		77	132.0		121.4	
30	54.0		1.6	17.3	3.3	20.0		78	6.5		3.3	
31	496.0		0.5	31.7	138.3	325.5		79	2.8		1.0	
32	16.9		0.4		3.1	4.0	9.4	80				
33	2.0			1.0	1.5			81	3.7		0.7	
34								82	20.6	20.1	0.7	
35	203.1		219.9	0.3				83	11.1	9.3	2.3	
36	27.4		21.6	1.3				84	15.1	13.1	2.0	
37	68.9		68.2	1.7	1.6			85	69.4	6.0	0.7	
38	17.7		7.1	2.3	2.3			86	6.5	2.3		
39	31.0			7.0	7.2			87	29.0	1.1		
40	23.1			4.3	1.4		17.4	88	4.0			
41	44.0		0.7	22.0	9.1	3.5		89	15.5			
42	80.4		0.4	47.0	11.1	11.3		90	16.5			
43	313.0			148.1	5.1	28.0		91	68.2			
44	9120.0			32.4	1.0	5.5	9081.1	92	46.0			
45	1200.0			815.4	6.1	117.3		93	4.0			
46	168.9			63.0		50.6		94	64.0	68.6		
47	604.0		139.6	418.9				95	707.0	707.0		
48	63.0		43.0	21.0				96	70.6	27.4	59.7	
49	64.2		45.7	14.0				97	452.0	455.0		
50	28.0		13.6	1.0				98	17.0	17.0		
51	16.8		0.4	1.0				99	73.8	73.2		
52	15.9			2.7				100	6.0	2.3		
53	28.9			20.7				101	10.0	0.8		
54	6.7			5.0				102	1.5	0.1		
55	22.6			16.0				103	81.3			
56	16.3			10.0				104	11.5			
57	32.8			18.3	2.0			105	12.8			
58	33.6			9.3	0.5			106	5.0			
59	220.8	39.2	71.4	96.7	13.5			107	1.8			
60	449.0		399.1	51.4	9.1			108	1.0			
61	164.4		31.9	88.7				109	1.2			

A - Silicone Oil (See Text, Results & Discussion)
 B - Trichloroethylene (MRC Spectra)
 C - Trimethyl Silanol (MRC Spectra)
 D - 1-Propanol (CEC Card No. 325)
 E - Ethanol (CEC Card No. 312)

F - Water
 G - Nitrogen
 H - Oxygen
 I - Carbon Dioxide
 J - Argon

} Atmospheric Contamination

Contrails

Table LXIX - Cont'd

No.	Spectrum of Mixture	Calculated Components				Mole No.	Spectrum of Mixture	Calculated Components			
		A	B								
119	15.2										
125	12.1	19.6									
130	620.0		701.8								
131	22.1		18.2								
132	589.0		672.6								
133	142.5	70.6	15.8								
134	198.0		215.0								
135	43.8		6.4								
136	22.0		22.8								
137	10.8		0.7								
147	161.1	113.7									
148	27.7										
149	181.2										
150	26.4										
151	15.9										
177	15.0										
191	31.0	43.0									
193	24.0	47.0									
207	116.4	129.4									
249	16.2	23.5									
251	11.1	25.5									
265	22.3	27.4									
267	26.7	113.7									
281	392.0	392.0									
282	111.6	109.8									
283	68.5	70.6									

A - Silicone Oil (See Text, Results & Discussion)
 B - Trichloroethylene (MRC Spectra)

Contrails

Table LXX

REPRESENTATIVE MASS SPECTRAL DATA
FOR SILICONE RELEASE AGENT DC-7

Mass No.	Spectrum of Mixture	Calculated Components				Mass No.	Spectrum of Mixture	Calculated Components			
		A	B	C	D, E, F, G, H			A	B	C	D, E, F, G, H
14	46.8	20.6	3.9		22.3	62					
15	50.6	33.5	9.5			63					
16	213.0	2.1	1.4		209.5	64					
17	1020.0	3.5			1016.5	65					
18	3240.0	2.7			3237.3	66					
19	13.5	9.0				67					
20	8.4				8.4	68					
21						69					
22	8.6				8.6	70					
23						71					
24	1.5		0.4			72					
25	7.4	1.6	1.2			73	3.6		25.8		
26	30.2	7.3	2.2			74	0.7		6.5		
27	70.9	70.4	1.1			75	5.2		3.8		
28	202.5	19.7	0.9		181.9	76					
29	89.0	76.5	22.5			77					
30	18.6	17.5	0.3			78					
31	283.5	283.5				79					
32	43.9	3.5			40.4	80					
33						81					
34						82					
35						83					
36	1.6					84					
37						85					
38	1.0					86					
39	2.0					87					
40	8.1		0.2		7.9	88					
41	6.2	3.0	0.9			89					
42	13.7	9.9	2.1			90					
43	36.8	24.4	6.0			91					
44	505.0	4.8	10.1		490.1						
45	110.1	102.1	0.3								
46	40.1	44.1				96	8.0		1.9		
47	2.0					119	1.5				
48						125	0.6		1.3		
49						133	6.0		4.8		
50						147	2.5		7.8		
51						177	2.4				
52						191	4.8		3.0		
53						193	2.6		3.2		
54						207	43.5		8.9		
55						208	9.2		1.9		
56						209	5.6		1.1		
57						249	1.0		1.6		
58						265	1.4		1.9		
59	1.4			2.7		281	26.9		26.9		
60						282	7.2		7.5		
61						283	4.3		4.8		

- A - Ethanol (CEC Card No. 312)
 - B - Acetaldehyde (CEC Card No. 308)
 - C - Silicone Oil (See Text, Results & Discussion)
 - D - Water
 - E - Nitrogen
 - F - Oxygen
 - G - Carbon Dioxide
 - H - Argon
- } Atmospheric Contamination

Table LXXI

**REPRESENTATIVE MASS SPECTRAL DATA
FOR DC-4 (MIL-I-8660)**

Mass No.	Spectrum of Mixture	Calculated Components					Mass No.	Spectrum of Mixture	Calculated Components				
		A	B	C	D	E, F, G, H, I			A	B	C	D	E, F, G, H, I
14	27.7	12.5				15.2	62						
15	28.2	20.3					63	1.1					
16	237.0	1.3				235.7	64						
17	1437.0	2.1				1434.9	65						
18	5000.0	1.6				4998.4	66	0.8					
19	14.0	5.4					67						
20	12.8					12.8	68						
21							69						
22	6.5						70						
23							71						
24	1.6	1.0					72						
25	5.0	4.4					73	3.1			21.0		
26	20.6	17.9					74	1.6			5.3		
27	45.7	42.6					75	8.5		5.4	3.1		
28	51.8	11.9				39.9	76	2.0					
29	57.1	46.3					77	3.6					
30	12.1	10.6					78	5.0					
31	171.6	171.6					79	1.6					
32	48.6	2.1				46.5	80						
33							81						
34							82						
35							83						
36	2.7						84						
37	1.3						85						
38	2.3						86						
39	4.2						87						
40	8.6					8.6	88						
41	3.8	1.8					89						
42	7.9	6.0					90						
43	21.8	14.8			C ₃ H ₇								
44	372.0	2.9				369.1	96	4.7			1.5		
45	70.4	61.8	1.3				119	1.0					
46	25.4	26.7					125	0.7			1.1		
47	2.0		0.7				133	4.1			3.9		
48							147	3.3			6.4		
49							177	1.4					
50	4.3						191	3.2			2.4		
51	4.8						193	2.0			2.6		
52	4.7						207	25.2			7.2		
53							208	5.4			1.5		
54							209	3.2			0.9		
55	0.7						249	1.0			1.3		
56	0.4						265	1.2			1.5		
57	0.5				C ₄ H ₉		281	21.9			21.9		
58	0.9				C ₄ H ₁₀		282	5.7			3.5		
59	1.3				2.2		283	3.8			2.6		
60													
61	1.5												

A - Ethanol (CEC Card No. 312)	E - Water)
B - Trimethyl Silanol (MRC Spectra)	F - Nitrogen)
C - Silicone Oil (See Text, Results & Discussion)	G - Oxygen) Atmospheric
D - C ₄₋₅ Hydrocarbons	H - Carbon Dioxide) Contamination
	I - Argon)

Table LXXII

REPRESENTATIVE MASS SPECTRAL DATA
FOR WAX LUBRICANT NO. 111

Peak No.	Spectrum of Mixture	Calculated Components				Peak No.	Spectrum of Mixture	Calculated Components			
		A	B, C, D, E					A			
1	6.2					62					
2	4.0					63	0.5				
3	289		289			64					
4	2025		2026			65	1.0				
5	7180		7180			66					
6	13					67	3.0				
7	15.6					68	2.0				
8						69	12.8	C ₅ H ₉			
9						70	11.8	C ₅ H ₁₀			
10	2.4					71	28.7	C ₅ H ₁₁			
11						72	2.0				
12						73					
13	1.6					74					
14	26.3	C ₂ H ₃				75					
15	66	C ₂ H ₄	66			76					
16	30.2	C ₂ H ₅				77	1.5				
17						78					
18						79					
19	20		20			80					
20						81	3.0				
21						82	2.9				
22						83	25.5	C ₆ H ₁₃			
23						84	6.5				
24						85	26.1	C ₆ H ₁₃			
25						86	1.3				
26	15.3					87	2.5				
27	6.4		6.4			88					
28	42.5	C ₃ H ₅				89					
29	11.7	C ₃ H ₆				90					
30	68.9	C ₃ H ₇				91					
31	137.7		137			92					
32	2.2					93					
33						94					
34						95	2.6				
35	7.9					96	2.0				
36	3.3					97	5.0	C ₇ H ₁₃			
37	2.8					98	5.5	C ₇ H ₁₄			
38	2.0					99	4.5	C ₇ H ₁₅			
39						100	0.8				
40	3.9					101	2.0				
41	1.9					102					
42	22.6	C ₄ H ₇				103					
43	20.0	C ₄ H ₈				104					
44	72.7	C ₄ H ₉				105					
45	3.8					106					
46						107					
47						108					
48						109					

A - Petroleum Ether
 B - Carbon Dioxide)
 C - Argon) Atmospheric
 D - Oxygen) Contaminants
 E - Nitrogen)

Table LXXIII

REPRESENTATIVE MASS SPECTRAL DATA
FOR SILASTIC RTV 882

Mass No.	Spectrum of Mixture	Calculated Components					Mass No.	Spectrum of Mixture	Calculated Components					
		A	B	C	D, E, F, G				A	B	C	D, E, F, G		
14	105.3	62.5			42.8		72	26.4						
15	268.8	55.0			213.8		73	24.8			24.8			
16	825.0	9.1			815.9									
17	478.0	23.9			454.1		91	14.7		14.7				
18	1617.0	54.0			1563.0		92	8.9		10.1				
19	38.2	33.9												
20							96	27.0			27.0			
21														
22	123.0				123.0		133	24.3			24.3			
23														
24							191	18.7			18.7			
25	40.3	28.9												
26	235.5	189.0					207	152.4			152.4			
27	724.0	583.4					208	32.4			32.4			
28	1107.0	198.1			908.9		209	18.8			18.8			
29	858.0	539.8												
30	87.6	75.7					281	131.7			131.7			
31	3140.0	3140.0					282	35.9			35.9			
32	90.4	70.3			20.1		283	22.3			22.3			
33	33.1	33.6												
34														
35														
36														
37	41.2	36.4												
38	59.0	51.8												
39	195.9	163.9	2.6											
40	44.0	32.0												
41	270.0	206.9												
42	288.0	252.8												
43	247.8	116.5												
44	7600.0	23.2			7576.8									
45	269.0	138.2			130.8									
46	34.3				34.3									
47														
48														
49														
50														
51														
52														
53	11.7													
54														
55	21.4													
56														
57	68.2	46.2												
58	66.2	10.4												
59	317.0	306.5												
60	174.0	206.0												
61	10.2													

A - 1-Propanol (CEC Card No. 325)
 B - Toluene (CEC Card No. 214)
 C - Silicone Oil (See text)

D - Water)
 E - Nitrogen) Atmospheric
 F - Oxygen) Contamination
 G - Carbon Dioxide)

Contrails

Table LXXIV

**REPRESENTATIVE MASS SPECTRAL DATA
FOR SILASTIC RTV 731**

Pass No.	Spectrum of Mixture	Calculated Components				Mass No.	Spectrum of Mixture	Calculated Components			
		A	B	C, D, E, F, G				A	B	C, D, E, F, G	
14	84.6	81.0		3.6		62					
15	189.0	207.5	0.5			63					
16	175.5	29.0		146.5		64					
17	1134.0	19.5		1114.5		65					
18	2860.0	30.0		3860.0		66					
19	7.5	0.5				67					
20	10.0					68					
21						69					
22						70					
23						71					
24	3.1	2.5				72					
25	7.2	6.2				73					
26	7.3	5.4				74					
27	9.4	1.4				75	8.0		8.0		
28	97.2	20.8		76.4		76					
29	74.8	61.0				77					
30	5.3	2.9				78					
31	24.3	18.4				79					
32	25.0	0.4		24.6		80					
33						81					
34						82					
35						83					
36	4.5	0.3				84					
37						85					
38						86					
39	5.0	0.3				87					
40	9.3	5.1		4.2		88					
41	25.0	17.8				89					
42	63.5	57.7				90					
43	370.0	370.0				91					
44	34.5	18.2		16.3		92					
45	365.0	334.0	2.0			93					
46	5.0	4.0				94					
47	3.0	1.4	1.0			95					
48						96					
49						97					
50						98					
51						99					
52						100					
53						101					
54						102					
55						103					
56						104					
57						105					
58						106					
59						107					
60	174.9	190.9				108					
61	4.6	4.3				109					

A - Acetic Acid (API Serial No. 1451)
 B - Trimethyl Silanol (MRC Spectra)
 C - Water)
 D - Nitrogen)
 E - Oxygen) Atmospheric
 F - Carbon Dioxide) Contamination
 G - Argon)

Table LXXV

REPRESENTATIVE MASS SPECTRAL DATA
FOR SEALANT RTV 90

Mass No.	Spectrum of Mixture	Calculated Components					Mass No.	Spectrum of Mixture	Calculated Components				
		A	B	C	D,E				A	B	C		
14	745	742					62						
15	1215	1206					63	1.0					
16	156	74			83		64						
17	698	123			586		65						
18	2080	94			1990		66						
19	340	323					67	1.0					
20	7.0						68	1.0					
21	3.0						69	2.2	C ₅ H ₉				
22	3.0				2.3		70	2.0	C ₅ H ₁₀				
23							71	3.0	C ₅ H ₁₁				
24	50.0	57					72						
25	255	263					73	11.0			13		
26	1044	1065					74						
27	2550	2533					75						
28	710	710			13		76						
29	2721	2750					77						
30	638	631					78						
31	10,000	10,058					79						
32	129	125					80						
33	24						81						
34							82						
35							83						
36							84						
37							85						
38							86						
39	3.0						87						
40	33.0						88						
41	112.5	109					89						
42	355.	355					90						
43	887	877					91						
44	298	171			127		92						
45	3800	3675			1.5		93						
46	1455	1585					94						
47	52.8						95						
48	4.2						96						
49	2.5						97						
50	1.0						98						
51	2.0						99						
52	2.0						100						
53	1.0												
54													
55	3.5												
56	2.6		C ₄ H ₈										
57	6.0		C ₄ H ₉										
58							281	13.8			13.8		
59							282	4.0			3.5		
60							283	2.5			2.5		
61													

A - Ethanol (CEC Card No. 312)
 B - C₅₋₆ Hydrocarbon
 C - Silicone Oil (See Text, Results & Discussion)
 D - Water)
 E - Carbon Dioxide) Atmospheric Contaminants

Table LXXVI

REPRESENTATIVE MASS SPECTRAL DATA
FOR SILASTIC RTV 501

Mass No.	Spectrum of Mixture	Calculated Components				Mass No.	Spectrum of Mixture	Calculated Components			
		A	B	C	D, E, F, G, H						
14	240	198.7			41.3	62					
15	177	174.7				63					
16	55.5	29.0			26.5	64					
17	211.5	75.9			135.6	65					
18	640	171.7			468.3	66					
19	119.1	107.8				67					
20	10.3					68					
21						69					
22						70					
23						71					
24	17.2					72					
25	100	91.9	0.1	0.7		73					
26	679	601.1	1.4	2.7		74					
27	2112	1855.0	10.9	3.7		75					
28	850	630.1	3.6	0.8	215.5	76					
29	1944	1716.0	6.6	2.0		77					
30	282	240.6	0.5			78					
31	10,000	9985.0	21.6			79					
32	300	223.7	0.4		75.9	80					
33	129.9	106.8	1.7			81					
34						82					
35						83					
36	21.0					84					
37	129.9	115.8	0.3	1.0		85					
38	186.6	164.8	0.6	1.1		86					
39	590	521.2	3.4	1.8		87					
40	123.0	101.8	0.8	0.4	20.0	88					
41	765	658.0	13.3	1.0		89					
42	984.0	803.8	6.8	3.3		90					
43	430	370.4	13.0	46.6		91					
44	98.4	73.9	0.9	1.0	22.6	92					
45	227.4	439.3	1.4			93					
46						94					
47						95					
48						96					
49						97					
50						98					
51						99					
52						100					
53	28.5		0.2			101					
54	4.5		0.2			102					
55	41.3		2.5			103					
56	17.4		17.4			104					
57	146	146.8	1.2	0.4		105					
58	44.6	33.0		12.6		106					
59	1185	974.5		0.4		107					
60	655	655.0				108					
61	26.3					109					

A - 1-Propanol (CEC Card No. 325)
 B - 1-Butanol (CEC Card No. 346)
 C - Acetone (CEC Card No. 318)

D - Water)
 E - Nitrogen) Atmospheric
 F - Oxygen) Contamination
 G - Carbon Dioxide)
 H - Argon)

Table LXXVII

**REPRESENTATIVE MASS SPECTRAL DATA
FOR SILASTIC C/R Q-3-0121**

Mass No.	Spectrum of Mixture	Calculated Components				Mass No.	Spectrum of Mixture	Calculated Components			
		A	B	C,D,E, F,G				A	B	C,D,E, F,G	
62	266.1	208.3		57.8	62	2.8	2.3				
63	591.0	533.5	0.7	56.8	63						
64	204.9	74.7		130.2	64						
65	705.0	50.0		655.0	65						
66	2304.0	77.2		2226.8	66						
67	7.0	1.3			67						
68	13.6			13.6	68						
69					69						
70	5.8			5.8	70						
71					71						
72	10.6	6.5			72						
73	22.8	15.9			73						
74	21.3	14.0			74						
75	17.3	3.6			75	9.8	9.8				
76	291.0	53.5		237.5	76						
77	216.0	157.0			77						
78	11.0	7.4			78						
79	22.8	47.4			79						
80	48.0			48.0	80						
81					81						
82					82						
83					83						
84					84						
85					85						
86					86						
87					87						
88	24.0	13.0		11.0	88						
89	62.0	45.7			89						
90	180.0	148.0			90						
91	951.0	951.0			91						
92	340.0	46.7		293.3	92						
93	810.0	859.0	2.4		93						
94	16.0	10.4			94						
95	6.5	3.6	1.2		95						
96					96						
97					97						
98					98						
99					99						
100					100						
101					101						
102					102						
103					103						
104					104						
105					105						
106					106						
107					107						
108	519.0	491.0			108						
109	13.0	11.0			109						

A - Acetic Acid (API Serial No. 1451)
 B - Trimethyl Silanol (MRC Spectra)
 C - Water)
 D - Nitrogen)
 E - Oxygen) Atmospheric
 F - Carbon Dioxide) Contamination
 G - Argon)

Contrails

Table LXXVIII

**REPRESENTATIVE MASS SPECTRAL DATA
FOR SILICONE EC 1663**

Mass No.	Spectrum of Mixture	Calculated Components					Mass No.	Spectrum of Mixture	Calculated Components					
		A	B	C	D, E, F, G, H				A	B	C	D, E, F, G, H		
14	81.5			80.0	1.5		62	2.0						
15	129.9		0.2	126.6			63	5.0	3.3					
16	542.0			7.8	534.2		64							
17	867.0				853.9		65	5.2	4.0					
18	2904.0			10.1	2893.9		66							
19	37.5			34.0			67							
20	7.0						68							
21							69							
22	70.5				70.5		70							
23							71							
24	5.2			6.0			72							
25	26.5			27.6			73	3.3						
26	110.1			111.9			74	2.5						
27	271.2	4.9		266.0			75	2.3		2.3				
28	542.0			74.5	467.5		76	0.8		0.1				
29	293.0			289.0			77	4.8	6.7					
30	66.9			66.3			78	3.5	4.0					
31	1071.0			071.0			79	2.0	3.8					
32	21.0			13.2	7.8		80							
33	2.0						81							
34							82							
35							83							
36							84							
37							85							
38	2.0						86							
39	12.1	8.3					87							
40	10.5				10.5		88							
41	15.4			11.5			89							
42	38.2			37.3			90							
43	100.5			92.1			91	51.0	51.0					
44	1050.0			18.0	1032.0		92	16.3	3.8					
45	444.0		0.6	385.9			93							
46	168.0			166.6			94							
47	5.3		0.3				95							
48							96							
49							97							
50	4.0	3.2					98							
51	7.3	7.8					99							
52	2.2	3.6					100							
53	2.0	2.0					101							
54							102							
55	2.0						103	2.0	2.9					
56							104	1.0	1.5					
57	1.8						105	7.3	12.2					
58							106	16.3	27.0					
59							107							
60							108							
61	2.0						109							

A - Xylene (CEC Card No. 220)
 B - Trimethyl Silanol (MRC Spectra)
 C - Ethanol (CEC Card No. 312)

D - Water)
 E - Nitrogen)
 F - Oxygen) Atmospheric
 G - Carbon Dioxide) Contamination
 H - Argon)

Table LXXIX

REPRESENTATIVE MASS SPECTRAL DATA
FOR SEALER - EPON 828

Mass No.	Spectrum of Mixture	Calculated Components				Mass No.	Spectrum of Mixture	Calculated Components			
		A	B	C, D, E, F, G				A	B	C, D, E, F, G	
14	47.3		0.7	46.6		62	1.0	1.0			
15	261.0		1.2			63	1.0	1.6			
16	845.0			845.0		64					
17	1599.0		0.1	1598.9		65	1.0	1.6			
18	5010.0	1.6		5008.4		66					
19	11.0	0.6	0.3			67	17.9	15.5			
20	12.4					68	1.0	1.1			
21						69	7.6	6.7			
22	105.0			105.0		70	1.0	0.6			
23						71	2.0	2.4			
24						72	6.0	4.7			
25	2.4	1.4				73					
26	33.1	24.9	1.1			74					
27	221.7	190.1	2.5			75	1.0				
28	748.0	27.7	0.7	719.6		76					
29	234.3	211.5	2.7	20.1		77					
30	11.4	6.3	0.6			78					
31	16.5	6.4	10.1			79					
32	11.1	0.9	0.1	10.1		80					
33						81					
34						82					
35						83	1.0				
36						84					
37	12.2	10.0				85	142.5	142.5			
38	27.3	21.6				86					
39	203.4	170.2				87					
40	37.2	24.6		12.6		88					
41	309.0	272.6	0.1			89					
42	101.5	88.3	0.4			90					
43	1494.0	1422.2	0.9			91					
44	5940.0	35.0	0.2	5904.8		92					
45	89.4	10.1	3.6	75.7		93					
46	24.7		1.6			94					
47						95					
48						96					
49						97					
50	9.9	7.9				98					
51	10.5	8.8				99					
52	3.5	2.6				100	124.2	149.9			
53	11.2	10.2				101	8.7	9.2			
54	2.7	2.1				102					
55	18.0	18.3				103					
56	15.1	14.4				104					
57	279.6	271.1				105					
58	432.0	458.9				106					
59	28.8	28.7				107					
60	2.7	1.7				108					
61	1.0	0.7				109					

A - Methyl Isobutyl Ketone (API Serial No. 380)
 B - Ethanol (CEC Card No. 312)
 C - Water)
 D - Nitrogen) Atmospheric
 E - Oxygen) Contamination
 F - Carbon Dioxide)
 G - Argon)

Contrails

Table XXC

REPRESENTATIVE MASS SPECTRAL DATA
FOR SILICONE PRIMER A-4004

Peak No.	Spectrum of Mixture	Calculated Components				Peak No.	Spectrum of Mixture	Calculated Components			
		A	B	C, D, E, F, G							
14	12.8	1.8		11.0	62						
15	15.4	3.0		12.4	63						
16	211.2			211.2	64						
17	1227.0			1227.0	65						
18	3790.0			3790.0	66						
19	9.8				67						
20	9.0				68						
21					69						
22	6.0				70						
23					71						
24					72						
25					73						
26	12.0	2.6	6.9		74						
27	65.4	6.3	54.6		75						
28	123.6	1.8	17.9	103.9	76						
29	45.4	6.8	33.0		77						
30	3.8		2.5		78						
31	133.5	25.2	108.3		79						
32	19.0	1.6	1.7	15.7	80						
33	7.0		8.7		81						
34					82						
35					83						
36	2.1				84						
37	3.2		1.5		85						
38	5.0		2.8		86						
39	24.2		17.2		87						
40	9.2		4.2	5.0	88						
41	70.1		66.8		89						
42	34.8		34.0		90						
43	66.0	2.2	65.3		91						
44	411.0		4.6	406.4	92						
45	11.5	9.1	7.1		93						
46	2.5	3.9			94						
47					95						
48					96						
49					97						
50					98						
51					99						
52					100						
53					101						
54					102						
55	15.0		12.6		103						
56	87.3		87.3		104						
57	12.3		6.2		105						
58					106						
59					107						
60					108						
61					109						

- A - Ethanol (CEC Card No. 312)
- B - 1-Butanol (CEC Card No. 346)
- C - Water)
- D - Nitrogen)
- E - Oxygen) Atmospheric Contamination
- F - Carbon Dioxide)
- G - Argon)

Table XXCI

REPRESENTATIVE MASS SPECTRAL DATA FOR SILICONE PRIMER SS-4004

Scan No.	Spectrum of Mixture	Calculated Components							H, I, J, K, L	Mass No.	Spectrum of Mixture	Calculated Components				
		A	B	C	D	E	F	G				A	B	C	D	E
14	570.0					396.5		126.9	46.6	62	9.0			5.2		
15	1626.0			1.6		1271.1		206.0		63	18.9		0.7	11.2		
16	325.0					52.6		12.7	259.7	64	4.5			2.7		
17	954.0					51.8		21.3	880.9	65	20.9	1.0	0.8	16.5		
18	3170.0					65.8		16.4	3087.8	66	3.5			2.1		
19	788.0					613.2		55.2		67	2.0					
20	21.5									68	2.0					
21	2.0									69	10.0					
22	5.0								5.0	70	3.2					
23										71	5.0					
24	17.5							9.8		72	5.2					
25	96.0				0.1	56.1	1.7	45.0		73	6.0				0.3	
26	488.0			2.6	1.3	295.6	6.4	182.1		74	3.0			1.4	0.1	
27	2250.0	1.4	1.0	6.4	10.1	1537.7	8.9	432.9		75	2.0			0.9		
28	490.0				3.3	144.7	1.9	121.3	218.8	76	1.8			0.6		
29	1704.0				6.1	1093.8	4.8	470.2		77	6.4	1.9	1.4	1.5		
30	186.0				0.5	93.0	0.2	107.9		78	2.6		0.8			
31	2109.0				20.0	512.3	0.6	1742.6		79	3.0	1.2	0.8			
32	69.0				0.3			21.4	47.3	80						
33	24.7				1.6					81						
34										82						
35										83	3.2					
36	27.2						0.6			84	3.0					
37	174.0			2.9	0.3	146.5	2.3			85	3.5			0.8		
38	270.0			6.2	0.5	220.2	2.6			86	2.2			1.1		
39	818.0	2.0	1.7	23.8	3.2	631.6	4.2			87	3.0			0.7		
40	136.0			2.7	0.8	94.7	0.9		36.9	88						
41	999.0			2.6	12.3	674.6	2.4	18.6		89	6.2			5.1		
42	602.0				6.3	422.8	7.8	60.6		90	4.0			4.3		
43	2250.0			2.2	12.0	1718.4	111.4	149.9		91	140.0	1.9	10.4	127.7		
44	1716.0			1.2	0.8	314.0	2.5	29.3	1368.2	92	93.0	0.5	0.8	88.0		
45	>10,000			6.2	1.3	8772.0		627.9		93	7.6			7.0		
46	420.0			4.4	0.1	200.9		271.1		94						
47	30.0									95						
48										96						
49	3.0			1.2						97	5.0					
50	19.2		0.6	7.7	0.2					103	1.7	0.9	0.6			
51	24.5	1.4	1.6	12.2	0.1					104	1.0	0.4				
52	8.8		0.7	3.0						105	20.8	18.1	2.5			
53	19.0			1.5	0.2					106	7.0	1.5	5.5			
54	3.5				0.2											
55	40.2				2.3											
56	16.1				16.1					118	1.5					
57	47.5				1.1			0.9		119	3.0	0.4				
58	30.2							30.2		120	7.0	5.4				
59	300.0					300.0	1.0			121	3.4	0.5				
60	36.0					36.0										
61	6.0			2.6												

- A - C₃ Alkyl Benzene (CEC Card No. 225)
- B - Xylene (CEC Card No. 220)
- C - Toluene (CEC Card No. 214)
- D - 1-Butanol (CEC Card No. 346)
- E - 2-Propanol (CEC Card No. 326)
- F - Acetone (CEC Card No. 318)
- G - Ethanol (CEC Card No. 312)

- H - Water
 - I - Nitrogen
 - J - Oxygen
 - K - Carbon Dioxide
 - L - Argon
- } Atmospheric Contamination

Contrails

Table XXCII
 REPRESENTATIVE MASS SPECTRAL DATA
 FOR SILICONE PRIMER EC-1694

Mass No.	Spectrum of Mixture	Calculated Components					Mass No.	Spectrum of Mixture	Calculated Components				
		A	B	C	D	E, F, G, H, I			A	B	C	D	E, F, G, H, I
14	71.5	55.5	7.5			8.5	62	3.5					2.8
15	207.0	177.9	12.1				63	6.9					6.0
16	343.0	7.4	0.7			334.9	64						
17	215.1	7.2	1.3			206.6	65	9.2					8.8
18	715.0	9.2	1.0			704.8	66						
19	95.7	85.8	3.3				67						
20	4.0						68						
21							69						
22	13.6					13.6	70						
23							71						
24	2.5		0.6				72						
25	11.3	7.9	2.6	0.6			73	2.0			1.6		
26	64.4	41.4	10.7	7.9			74	1.8			0.6		
27	324.0	215.5	25.5	62.8	3.4		75						
28	395.0	20.3	7.1	20.6		347.0	76						
29	237.0	153.1	27.7	38.0			77						
30	23.3	13.0	6.4	2.9			78						
31	300.0	71.7	102.7	124.6			79						
32	12.8		1.3	2.0		9.5	80						
33	9.8			10.1			81						
34							82						
35							83						
35	4.0						84						
37	25.0	20.5		1.7			85						
38	39.0	30.8		3.2	3.3		86						
39	131.1	88.4		19.8	12.6		87						
40	25.4	13.3		4.8		7.3	88						
41	186.0	94.4	1.1	76.9			89						
42	105.0	59.2	3.6	39.1			90	4.5					
43	333.0	240.6	8.8	75.1			91				2.3		
44	2907.0	44.0	1.7	5.2		2856.1	92	68.0			68.0		
45	1299.0	1228.0	37.0	8.1	3.3	22.6	93	45.5			46.9		
46	57.0	28.1	16.0	0.6			94						
47							95						
48							96						
49							97						
50	7.0			1.0	4.1		98						
51	8.6			0.9	6.5		99						
52							100						
53	4.7			1.2			101						
54	1.5			1.2			102						
55	21.5			14.5			103						
56	100.5			100.5			104						
57	16.0			7.1			105						
58	6.0						106						
59	42.0	42.0					107						
60	4.8	5.0					108						
61							109						

A - 2-Propanol (CEC Card No. 326)
 B - Ethanol (CEC Card No. 312)
 C - 1-Butanol (CEC Card No. 346)
 D - Toluene (CEC Card No. 214)

E - Water)
 F - Nitrogen)
 G - Oxygen) Atmospheric
 H - Carbon Dioxide) Contamination
 I - Argon)

Table XXCIII

REPRESENTATIVE MASS SPECTRAL DATA
FOR ELECTRICAL RESIN, SCOTCHCAST NO. 8

Mass No.	Spectrum of Mixture	Calculated Components					Mass No.	Spectrum of Mixture	Calculated Components				
		A	B	C	D	E, F, G, H, I			A	B	C	D	
14	20.4			0.9		19.5	62	4.5	3.6				
15	50.3	1.1		0.8			63	9.4	7.7				
16	178.8			0.1		178.7	64	2.3	1.8				
17	709.0			0.3		708.7	65	12.4	11.3				
18	2388.0			0.8		2387.2	66	1.9	1.4				
19	4.5			0.5			67	1.2					
20	7.9						68						
21							69	0.8					
22	11.1					11.1	70						
23							71						
24							72	0.7					
25	1.4			0.4	1.8		73	1.0					
26	7.3	1.8		2.7	6.9		74	1.3	0.9				
27	20.5	4.4		8.2	9.6		75	1.6	0.6				
28	140.7			2.8	2.0	135.9	76	2.7	0.4				
29	44.5			7.6	5.1		77	1.5	1.0	0.1			
30	4.9			1.1	0.2		78	0.5					
31	43.9			44.2	0.7		79						
32	61.9			1.0		60.9	80						
33	0.6			0.5			81						
34							82						
35	0.7						83						
36	3.2				0.7		84						
37	5.0	2.0		0.5	2.5		85	8.0	0.5				
38	9.0	4.2		0.7	2.8		86	1.5	0.8				
39	29.5	16.3	0.1	2.3	4.6		87	0.8	0.5				
40	6.4	1.8		0.5	1.0	3.1	88						
41	18.9	1.8		2.9	2.5		89	3.8	3.5				
42	9.4			3.6	8.4		90	4.1	3.0				
43	122.7	1.5		1.6	119.6		91	87.5	87.5				
44	576.0	0.8		0.3	2.7	572.2	92	64.0	60.2				
45	16.1	4.3		1.9			93	4.5	4.8				
46	5.6	3.0					94						
47							95						
48							96						
49	1.1	0.8					97						
50	7.3	5.3	0.1				98						
51	10.2	8.4	0.1				99						
52	2.7	2.1	0.1				100						
53	2.0	1.0					101						
54							102						
55	1.6						103						
56	1.2						104						
57	14.5			0.6	1.0		105						
58	31.4			0.1	32.4		106						
59	2.0			4.3	1.1		107						
60	2.9			2.9			108						
61	2.6	1.8					109						

A - Toluene (CEC Card No. 214)
 B - Benzene (CEC Card No. 212)
 C - 1-Propanol (CEC Card No. 325)
 D - Acetone (CEC Card No. 318)

E - Water)
 F - Nitrogen)
 G - Oxygen) Atmospheric
 H - Carbon Dioxide) Contamination
 I - Argon)

Contrails

Table XXCIV

REPRESENTATIVE MASS SPECTRAL DATA FOR DC-325

Mass No.	Spectrum of Mixture	Calculated Components					Mass No.	Spectrum of Mixture	Calculated Components					
		A	B	C	D,E, F,G,H				A	B	C	D,E, F,G,H		
14	129.3				129.3		62							
15	20.5		0.2				63							
16	234.3				234.3		64							
17	1164.0				1164.0		65							
18	4010.0				4010.0		66							
19	8.0						67							
20	25.6				25.6		68							
21							69							
22	10.3				10.3		70							
23							71							
24							72							
25							73							
26	4.2	2.9					74							
27	9.0	4.1					75	2.8		2.8				
28	318.0				318.0		76							
29	10.9	2.2			8.7		77							
30							78							
31	4.8						79							
32	33.2				33.2		80							
33							81							
34							82							
35	2.8						83							
36	12.6						84							
37	2.1	1.1					85							
38	5.6	1.2					86							
39	4.2	1.9		0.6			87							
40	6.7				6.7		88							
41	5.6	1.1					89							
42	5.5	3.6					90							
43	50.9	50.9					91	2.0			2.0			
44	539.0				539.0		92	1.3			1.4			
45	9.5		0.7		8.8		93							
46	2.9				2.9		94							
47	1.0		0.4				95							
48							96							
49							97							
50							98							
51							99							
52							100							
53							101							
54							102							
55	1.6						103							
56	2.8						104							
57	3.7						105							
58	10.6	13.8					106							
59							107							
60							108							
61							109							

A - Acetone (CEC Card No. 318)
 B - Trimethyl Silanol (MRC Spectra)
 C - Toluene (CEC Card No. 214)

D - Water)
 E - Nitrogen) Atmospheric
 F - Oxygen) Contamination
 G - Carbon Dioxide)
 H - Argon)

Table XXCV

REPRESENTATIVE MASS SPECTRAL DATA
FOR PLEXIGLAS, NO. 2 CLEARMIL

Methylmethacrylate is present as a low level gas-off product. The following lines were observed and are the strong lines of methyl methacrylate according to API spectrum No. 1648.

<u>Mass</u>	<u>Intensity Chart Div.</u>
41	31
69	20
39	12.3
100	10.4
40	3.1
59	2.5

Table XXCVI

REPRESENTATIVE MASS SPECTRAL DATA
FOR THERMOFIT TUBING SPLICER C/R 197-075

A trace of hydrocarbon was detected as a gas-off product. These are characterized by weak lines at the following masses:

<u>Mass</u>	<u>Species</u>
27	C ₂ H ₃
29	C ₂ H ₅
43	C ₃ H ₇
57	C ₄ H ₉

Table XXCVII

REPRESENTATIVE MASS SPECTRAL DATA
FOR ACETAL RESIN, DELRIN NO. 100

Scan No.	Spectrum of Mixture	Calculated Components					Mass No.	Spectrum of Mixture	Calculated Components					
		A	B	C, D, E, F, G										
14	74.7			72.8			62							
15							63							
16	169.			156			64							
17	847			850			65							
18	2980			2980			66							
19	4.5						67							
20	8.0			1.5			68							
21							69							
22	5.0			5.1			70							
23							71							
24							72							
25							73							
26	2.0		1.3				74							
27	6.0		1.0				75							
28	576	57		487			76							
29	245.4	185	24.0				77							
30	164.4	164					78							
31	8.0	3.5					79							
32	107.1			107			80							
33							81							
34							82							
35							83							
36							84							
37							85							
38							86							
39	3.5						87							
40	12.0		1.9	12.0			88							
41	6.0		1.5				89							
42	2.0		3.5				90							
43	11.8		11.8				91							
44	302		21.2	280			92							
45	5.9		1.0	3.2			93							
46	1.5			1.2			94							
47							95							
48							96							
49							97							
50							98							
51							99							
52							100							
53							101							
54							102							
55							103							
56							104							
57							105							
58							106							
59							107							
60							108							
61							109							

A - Formaldehyde (API Serial No. 84)
 B - Acetaldehyde (API Serial No. 293)
 C - Water)
 D - Nitrogen)
 E - Oxygen) Atmospheric Contamination
 F - Carbon Dioxide)
 G - Argon)

Contrails

Table XXCVIII

MASS SPECTRAL DATA FOR GLC FRACTION OF COMPONENT COMMON TO
GAS-OFF PRODUCTS FROM
MAGNESIUM/LITHIUM ALLOYS, LA-91, LA-141, AND LA-2-933

Mass No.	Spectrum of Mixture	Calculated Components					Mass No.	Spectrum of Mixture	Calculated Components				
		A	B, C, D, E										
14	40.3						62						
15	25.3						63						
16	681		681				64						
17	2312		2312				65						
18	>10,000		16,210				66						
19	52.1						67						
20							68						
21							69						
22							70						
23							71						
24							72						
25	1.3						73						
26	6.1						74						
27	31.7	X					75						
28	383.2		383				76						
29	30.6	X					77						
30	4.5						78						
31	18.0						79						
32	68.2		68				80						
33							81						
34							82						
35							83						
36	3.0						84						
37	2.0						85						
38	3.4						86						
39	9.0						87						
40	10.9						88						
41	12.0	X					89						
42	9.1						90						
43	50.1	X					91						
44	295		295				92						
45	81.2	X					93						
46	4.0						94						
47	2.1						95						
48							96						
49							97						
50							98						
51							99						
52							100						
53							101						
54							102						
55							103						
56							104						
57							105						
58							106						
59							107						
60							108						
61							109						

A - Possibly a C₅ or higher secondary alcohol (Characteristic Lines Marked by "X")
 B - Water
 C - Carbon Dioxide
 D - Nitrogen
 E - Oxygen

} Atmospheric Contaminants

APPENDIX III

REPRESENTATIVE GAS CHROMATOGRAMS
FOR
GAS-OFF EXPERIMENTS

Contrails

The gas chromatograms shown in this appendix were obtained on an F & M Scientific Corporation Model 810 Gas Chromatograph. Instrument conditions and column specifications are listed in Table XXCIX. Since retention times tended to shift somewhat due to column aging, a standard mixture was used as a day to day reference.

The gas chromatograms are representative of a particular candidate material. In comparing patterns for different candidate materials, consideration must be taken of instrument sensitivity factors and the amounts of atmosphere used for analysis. Although, generally a 25 ml aliquot was used, some of the early analyses were performed on the condensate from the total 9-liter volume.

Table XXCIX

GAS CHROMATOGRAPHIC INSTRUMENT CONDITIONS

Detector (All samples in Section I were analyzed using a flame ionization detector and a F & M Model 810 Research Gas Chromatograph)

Condition

- D Column temp. - 35°-240°C @ 10°C/min.
Detector temp. - 275°C Injection port temp. - 260°C
Dual column detection Flow split - 1:10
Column A Flow Rate - 60 ml/min.
Column B Flow Rate - 130 ml/min.
Range - 10 Attenuation - X4
- E Column temp. - 35°-240°C @ 10°C/min.
Detector temp. - 275°C Injection port temp. - 260°C
Dual column detection
Column A Flow Rate - 60 ml/min.
Column B Flow Rate - 130 ml/min.
Range - 10 Attenuation - X8
- F Column temp. - 35°-240°C @ 10°C/min.
Detector temp. - 275°C Injection port temp. - 260°C
Dual column detection
Column A Flow Rate - 60 ml/min.
Column B Flow Rate - 130 ml/min.
Range - 10² Attenuation - X8
- G Column temp. - 35°-240°C @ 10°C/min.
Detector temp. - 275°C Injection port temp. - 260°C
Single column detection
Column A Flow Rate - 60 ml/min.
Range - 10² Attenuation - X16
- H Column temp. - 35°-240°C @ 10°C/min.
Detector temp. - 275°C Injection port temp. - 260°C
Single column detection
Column A Flow Rate - 60 ml/min.
Range - 10 Attenuation - X16

Contrails

Table XXCIX - Cont'd

Condition

- I Column temp. - 35°-240°C @ 10°C/min.
Detector temp. - 275°C Injection port temp. - 260°C
Single column detection
Column A Flow Rate - 60 ml/min.
Range - 10 Attenuation - X16
- J Column temp. - 35°-240°C @ 10°C/min.
Detector temp. - 275°C Injection port temp. - 260°C
Single column detection
Column A Flow Rate - 20 ml/min.
Range - 10 Attenuation - X32
- K Column temp. - 35°-240°C @ 10°C/min.
Detector temp. - 275°C Injection port temp. - 260°C
Single column detection Flow split - 1:10
Column A Flow Rate - 85 ml/min.
Range - 10 Attenuation - X16
- L Column temp. - 35°-240°C @ 10°C/min.
Detector t-mp. - 275°C Injection port temp. - 260°C
Single column detection
Column A Flow Rate - 60 ml/min.
Range - 10 Attenuation - X8
- M Column temp. - 35°-240°C @ 10°C/min.
Detector temp. - 275°C Injection port temp. - 260°C
Single column detection
Column A Flow Rate - 40 ml/min.
Range - 10 Attenuation - X8

Columns used with the above instrument conditions.

- 1 5% Carbowax 20 m on 60-80 mesh Gas-Pack F 11' x 1/4"
stainless steel tubing. Packed 9-64.
- 2 Same as Column No. 1 only repacked with new substrate
on 4-2-65.
- 3 Repacked with a new lot of substrate, same as
Column No. 1. But due to the inadequacy to separate
the components in the standard, it was repacked with
the old substrate from Column No. 2.




Figure 7. Gas Chromatogram of 10 Component Standard.

Contrails




Figure 8. Gas Chromatogram of Gas-Off Products from Adhesive, A-4000 (90 Days, Air).

Contrails




Figure 9. Gas Chromatogram of Gas-Off Products from Adhesive #271 (30 Days, Oxygen).

Contrails




Figure 10. Gas Chromatogram of Gas-Off Products from Resin, Versamid 125 (90 Days, Air).




Figure 11. Gas Chromatogram of Gas-Off Products from Neoprene, Phenolic EC-847 (30 + 30 Days, Air).




Figure 12. Gas Chromatogram of Gas-Off Products from Silastic #950 (90 Days, Oxygen).




Figure 13. Gas Chromatogram of Gas-Off Products from Silastic S2007 (90 Days, Oxygen).




Figure 14. Gas Chromatogram of Gas-Off Products from Velvet Coating No. 104-C 10 Black (30 + 30 + 30 Days, Air).




Figure 15. Gas Chromatogram of Gas-Off Products from Class H Silicone Impregnating Varnish, No. 997 (30 + 30 + 30 Days, Oxygen).




Figure 16. Gas Chromatogram of Gas-Off Products from 620 Light Gull Gray Coatings XA-193 (90 Days, Oxygen).




Figure 17. Gas Chromatogram of Gas-Off Products from 3615 Gray Coating XA-194 (90 Days, Oxygen).




Figure 18. Gas Chromatogram of Gas-Off Products from Silver Marking Ink No. 1448 (with Cresylic Acid)(30 + 30 Days, Oxygen).

Contrails




Figure 19. Gas Chromatogram of Gas-Off Products from Lockfoam E-302 (R and T) (60 Days, Oxygen).

Contrails




Figure 20. Gas Chromatogram of Gas-Off Products from Fluorolube Oil Grade FS-5 (90 Days, Oxygen).

Contrails




Figure 21. Gas Chromatogram of Gas-Off Products from Fluorolube Grease Grade GR-544 Type L.G. (90 Days, Oxygen).

Contrails




Figure 22. Gas Chromatogram of Gas-Off Products from Silicone Fluid F-50 (90 Days, Air).

Contrails




Figure 23. Gas Chromatogram of Gas-Off Products from Silicone Grease G-300 (90 Days, Oxygen).

Contrails




Figure 24. Gas Chromatogram of Gas-Off Products from Silicone Release Agent DC-7 (90 Days, Air).

Contrails




Figure 25. Gas Chromatogram of Gas-Off Products from DC-4 (MIL-I-6880) (90 Days, Oxygen).

Contrails




Figure 26. Gas Chromatogram of Gas-Off Products from Wax Lubricant #111 (90 Days, Air).

Contrails




Figure 27. Gas Chromatogram of Gas-Off Products from Silastic RTV-882 (30 + 30 + 30 Days, Oxygen).

Contrails




Figure 28. Gas Chromatogram of Gas-Off Products from Silastic RTV-731 (60 Days, Oxygen).




Figure 29. Gas Chromatogram of Gas-Off Products from Sealant RTV-90 (30 + 30 + 30 Days, Oxygen).




Figure 30. Gas Chromatogram of Gas-Off Products from Silastic RTV-501 (60/Days, oxygen).




Figure 31. Gas Chromatogram of Gas-Off Products from Silastic C/R Q-3-0121 - Sealant Q-3-0121 (30 Days, Air).




Figure 32. Gas Chromatogram of Gas-Off Products from Silicone EC-1663 (30 + 30 Days, Air).




Figure 33. Gas Chromatogram of Gas-Off Products from Sealer - Epon 828 (30 + 30 + 30 Days, Oxygen).




Figure 34. Gas Chromatogram of Gas-Off Products from Silicone Primer A-4004 (30 + 30 Days, Air).




Figure 35. Gas Chromatogram of Gas-Off Products from Silicone Primer SS-4004 (30 + 30 + 30 Days, Oxygen).

Note: See Standard #30.




Figure 36. Gas Chromatogram of Gas-Off Products from Silicone Primer SS-4004 (60 Days, Oxygen).

Note: See Standard #43.




Figure 37. Gas Chromatogram of Gas-Off Products from Silicone Primer EC-1694 (90 Days, Air).

Contrails




Figure 38. Gas Chromatogram of Gas-Off Products from Electrical Resin Scotchcast #8 (60 Days, Oxygen).

Contrails




Figure 39. Gas Chromatogram of Gas-Off Products from DC-325 (30 + 30 + 30 Days, Oxygen).




Figure 40. Gas Chromatogram of Gas-Off Products from Plexiglas No. 2 Clearmil (30 Days, Oxygen).




Figure 41. Gas Chromatogram of Gas-Off Products from Magnesium Lithium Alloy La-91 (9% Lithium) (30 Days, Oxygen).

Contrails




Figure 42. Gas Chromatogram of Gas-Off Products from Magnesium Lithium Alloy LA-141 (14% Lithium) (30 Days, Oxygen).

Contrails




Figure 43. Gas Chromatogram of Gas-Off Products from Magnesium Lithium Alloy LA2-933 (9% Lithium) (30 Days, Oxygen).

Contrails

APPENDIX IV

CARBON DESORPTION ANALYSES
AND
GAS CHROMATOGRAMS

Contrails

The gas chromatograms shown in this appendix were obtained on F & M Scientific Corporation Model 300 and Model 500 Gas Chromatographs using thermal conductivity detectors with rhenium-tungsten filaments. Instrument conditions and column specifications are listed in Table XC.

Table XC

GAS CHROMATOGRAPHIC INSTRUMENT CONDITIONS
FOR ANALYSIS OF CARBON DESORBATES

Condition

- O Column temp. - 35° for 1 min; programmed @ 21°C/min.
 to 350°C
 Detector temp. - 265°C Injection port temp. - 310°C
 Flow Rate - 5 ml/min. Filament current - 175 ma
 Chart speed - 0.5"/min. Sample size - 1.0 ml (gas)
 Column - Linde Molecular Sieve 5A
 (2' x 1/4" stainless steel)
- P Column temp. - 50°C
 Detector temp. - 265°C Injection port temp. - 310°C
 Flow Rate - 60 ml/min. Filament current - 172 ma
 Chart speed - 0.5"/min. Sample size - 0.2 µl
 Column - 10% Octoil S on Haloport F
 (10' x 1/4" copper)
- Q Column temp. - 95°C
 Detector temp. - 265°C Injection port temp. - 310°C
 Flow Rate - 60 ml/min. Filament current - 175 ma
 Chart speed - 0.5"/min. Sample size - 0.2 µl
 Column - Carbowax 5000 on 60-80 mesh
 (6' x 1/4" stainless steel)

Table XCI

ANALYSIS OF DESORBATE FROM CARBON CANISTER 10-12 DAY

Fraction	Weight (mg)	Mole Percent					
		CO ₂	Water	Ethylene	Ethanol	Freon-12	Acetaldehyde
Volatile at -76°C	13.5 ⁽¹⁾	81.7	6.2	9.5	-	1.5	1.1
Volatile at 0°C	13.1 ⁽¹⁾	92.6	3.9	1.0	0.7	1.1	0.7
Volatile at 23°C	11.1 ⁽¹⁾	64.6	10.8	-	13.9	0.5	10.2
Volatile at 100°C	467.5	0.2	85.8	-	12.7	-	1.3

(1) Determined by pressure-volume measurements

Table XCII
ANALYSIS OF DESORBATE FROM CARBON CANISTER 16-18 DAY

Fraction	Weight (mg)	Mole Percent						
		CO ₂	Water	Ethylene	Ethanol	Freon 12	Acetaldehyde	Acetone
Volatile at -76°C	14.3 (1)	97.3	0.2	1.9	-	0.6	-	-
Volatile at 0°C	14.1 (1)	97.3	1.6	1.6	-	1.0	-	-
Volatile at 23°C	45.2	1.4	42.4	-	54.1	-	2.1	-
Volatile at 100°C	8.4	4.8	55.4	-	36.5	-	1.2	2.1

(1) Determined by pressure-volume measurement.

Table XCIII
ANALYSIS OF DESORBATE FROM CARBON CANISTER 26-28 DAY

<u>Fraction</u>	<u>Weight (mg)</u>	<u>Mole Percent</u>				
		<u>CO₂</u>	<u>Water</u>	<u>Ethylene</u>	<u>Ethanol</u>	<u>Acetaldehyde</u>
Volatille at -76 °C	7.4(1)	98.1	1.0	0.9	-	-
Volatille at 0 °C	13.6	98.7	1.3	-	-	-
Volatille at 23 °C	not determined	0.7	35.6	-	62.6	1.1
Volatille at 100 °C	406.4	0.4	92.3	-	7.2	0.1

(1) Determined by pressure-volume measurement

Table XCIV

ANALYSIS OF DESORBATE FROM CARBON CANISTER 28 DAY (THOMAS)

Fraction	Weight (mg)	Mole Percent							
		CO ₂	Water	Ethylene	Ethanol	Freon-12	Hydrocarbon	C ₃	Acetaldehyde
Volatiles at -76°C	20-30(1)	82.6	0.1	16.6	-	0.4	0.2	-	-
Volatiles at 0°C	18(1)	93.0	0.1	5.4	0.3	0.4	0.7	-	-
Volatiles at 23°C	36.2	-	79.3	-	19.7	0.9	-	-	-
Volatiles at 100°C	872.5	-	63.3	-	36.2	-	-	-	0.5

(1) Determined by pressure-volume measurements

Desorption Products of
Carbon 16-18 Day
(-76°C fraction)
Linde sieve 5A column
Instrument condition - O

A = Oxygen
B = Nitrogen
C = Carbon Dioxide




Figure 44. Gas Chromatogram of Desorption Products of Carbon 16-18 Day (-76°C Fraction).




Figure 45. Gas Chromatogram of Desorption Products of Carbon 16-18 Day (0°C Fraction).

Desorption Products of
Carbon 16-18 Day
(23°C fraction) Carbowax
4000 Column
Instrument Condition - Q

- A = Air + Carbon Dioxide
- B = Acetaldehyde
- C = Unknown
- D = Ethanol
- E = Paraldehyde (tentative)
- F = Water




Figure 46. Gas Chromatogram of Desorption Products of Carbon 16-18 Day (23°C Fraction) Using Carbowax 4000 Column.




Figure 47. Gas Chromatogram of Desorption Products of Carbon 16-18 Day (23°C Fraction) Using Octoil S Column.

Contrails




Figure 48. Gas Chromatogram of Desorption Products of Carbon 16-18 Day (100°C Fraction) Using Carbowax 4000 Column.




Figure 49. Gas Chromatogram of Desorption Products of Carbon 16-18 Day (100°C Fraction) Using Octoil S Column.

Contrails

APPENDIX V

ANALYTICAL DATA
FOR
HYDROLYSIS OF MCS 198

Contrails

The gas chromatograms shown in this appendix were obtained on F & M Scientific Corporation Model 300 and Model 500 Gas Chromatographs using thermal conductivity detectors with rhenium-tungsten filaments. Instrument conditions and column specifications are listed in Table XCV.

Table XCVI

MCS 198 + LiOH IN ATMOSPHERE OF 35% RELATIVE HUMIDITY

Contact Time (hrs)	Weight of Condensables (mg)	Composition of Condensables by GLC (% of Total Peak Area)						
		Water	2-Propanol	2-Butanol	S1(OIP)4	S1(OIP)3 (OSB)3	S1(OIP)2 (OSB)2	S1(OIP) (OSB)1
1 ^a	47.5	72.4	19.6	8.0	-	-	-	-
1 + 5 ^a	24.3	58.8	27.8	12.1	0.6	0.6	0.1	-
1 + 5 + 18 ^a	26.7	19.9	55.6	18.5	2.1	2.8	1.1	trace
6	30.2	69.9	22.6	7.5	-	-	-	-
24	127.0	trace	71.7	23.4	2.1	2.4	0.4	-
24 (Blank) ^b	36.5	59.3	23.8	13.1	1.5	1.7	0.6	trace
24 (Water) ^c	140.0	trace	64.2	13.8	7.3	9.8	4.9	-

^a After removing head gases, flask was recharged and progressive analyses were performed.

^b No LiOH.

^c Three Milliliters of water added to LiOH.

IP - Isopropyl
SB - Secondary butyl

MCS 198 + LiOH (1Hour)
Silicone Gum Rubber Column
Instrument Condition - R
A = Air
B = Water
C = Isopropanol
D = 2-Butanol
E = Hexanols, Heptanols, Xylenes





Figure 50. Gas Chromatogram of Gaseous Product from MCS 198 and LiOH (1 hour).



MCS 198 + LiOH
 (1 Hour + 5 Hour)
 Silicone Gum Rubber Column
 Instrument Condition - R

A = Water
 B = Isopropanol
 C = 2-Butanol
 D = Hexanols, Heptanols, Xylene
 E = Si(OIP)₄
 F = Si(OIP)₃ (OSB)
 G = Si(OIP)₂(OSB)₂
 IP - Isopropyl
 SB - Secondary Butyl

Figure 51. Gas Chromatogram of Gaseous Product from MCS 198 and LiOH (1 hour + 5 hours).

MCS 198 + LiOH (1 Hour +
5 Hour + 18 Hour)
Silicone Gum Rubber Column
Instrument Condition - R

- A = Air
- R = Water
- C = Isopropanol
- D = 2-Butanol
- E = Hexanols, Heptanols, Xylenes
- F = Si(OIP)₄
- G = Si(OIP)₃(OSB)
- H = Si(OIP)₂(OSB)₂
- I = Si(OIP)(OSB)₃
- IP - Isopropyl
- SB - Secondary Butyl




Figure 52. Gas Chromatogram of Gaseous Product from MCS 198 and LiOH
(1 hour + 5 hours + 18 hours).

MCS 198 + LiOH (6Hour)
Silicone Gum Rubber Column
Instrument Condition - R

A = Air
B = Water
C = Isopropanol
D = 2-Butanol
E = Hexanols, Heptanols, Xylenes





Figure 53. Gas Chromatogram of Gaseous Product of MCS 198 and LiOH (6 hours).



MCS 198 + LiOH (24 Hour)
 Silicone Gum Rubber Column
 Instrument Condition - R

A = Air
 B = Isopropanol
 C = 2-Butanol
 D = Hexanols, Heptanols, Xylenes
 E = Si(OIP)₄
 F = Si(OIP)₃(OSE)
 G = Si(OIP)₂(OSE)₂
 IP - Isopropyl
 SB - Secondary Butyl

Figure 54. Gas Chromatogram of Gaseous Product of MCS 198 and LiOH (24 hours).

MCS 198 (24 Hour Blank -
No LiOH)
Silicone Gum Rubber Column
Instrument Condition - R

A = Air
B = Water
C = Isopropanol
D = 2-Butanol
E = Hexanols, Heptanols, Xylenes
F = Si(OIP)₄
G = Si(OIP)₃(OSB)
H = Si(OIP)₂(OSB)₂
IP - Isopropyl
SB - Secondary Butyl




Figure 55. Gas Chromatogram of Gaseous Product from MCS 198 (24 hour Blank - no LiOH).

MCS 198 + LiOH + Water
(3 ml.) (24 Hours)
Silicone Gum Rubber Column
Instrument Condition - R

- A = Isopropanol
- B = 2-Butanol
- C = Hexanol, Heptanol, Xylenes
- D = Si(OIP)3(OSB)*
- E = Si(OIP)2(OSB)2
- F = Si(OIP) (OSB)3
- IP - Isopropyl
- SB - Secondary Butyl





Figure 56. Gas Chromatogram of Gaseous Product of MCS 198, LiOH and Water (24 hours).



MCS 198 Sprayed onto
LiOH, H₂O
Silicone Gum Column
Instrument Condition - R

A = Water
B = Isopropanol
C = Hexanols, Heptanols, Xylenes
D = Si(OP)₃(OSB)
E = Si(OP)₂(OSB)₂
F = Si(OP)(OSB)₃

IP - Isopropyl
SB - Secondary Butyl

Figure 57. Gas Chromatogram of Gaseous Product from MCS 198 Sprayed onto LiOH·H₂O.

REFERENCES

1. Nestler, F. H. M., and Smith, W. D. (1958). Submarine Habitability-Atmosphere Sampling and Analysis, Naval Research Laboratory Memo Report 866.
2. Nestler, F. H. M., and Smith, W. D. (1959). Submarine Habitability-Atmosphere Sampling and Analysis, Naval Research Laboratory Memo Report 982, Vol. II.
3. Platt, V. R., (1960). Chemical Constituents of Submarine Atmospheres, Naval Research Laboratory Report 5465.
4. Umstead, M. E., Christian, J. G. and Johnson, J. E. (1960). A Study of the Organic Vapors in the Atmosphere of the U.S.S. Skate, Naval Research Laboratory Memo Report 1057.
5. Umstead, M. E. (1961). Gas Chromatography in the Study of Trace Organic Vapor Contaminants, Chapter 8, Annual Progress Report, The Present Status of Chemical Research in Atmosphere Purification and Control on Nuclear-Powered Submarines, Platt, V. R., and Ramskill, R. A. Editors, Naval Research Laboratory Report 5630.
6. Umstead, M. E. and Carnart, H. W. (1962). Gas Chromatography as a Submarine Atmosphere Monitor, Naval Research Laboratory Report 5814. Chapter 6.
7. Kinsey, J. L. (1963). Origin of Contamination in the Nuclear Submarine Atmosphere, Symposium on Toxicity in the Closed Ecological System, Palo Alto, Calif., Lockheed Missiles and Space Co., pp. 1-8.
8. Anderson, W. L., and Saunders, R. A. (1963). Evaluation of Materials in the Closed System, *ibid.*, pp. 9-18.
9. Sheeby, J. F. (1963). Screening for Toxic Materials in the Design Engineering Phase, *ibid.*, pp. 19-32.
10. Honma, M., and Rinehart, R. W. (1963). Method of Detection and Quantification, *ibid.*, pp. 155-170.
11. Carhart, H. W. (1963). Detection of Contaminants in the Nuclear Submarine Atmosphere, *ibid.*, pp. 171-180.
12. Johnson, E. (1963). Atmosphere Monitoring in Nuclear Submarines, *ibid.*, pp. 223-232.

Contrails

13. Donner, W., and Weber, T. B. (1963). Present and Potential Instrumental Methods for Manned Spacecraft, *ibid.*, pp. 181-200.
14. Watson, E. S. (1963). Optical Instrument Methods for Manned Spacecraft: Ultraviolet, Visible and Infrared Spectrophotometry, *ibid.*, pp. 201-214.
15. Weber, T. B. (1963). Atmosphere Monitoring in the Space Cabin Simulator, *ibid.*, pp. 233-256.
16. Saunders, R. A. (1962). Analysis of Spacecraft Atmosphere, Naval Research Laboratory Report 5816 (AD No. 288255).
17. McKee, H. C., Rhoades, J. W., Wheeler, R. J. and Burchfield, H. P. (1963). Gas Chromatographic Measurement of Trace Contaminants in a Simulated Space Cabin, National Aeronautics and Space Administration TND-1825, under Contract No. NASw-150 with Southwest Research Institute, San Antonio, Texas.
18. Christianson, J. C., Sokol, R. J., Bethea, R. M. (1965). Gas Chromatographic Analysis of Simulated Spacecraft Atmospheres, *J. Gas Chromatography*, Volume 3, No. 4, pp. 115-120.
19. Boebel, C. P., Mackie, N. A., and Quaintance, C. C. (1962). Outgassing Studies of Space Materials, Transactions of the Ninth Vacuum Symposium, pp. 307-310. G. H. Bancroft, Ed., MacMillan Co., N. Y.
20. Gonnella, N. (1964). Chromatographic Analysis of Evolved Contaminants from Space Craft Materials, 15th Annual Mid-American Symposium on Spectroscopy. Chicago, Ill., June 1964.
21. Schwenk, U., Hachenberg, H. and Forderreuther (1961). Trace Analysis by Using the Flame Ionization Detector and Packed Columns in Gas Chromatography, *Brennstoff-Chemie*, Vol. 42, No. 9, pp. 295-6.
22. McLafferty, F. W. (1957). Mass Spectrometry in Chemical Research and Production, *Applied Spectroscopy*, Vol. 11, No. 4, pp. 148-156.
23. Biemann, K. (1962). Mass Spectrometry Organic Chemical Applications, McGraw-Hill, Chapter 4, pp. 171-172.

DOCUMENT CONTROL DATA - R&D		
<i>(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)</i>		
1. ORIGINATING ACTIVITY (Corporate author) Monsanto Research Corporation 1515 Nicholas Road Dayton, Ohio 45407		2a. REPORT SECURITY CLASSIFICATION UNCLASSIFIED
		2b. GROUP N/A
3. REPORT TITLE IDENTIFICATION OF VOLATILE CONTAMINANTS OF SPACE CABIN MATERIALS		
4. DESCRIPTIVE NOTES (Type of report and inclusive dates) Final report, June 1964 - September 1965		
5. AUTHOR(S) (Last name, first name, initial) Pustinger, J. V., Jr. Hodgson, F. N. Ross, W. D.		
6. REPORT DATE June 1966	7a. TOTAL NO. OF PAGES 208	7b. NO. OF REFS 23
8a. CONTRACT OR GRANT NO. AF 33(615)-1779	9a. ORIGINATOR'S REPORT NUMBER(S)	
b. PROJECT NO. 6302		
c. Task No. 630204	9b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report)	
d.	AMRL-TR-66-53	
10. AVAILABILITY/LIMITATION NOTICES Distribution of this document is unlimited.		
11. SUPPLEMENTARY NOTES	12. SPONSORING MILITARY ACTIVITY Aerospace Medical Research Laboratories, Aerospace Medical Division, Air Force Systems Command, Wright-Patterson AFB, O.	
13. ABSTRACT Fifty-five candidate materials for space cabin construction were stored for 30, 60, and 90 day periods at 23-25°C, and 20-40% R.H. in environments of air at a pressure of one atmosphere and oxygen at 5 psia. The composition of the gas-off products were determined by mass spectrometry and gas chromatography. Additional analyses were performed on desorbates from four carbon canisters from space cabin simulators and the hydrolysis products of MCS 198.		

14. KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT

Space cabin candidate materials
 Volatile contaminant analyses
 Mass spectrometry
 Gas chromatography

INSTRUCTIONS

1. ORIGINATING ACTIVITY: Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization (corporate author) issuing the report.

2a. REPORT SECURITY CLASSIFICATION: Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

2b. GROUP: Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

3. REPORT TITLE: Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parenthesis immediately following the title.

4. DESCRIPTIVE NOTES: If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.

5. AUTHOR(S): Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.

6. REPORT DATE: Enter the date of the report as day, month, year, or month, year. If more than one date appears on the report, use date of publication.

7a. TOTAL NUMBER OF PAGES: The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. NUMBER OF REFERENCES: Enter the total number of references cited in the report.

8a. CONTRACT OR GRANT NUMBER: If appropriate, enter the applicable number of the contract or grant under which the report was written.

8b, 8c, & 8d. PROJECT NUMBER: Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.

9a. ORIGINATOR'S REPORT NUMBER(S): Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. OTHER REPORT NUMBER(S): If the report has been assigned any other report numbers (either by the originator or by the sponsor), also enter this number(s).

10. AVAILABILITY/LIMITATION NOTICES: Enter any limitations on further dissemination of the report, other than those

imposed by security classification, using standard statements such as:

- (1) "Qualified requesters may obtain copies of this report from DDC."
- (2) "Foreign announcement and dissemination of this report by DDC is not authorized."
- (3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through _____."
- (4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through _____."
- (5) "All distribution of this report is controlled. Qualified DDC users shall request through _____."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. SUPPLEMENTARY NOTES: Use for additional explanatory notes.

12. SPONSORING MILITARY ACTIVITY: Enter the name of the departmental project office or laboratory sponsoring (paying for) the research and development. Include address.

13. ABSTRACT: Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS), (S), (C), or (U).

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. KEY WORDS: Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical content. The assignment of links, rules, and weights is optional.